

Last Revision Date: April 2005
Supersedes: April 1999

PRESSURE SENSITIVE ADHESIVE

DESCRIPTION: PLIOBOND 5001 pressure sensitive adhesive is a permanent adhesive with clarity and strength properties that make it ideal for pressure sensitive tape, label stock and adhesive-backed foam. It has shown excellent adhesion to paper, polyurethane foam, polyethylene foam, foil, and polyester film.

PLIOBOND 5001 pressure sensitive adhesive demonstrates high tack, minimum cold flow, good aging characteristics, high peel strength, and especially, high shear strength. In test evaluations in film applications, PLIOBOND 5001 pressure sensitive adhesive samples were subjected to 1,500 gram loads, in contrast to the usual 500 gram load, on a ½ inch overlap and aged at room temperature. The results show that PLIOBOND 5001 pressure sensitive adhesive withstands extreme load conditions for long periods of time (see Table 2).

PLIOBOND 5001 versus ACRYLIC ADHESIVES: When compared to several acrylic adhesives, PLIOBOND 5001 pressure sensitive adhesive shows superior shear and peel adhesion, with and without aging. It is far superior to acrylic adhesives in initial shear and peel adhesion tests (see Table 3). After aging, it still exhibits higher peel values than the acrylics.

The testing showed one week's aging caused a sharp increase in the shear value of the acrylic adhesives. This increase is due to the adhesive cross-linking during aging. The acrylics, however, were not cross-linked during the drying cycle and may require a much higher temperature to initiate this reaction in a short drying cycle.

Aging has no effect on PLIOBOND 5001 pressure sensitive adhesive other than causing a slight increase in peel adhesion. Peel values of the acrylics changed very little during aging. After two weeks, their peel values were virtually unchanged, although shear was further increased.

PLIOBOND 5001 pressure sensitive adhesive also demonstrates better tack properties than the acrylics tested. Rolling ball tack tests run on aged samples clearly indicate that the tack of acrylic pressure sensitive adhesives does not compare with that of PLIOBOND 5001 pressure sensitive adhesive. Thus, PLIOBOND 5001 pressure sensitive adhesive is easier to handle and more likely to make a satisfactory bond. With the exception of polyvinyl chloride substrates, PLIOBOND 5001 pressure sensitive adhesive was shown to be superior to the acrylic adhesives for pressure sensitive applications.

SUGGESTED USES: PLIOBOND 5001 adhesive can be used as a pressure sensitive adhesive for paper, foams, and films.

©Ashland, 1999, 2005

Ashland Inc., Performance Materials • PO Box 2219 • Columbus, OH 43216 • Tel: 1.800.322.6580 – Customer Service • Tel: 1.614.790.3333 • Fax: 1.614.790.3206



Ashland is committed to the continuous evolution of technology and service solutions that promote health, safety and environmental protection around the world.

All statements, information and data presented herein are believed to be accurate and reliable but are not to be taken as a guarantee, express warranty or implied warranty of merchantability or fitness for a particular purpose, or representation, express or implied, for which seller assumes legal responsibility, and they are offered solely for your consideration, investigation and verification. Statements or suggestions concerning possible use of this product are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe on any patent.

* Responsible Care and the Responsible Care logo are registered service marks of the American Chemistry Council in the U.S. and of different entities in other countries.

® Registered trademark, Ashland
© 2008 Ashland

ASHLAND.

TABLE 1
TYPICAL PHYSICAL PROPERTIES AT 77°F *

Base	Synthetic Rubber Resin Blend
Color	Transparent Amber
Solids by Weight, %	43 +/- 3
Viscosity, cps Brookfield RVT Spindle No. 3 at 10 rpm	3,750 +/- 1750
Specific Gravity	0.7755
Pounds per Gallon	6.4595
Flash Point, °F, (TCC)	Less than zero
Estimated Coverage	500-550 sq ft/gal/dry mil

* Typical Values: (Based on material tested in our laboratories but varies from sample to sample. Typical values should not be construed as a guaranteed analysis of any specific lot or as specification items.)

METHOD OF APPLICATION: Apply PLIOBOND 5001 adhesive in a 1-2 mil thickness. PLIOBOND 5001 adhesive can be dried at room temperature or forced dried in a range of 100°F to 200°F for three to five minutes. When the PLIOBOND 5001 adhesive is dry, the adhesive film will remain tacky and can be bonded as desired.

TABLE 2
TYPICAL ADHESION PROPERTIES ON DRIED FILM

<u>* TEST</u>	<u>Pressure Sensitive Adhesive</u>
Peel Strength	62-64 oz/in width
Aged Peel Strength	78-80 oz/ in width
Shear Strength (1,500 grams test)	1 month (no movement)
Aged Shear Strength (1,500 grams test)	8 days to failure

*** TEST METHODS USED FOR EVALUATION**

Peel Strength	180° Peel test using ASTM D-903-49
Shear Adhesion	PSTC-7 using ½" lap shear with 1,500 gram weight
Aged Shear Test	Sample aged at 158°F

PLIOGRIP™ 5001
Pressure Sensitive Adhesive
(Continued)

*Test	PLIOBOND 5001 Pressure Sensitive Adhesive	Acrylic A	Acrylic B	Acrylic C
Shear Strength (1,000 grams)	Removed after 17 days	106 min	117 min	24 min
Aged Shear Strength 1 week at 158°F 2 weeks at 158°F 3 weeks at Room Temperature	Removed after 11 days Removed after 9 days No Movement	84 hrs 115 hrs 40 min	Removed after 11 days Removed after 9 days 206 min	15 hrs 54 hrs 109 min
Peel Strength, Lbs./in, Fresh 1 week at 158°F 2 weeks at 158°F 3 weeks at Room Temperature	4.4 4.6-4.9 4.6-4.9 4.3-4.6	2.7 2.8 2.8 3.0	3.0 2.5 2.5 3.3	2.2 1.9 2.1 2.5
Tack Aged 2 weeks at 158°F	2 in	Off Scale	Off Scale	6 3/4 in

*** TEST METHODS USED FOR EVALUATION**

Shear Strength	PSTC-7 using 1/2" lap shear with 1,000 gram weight
Peel Strength	180° Peel test using ASTM D903-49
Tack	PSTC-6 using Rolling Ball Test

HANDLING: PLIOBOND 5001 pressure sensitive adhesive contains ingredients that could be harmful if mishandled. Contact with skin and eyes should be avoided and the recommended personal protective equipment be should be worn.

Ashland maintains Material Safety Data Sheets on all of its products. Material Safety Data Sheets contain health and safety information for your development of appropriate product handling procedures to protect your employees and customers.


Our Material Safety Data Sheets should be read and understood by all of your supervisory personnel and employees before using Ashland products in your facilities.

RECOMMENDED STORAGE: When PLIOBOND 5001 pressure sensitive adhesive is stored indoors, out of direct sunlight, and in the original, unopened container between 60°F and 80°F, the shelf life is six months. Always rotate stock.

DOT Label Required: Extremely Flammable Liquid, UN 1133

CODE: 584501

Ashland Inc., Performance Materials • PO Box 2219 • Columbus, OH 43216 • Tel: 1.800.322.6580 – Customer Service • Tel: 1.614.790.3333 • Fax: 1.614.790.3206

 Ashland is committed to the continuous evolution of technology and service solutions that promote health, safety and environmental protection around the world.

All statements, information and data presented herein are believed to be accurate and reliable but are not to be taken as a guarantee, express warranty or implied warranty of merchantability or fitness for a particular purpose, or representation, express or implied, for which seller assumes legal responsibility, and they are offered solely for your consideration, investigation and verification. Statements or suggestions concerning possible use of this product are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe on any patent.

* Responsible Care and the Responsible Care logo are registered service marks of the American Chemistry Council in the U.S. and of different entities in other countries.
 * Registered trademark, Ashland
 © 2008 Ashland

ASHLAND.