

ARALDITE® AW 106

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	05/02/2017	400001010251	Date of first issue: 05/02/2017

SECTION 1. IDENTIFICATION

Product name : ARALDITE® AW 106

Manufacturer or supplier's details

Company name of supplier : Huntsman Advanced Materials Americas LLC
Address : P.O. Box 4980
The Woodlands,
TX 77387
United States of America (USA)
Telephone : Non-Emergency: (800) 257-5547
E-mail address of person responsible for the SDS : MSDS@huntsman.com

Emergency telephone number : Chemtrec: (800) 424-9300 or (703) 527-3887

Recommended use of the chemical and restrictions on use

Recommended use : Epoxy constituents

SECTION 2. HAZARDS IDENTIFICATION**GHS classification in accordance with 29 CFR 1910.1200**

Skin irritation : Category 2
Eye irritation : Category 2A
Skin sensitisation : Category 1
Acute aquatic toxicity : Category 2
Chronic aquatic toxicity : Category 2

GHS label elements

Hazard pictograms :



Signal word : Warning

Hazard statements : H315 Causes skin irritation.
H317 May cause an allergic skin reaction.
H319 Causes serious eye irritation.
H411 Toxic to aquatic life with long lasting effects.

Precautionary statements : **Prevention:**
P261 Avoid breathing dust/ fume/ gas/ mist/ vapours/ spray.
P264 Wash skin thoroughly after handling.
P272 Contaminated work clothing should not be allowed out of

ARALDITE® AW 106

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	05/02/2017	400001010251	Date of first issue: 05/02/2017

the workplace.

P273 Avoid release to the environment.

P280 Wear protective gloves/ eye protection/ face protection.

Response:

P302 + P352 IF ON SKIN: Wash with plenty of soap and water.

P305 + P351 + P338 IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.

P333 + P313 If skin irritation or rash occurs: Get medical advice/ attention.

P337 + P313 If eye irritation persists: Get medical advice/ attention.

P362 Take off contaminated clothing and wash before reuse.

P391 Collect spillage.

Storage:

Not available

Disposal:

P501 Dispose of contents/container to an approved facility in accordance with local, regional, national and international regulations.

Other hazards

None known.

SECTION 3. COMPOSITION/INFORMATION ON INGREDIENTS

Substance / Mixture : Mixture

Hazardous components

Chemical name	CAS-No.	Concentration (% w/w)
Bisphenol A epoxy resin	25068-38-6	70 - 90
bisphenol F-epoxy resin	9003-36-5	5 - 10
bisphenol A - epoxy resins, number average MW >700 - <1100	25068-38-6	1 - 5
Silicon, amorphous	112945-52-5	1 - 5

The specific chemical identity and/or exact percentage (concentration) of composition may be withheld as a trade secret.

SECTION 4. FIRST AID MEASURES

General advice	: Move out of dangerous area. Show this safety data sheet to the doctor in attendance. Do not leave the victim unattended.
If inhaled	: If unconscious, place in recovery position and seek medical advice. If symptoms persist, call a physician.
In case of skin contact	: If skin irritation persists, call a physician. If on skin, rinse well with water. If on clothes, remove clothes.

ARALDITE® AW 106

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	05/02/2017	400001010251	Date of first issue: 05/02/2017

In case of eye contact	: Immediately flush eye(s) with plenty of water. Remove contact lenses. Protect unharmed eye. Keep eye wide open while rinsing. If eye irritation persists, consult a specialist.
If swallowed	: Keep respiratory tract clear. Do not give milk or alcoholic beverages. Never give anything by mouth to an unconscious person. If symptoms persist, call a physician.
Most important symptoms and effects, both acute and delayed	: None known.
Notes to physician	: No information available.

SECTION 5. FIREFIGHTING MEASURES

Suitable extinguishing media	: No data is available on the product itself.
Unsuitable extinguishing media	: High volume water jet
Specific hazards during firefighting	: No data is available on the product itself. Do not allow run-off from fire fighting to enter drains or water courses.
Hazardous combustion products	: No hazardous combustion products are known No data is available on the product itself.
Specific extinguishing methods	: No data is available on the product itself.
Further information	: Collect contaminated fire extinguishing water separately. This must not be discharged into drains. Fire residues and contaminated fire extinguishing water must be disposed of in accordance with local regulations.
Special protective equipment for firefighters	: Wear self-contained breathing apparatus for firefighting if necessary.

SECTION 6. ACCIDENTAL RELEASE MEASURES

Personal precautions, protective equipment and emergency procedures	: Use personal protective equipment.
---	--------------------------------------

ARALDITE® AW 106

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	05/02/2017	400001010251	Date of first issue: 05/02/2017

Environmental precautions : Prevent product from entering drains.
Prevent further leakage or spillage if safe to do so.
If the product contaminates rivers and lakes or drains inform respective authorities.

Methods and materials for containment and cleaning up : Soak up with inert absorbent material (e.g. sand, silica gel, acid binder, universal binder, sawdust).
Keep in suitable, closed containers for disposal.

SECTION 7. HANDLING AND STORAGE

Advice on protection against fire and explosion : Normal measures for preventive fire protection.

Advice on safe handling : Do not breathe vapours/dust.
Avoid exposure - obtain special instructions before use.
Avoid contact with skin and eyes.
For personal protection see section 8.
Smoking, eating and drinking should be prohibited in the application area.
Dispose of rinse water in accordance with local and national regulations.
Persons susceptible to skin sensitisation problems or asthma, allergies, chronic or recurrent respiratory disease should not be employed in any process in which this mixture is being used.

Conditions for safe storage : Keep container tightly closed in a dry and well-ventilated place.
Containers which are opened must be carefully resealed and kept upright to prevent leakage.
Electrical installations / working materials must comply with the technological safety standards.

Materials to avoid : Strong acids

Strong bases

Strong oxidizing agents

SECTION 8. EXPOSURE CONTROLS/PERSONAL PROTECTION**Components with workplace control parameters**

Components	CAS-No.	Value type (Form of exposure)	Control parameters / Permissible concentration	Basis
Silicon, amorphous	112945-52-5	TWA (Dust)	20 Million particles per cubic foot (Silica)	OSHA Z-3

ARALDITE® AW 106

Version 1.0 Revision Date: 05/02/2017 SDS Number: 400001010251 Date of last issue: -
 Date of first issue: 05/02/2017

		TWA (Dust)	80 mg/m ³ / %SiO ₂ (Silica)	OSHA Z-3
		TWA (Dust)	20 Million particles per cubic foot (Silica)	OSHA Z-3
		TWA (Dust)	80 mg/m ³ / %SiO ₂ (Silica)	OSHA Z-3

Personal protective equipment

- Respiratory protection : Wear a full face respirator conforming to EN 136 with type A/P2 filter or better
- Hand protection
- Material : butyl-rubber
- Break through time : > 8 h
- Material : Solvent-resistant gloves (butyl-rubber)
- Material : Nitrile rubber
- Break through time : 10 - 480 min
- Material : Neoprene gloves
- Remarks : The suitability for a specific workplace should be discussed with the producers of the protective gloves.
- Eye protection : Eye wash bottle with pure water
Tightly fitting safety goggles
Wear face-shield and protective suit for abnormal processing problems.
- Skin and body protection : Impervious clothing
Choose body protection according to the amount and concentration of the dangerous substance at the work place.
- Hygiene measures : When using do not eat or drink.
When using do not smoke.
Wash hands before breaks and at the end of workday.

SECTION 9. PHYSICAL AND CHEMICAL PROPERTIES

- Appearance : paste
- Colour : No data is available on the product itself.
- Odour : slight
- Odour Threshold : No data is available on the product itself.
- pH : ca. 6 (20 °C)
Concentration: 500 g/l
- Freezing point : No data is available on the product itself.

ARALDITE® AW 106

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	05/02/2017	400001010251	Date of first issue: 05/02/2017

Melting point	No data is available on the product itself.
Boiling point	: > 200 °C
Flash point	: 210 °C Method: Pensky-Martens closed cup, closed cup
Evaporation rate	: No data is available on the product itself.
Flammability (solid, gas)	: No data is available on the product itself.
Flammability (liquids)	: No data is available on the product itself.
Upper explosion limit	: No data is available on the product itself.
Lower explosion limit	: No data is available on the product itself.
Vapour pressure	: < 0.001 hPa (20 °C)
Relative vapour density	: No data is available on the product itself.
Relative density	: 1.14 - 1.19
Density	: 1.15 g/cm ³ (25 °C)
Solubility(ies)	
Water solubility	: practically insoluble (20 °C)
Solubility in other solvents	: No data is available on the product itself.
Partition coefficient: n-octanol/water	: No data is available on the product itself.
Auto-ignition temperature	: No data is available on the product itself.
Decomposition temperature	: > 200 °C
Self-Accelerating decomposition temperature (SADT)	: No data is available on the product itself.
Viscosity	
Viscosity, dynamic	: 30,000 - 50,000 mPa.s (25 °C)
Explosive properties	: No data is available on the product itself.
Oxidizing properties	: No data is available on the product itself.
Particle size	: No data is available on the product itself.

SECTION 10. STABILITY AND REACTIVITY

Reactivity	: No decomposition if stored and applied as directed.
Chemical stability	: No decomposition if stored and applied as directed.

ARALDITE® AW 106

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	05/02/2017	400001010251	Date of first issue: 05/02/2017

Possibility of hazardous reactions	: No decomposition if stored and applied as directed.
	: No decomposition if stored and applied as directed.
	: No decomposition if stored and applied as directed.
Conditions to avoid	: No data available
Incompatible materials	: No data available
Hazardous decomposition products	: Carbon oxides
	: Burning produces noxious and toxic fumes.

SECTION 11. TOXICOLOGICAL INFORMATION

Information on likely routes of exposure : No data is available on the product itself.

Acute toxicity**Components:**

Bisphenol A epoxy resin:

Acute oral toxicityComponents : LD50 (Rat, female): > 2,000 mg/kg
Method: OECD Test Guideline 420
Assessment: The substance or mixture has no acute oral toxicity

bisphenol F-epoxy resin:

Acute oral toxicityComponents : LD50 (Rat, male and female): > 5,000 mg/kg
Method: OECD Test Guideline 401

bisphenol A - epoxy resins, number average MW >700 - <1100:

Acute oral toxicityComponents : LD50 (Rat, female): > 2,000 mg/kg
Method: OECD Test Guideline 420
Assessment: The substance or mixture has no acute oral toxicity

Silicon, amorphous:

Acute oral toxicityComponents : LD50 (Rat): > 5,000 mg/kg
Method: OECD Test Guideline 401

Components:

bisphenol A - epoxy resins, number average MW >700 - <1100:

Acute inhalation toxicity : LC0 (Rat, male): 10 ppt
Exposure time: 5 h
Test atmosphere: vapour

Silicon, amorphous:

Acute inhalation toxicity : LC50 (Rat, male and female): > 58.8 mg/l
Exposure time: 4 h

ARALDITE® AW 106

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	05/02/2017	400001010251	Date of first issue: 05/02/2017

Test atmosphere: dust/mist
Method: OECD Test Guideline 403

Components:

Bisphenol A epoxy resin:

Acute dermal toxicity : LD50 (Rat, male and female): > 2,000 mg/kg
Method: OECD Test Guideline 402
Assessment: The substance or mixture has no acute dermal toxicity

bisphenol F-epoxy resin:

Acute dermal toxicity : LD50 (Rat, male and female): > 2,000 mg/kg
Method: OECD Test Guideline 402
Assessment: The substance or mixture has no acute dermal toxicity

bisphenol A - epoxy resins, number average MW >700 - <1100:

Acute dermal toxicity : LD50 (Rat, male and female): > 2,000 mg/kg
Method: OECD Test Guideline 402
Assessment: The substance or mixture has no acute dermal toxicity

Silicon, amorphous:

Acute dermal toxicity : LD50 (Rabbit): > 5,000 mg/kg

Acute toxicity (other routes of administration) : No data available

Skin corrosion/irritation**Product:**

Remarks: May cause skin irritation and/or dermatitis.

Serious eye damage/eye irritation**Product:**

Remarks: May cause irreversible eye damage.

Respiratory or skin sensitisation**Product:**

Remarks: Causes sensitisation.

Assessment: No data available

Germ cell mutagenicity**Components:**

Bisphenol A epoxy resin:

ARALDITE® AW 106

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	05/02/2017	400001010251	Date of first issue: 05/02/2017

Genotoxicity in vitro : Metabolic activation: with and without metabolic activation
Method: OECD Test Guideline 476
Result: positive

Concentration: 0 - 5000 ug/plate
Metabolic activation: with and without metabolic activation
Method: OECD Test Guideline 471
Result: positive

bisphenol F-epoxy resin:
Genotoxicity in vitro : Metabolic activation: with and without metabolic activation
Method: OECD Test Guideline 471
Result: positive

Metabolic activation: with and without metabolic activation
Method: OECD Test Guideline 473
Result: positive

Metabolic activation: with and without metabolic activation
Method: OECD Test Guideline 476
Result: positive

bisphenol A - epoxy resins, number average MW >700 - <1100:
Genotoxicity in vitro : Metabolic activation: with and without metabolic activation
Method: OECD Test Guideline 476
Result: positive

Concentration: 0 - 5000 ug/plate
Metabolic activation: with and without metabolic activation
Method: OECD Test Guideline 471
Result: positive

Silicon, amorphous:
Genotoxicity in vitro : Metabolic activation: with and without metabolic activation
Method: OECD Test Guideline 473
Result: negative

Metabolic activation: with and without metabolic activation
Method: OECD Test Guideline 476
Result: negative

Metabolic activation: with and without metabolic activation
Method: OECD Test Guideline 471
Result: negative

Components:

Bisphenol A epoxy resin:
Genotoxicity in vivo : Cell type: Germ
Application Route: Oral
Method: OECD Test Guideline 478
Result: negative

Cell type: Somatic
Application Route: Oral
Dose: 0 - 5000 mg/kg

ARALDITE® AW 106

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	05/02/2017	400001010251	Date of first issue: 05/02/2017

Method: OPPTS 870.5395
Result: negative

bisphenol F-epoxy resin:
Genotoxicity in vivo

: Cell type: Somatic
Application Route: Oral
Exposure time: 48 h
Dose: 2000 mg/kg
Method: OECD Test Guideline 474
Result: negative

Cell type: Somatic
Application Route: Oral
Dose: 2000 mg/kg
Method: OECD Test Guideline 486
Result: negative

bisphenol A - epoxy resins, number average MW >700 - <1100:
Genotoxicity in vivo

: Cell type: Germ
Application Route: Oral
Method: OECD Test Guideline 478
Result: negative

Cell type: Somatic
Application Route: Oral
Dose: 0 - 5000 mg/kg
Method: OPPTS 870.5395
Result: negative

Silicon, amorphous:
Genotoxicity in vivo

: Application Route: Inhalation
Dose: 50 mg/m³
Result: negative

Components:

Bisphenol A epoxy resin:
Germ cell mutagenicity-
Assessment

: Weight of evidence does not support classification as a germ cell mutagen.

bisphenol A - epoxy resins, number average MW >700 - <1100:
Germ cell mutagenicity-
Assessment

: Animal testing did not show any mutagenic effects.

Germ cell mutagenicity-
Assessment

: No data available

Carcinogenicity**Components:**

Bisphenol A epoxy resin:
Species: Rat, (male and female)
Application Route: Oral
Exposure time: 24 month(s)
Dose: 15 mg/kg

ARALDITE® AW 106

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	05/02/2017	400001010251	Date of first issue: 05/02/2017

Frequency of Treatment: 7 days/week
Method: OECD Test Guideline 453
Result: negative

Species: Mouse, (male)
Application Route: Dermal
Exposure time: 24 month(s)
Dose: 0.1 mg/kg
Frequency of Treatment: 3 days/week
Method: OECD Test Guideline 453
Result: negative

Species: Rat, (female)
Application Route: Dermal
Exposure time: 24 month(s)
Dose: 1 mg/kg
Frequency of Treatment: 5 days/week
Method: OECD Test Guideline 453
Result: negative

bisphenol A - epoxy resins, number average MW >700 - <1100:
Species: Rat, (male and female)
Application Route: Oral
Exposure time: 24 month(s)
Dose: 15 mg/kg
Frequency of Treatment: 7 daily
Method: OECD Test Guideline 453
Result: negative

Species: Mouse, (male)
Application Route: Dermal
Exposure time: 24 month(s)
Dose: .1 mg/kg
Frequency of Treatment: 3 daily
Method: OECD Test Guideline 453
Result: negative

Species: Rat, (female)
Application Route: Dermal
Exposure time: 24 month(s)
Dose: 1 mg/kg
Frequency of Treatment: 5 daily
Method: OECD Test Guideline 453
Result: negative

Silicon, amorphous:
Species: Rat, (male and female)
Application Route: Oral
Exposure time: 103 weeks
Dose: 1800 - 3200 mg/kg
Frequency of Treatment: 7 daily
Method: OECD Test Guideline 453
Result: negative

Components:

ARALDITE® AW 106

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	05/02/2017	400001010251	Date of first issue: 05/02/2017

bisphenol A - epoxy resins, number average MW >700 - <1100:

Carcinogenicity - : Animal testing did not show any carcinogenic effects.

Assessment

IARC

No component of this product present at levels greater than or equal to 0.1% is identified as probable, possible or confirmed human carcinogen by IARC.

ACGIH

No component of this product present at levels greater than or equal to 0.1% is identified as a carcinogen or potential carcinogen by ACGIH.

OSHA

No component of this product present at levels greater than or equal to 0.1% is identified as a carcinogen or potential carcinogen by OSHA.

NTP

No component of this product present at levels greater than or equal to 0.1% is identified as a known or anticipated carcinogen by NTP.

Reproductive toxicity**Components:**

Bisphenol A epoxy resin:

Effects on fertility

: Test Type: Two-generation study
Species: Rat, male and female
Application Route: Oral
Dose: >750 milligram per kilogram
General Toxicity - Parent: No-observed-effect level: 540 mg/kg body weight
General Toxicity F1: No-observed-effect level: 540 mg/kg body weight
Symptoms: No adverse effects
Method: OECD Test Guideline 416
Result: No effects on fertility and early embryonic development were detected.

bisphenol F-epoxy resin:

Species: Rat, male and female
Application Route: Oral
Method: OECD Test Guideline 416
Result: No effects on fertility and early embryonic development were detected.

bisphenol A - epoxy resins, number average MW >700 - <1100:

Species: Rat, male and female
Application Route: Oral
Method: OECD Test Guideline 416
Result: No effects on fertility and early embryonic development were detected.

Components:

Bisphenol A epoxy resin:

Effects on foetal development

: Species: Rabbit, female
Application Route: Dermal
General Toxicity Maternal: No observed adverse effect level:

ARALDITE® AW 106

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	05/02/2017	400001010251	Date of first issue: 05/02/2017

30 mg/kg body weight
Method: Other guidelines
Result: No teratogenic effects

Species: Rabbit, female
Application Route: Oral
General Toxicity Maternal: No observed adverse effect level:
60 mg/kg body weight
Method: OECD Test Guideline 414
Result: No teratogenic effects

Species: Rat, female
Application Route: Oral
General Toxicity Maternal: No observed adverse effect level:
180 mg/kg body weight
Method: OECD Test Guideline 414
Result: No teratogenic effects

bisphenol F-epoxy resin:

Species: Rabbit, female
Application Route: Dermal
General Toxicity Maternal: No observed adverse effect level:
30 mg/kg body weight
Result: No teratogenic effects

bisphenol A - epoxy resins, number average MW >700 - <1100:

Species: Rabbit, female
Application Route: Dermal
General Toxicity Maternal: No observed adverse effect level:
30 mg/kg body weight
Method: Other guidelines
Result: No teratogenic effects

Species: Rabbit, female
Application Route: Oral
General Toxicity Maternal: No observed adverse effect level:
60 mg/kg body weight
Method: OECD Test Guideline 414
Result: No teratogenic effects

Species: Rat, female
Application Route: Oral
General Toxicity Maternal: No observed adverse effect level:
180 mg/kg body weight
Method: OECD Test Guideline 414
Result: No teratogenic effects

Silicon, amorphous:

Species: Mouse
Application Route: Oral
General Toxicity Maternal: No observed adverse effect level:
1,340 mg/kg body weight
Method: OECD Test Guideline 414
Result: No teratogenic effects

Species: Rabbit

ARALDITE® AW 106

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	05/02/2017	400001010251	Date of first issue: 05/02/2017

Application Route: Oral
General Toxicity Maternal: No observed adverse effect level:
1,600 mg/kg body weight
Method: OECD Test Guideline 414
Result: No teratogenic effects

Species: Rat
Application Route: Oral
General Toxicity Maternal: No observed adverse effect level:
1,350 mg/kg body weight
Method: OECD Test Guideline 414
Result: No teratogenic effects

Components:

bisphenol A - epoxy resins, number average MW >700 - <1100:

Reproductive toxicity - : No evidence of adverse effects on sexual function and fertility,
Assessment or on development, based on animal experiments.

STOT - single exposure

No data available

STOT - repeated exposure

No data available

Repeated dose toxicity**Components:**

Bisphenol A epoxy resin:
Species: Rat, male and female
NOAEL: 50 mg/kg
Application Route: Ingestion
Exposure time: 14 Weeks
Number of exposures: 7 d
Method: Subchronic toxicity

Species: Rat, male and female
NOEL: 10 mg/kg
Application Route: Skin contact
Exposure time: 13 Weeks
Number of exposures: 5 d
Method: Subchronic toxicity

Species: Mouse, male
NOAEL: 100 mg/kg
Application Route: Skin contact
Exposure time: 13 Weeks
Number of exposures: 3 d
Method: Subchronic toxicity

bisphenol F-epoxy resin:
Species: Rat, male and female
NOAEL: 250 mg/kg

ARALDITE® AW 106

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	05/02/2017	400001010251	Date of first issue: 05/02/2017

Application Route: Ingestion
Exposure time: 13 Weeks
Number of exposures: 7 d
Method: Subchronic toxicity

bisphenol A - epoxy resins, number average MW >700 - <1100:

Species: Rat, male and female
NOAEL: 50 mg/kg
Application Route: Ingestion
Exposure time: 14 Weeks
Number of exposures: 7 d
Method: Subchronic toxicity

Species: Rat, male and female
NOEL: 10 mg/kg
Application Route: Skin contact
Exposure time: 13 Weeks
Number of exposures: 5 d
Method: Subchronic toxicity

Silicon, amorphous:

Species: Rat, male and female
NOAEL: 7950 - 8980 mg/kg
Application Route: Ingestion
Exposure time: 4,320 h
Number of exposures: 7 d
Method: Subchronic toxicity

Species: Rat, male and female
: 4000 - 4500 mg/m³
Application Route: Ingestion
Test atmosphere: dust/mist
Exposure time: 13 Weeks
Number of exposures: 7 d
Method: OECD Test Guideline 413

Repeated dose toxicity - : No data available
Assessment

Aspiration toxicity

No data available

Experience with human exposure

General Information: No data available

Inhalation: No data available

Skin contact: No data available

ARALDITE® AW 106

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	05/02/2017	400001010251	Date of first issue: 05/02/2017

Eye contact: No data available

Ingestion: No data available

Toxicology, Metabolism, Distribution

No data available

Neurological effects

No data available

Further information**Product:**

Remarks: No data available

SECTION 12. ECOLOGICAL INFORMATION**Ecotoxicity****Components:**

Bisphenol A epoxy resin:

Toxicity to fish : LC50 (Oncorhynchus mykiss (rainbow trout)): 1.5 mg/l
Exposure time: 96 h
Test Type: static test
Test substance: Fresh water
Method: OECD Test Guideline 203

bisphenol F-epoxy resin:

Toxicity to fish : LC50 (Oncorhynchus mykiss (rainbow trout)): 0.55 mg/l
Exposure time: 96 h
Test Type: semi-static test
Test substance: Fresh water
Method: OECD Test Guideline 203

Silicon, amorphous:

Toxicity to fish : LL50 (Brachydanio rerio (zebrafish)): > 10,000 mg/l
Exposure time: 96 h
Test Type: static test
Test substance: Fresh water
Method: OECD Test Guideline 202

Components:

Bisphenol A epoxy resin:

Toxicity to daphnia and other aquatic invertebrates : EC50 (Daphnia magna (Water flea)): 2.7 mg/l
Exposure time: 48 h
Test Type: static test
Test substance: Fresh water

ARALDITE® AW 106

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	05/02/2017	400001010251	Date of first issue: 05/02/2017

bisphenol F-epoxy resin:

Toxicity to daphnia and other aquatic invertebrates : EC50 (Daphnia magna (Water flea)): 1.6 mg/l
 Exposure time: 48 h
 Test Type: static test
 Test substance: Fresh water
 Method: OECD Test Guideline 202

Silicon, amorphous:

Toxicity to daphnia and other aquatic invertebrates : EL50 (Daphnia magna (Water flea)): >= 1,000 mg/l
 Exposure time: 24 h
 Test Type: static test
 Test substance: Fresh water
 Method: OECD Test Guideline 202

Components:

Bisphenol A epoxy resin:

Toxicity to algae : EC50 (Selenastrum capricornutum (green algae)): 9.4 mg/l
 Exposure time: 72 h
 Test Type: static test
 Test substance: Fresh water
 Method: EPA-660/3-75-009

bisphenol F-epoxy resin:

Toxicity to algae : EC50 (Selenastrum capricornutum (green algae)): 1.8 mg/l
 Exposure time: 72 h
 Test Type: static test
 Test substance: Fresh water
 Method: OECD Test Guideline 201

Silicon, amorphous:

Toxicity to algae : EL50 (Desmodesmus subspicatus (Scenedesmus subspicatus)): > 10,000 mg/l
 Exposure time: 72 h
 Test Type: static test
 Test substance: Fresh water
 Method: OECD Test Guideline 201

Components:

bisphenol F-epoxy resin:

M-Factor (Acute aquatic toxicity) : 1
 Toxicity to fish (Chronic toxicity) : No data available

Components:

Bisphenol A epoxy resin:

Toxicity to daphnia and other aquatic invertebrates (Chronic toxicity) : NOEC (Daphnia magna (Water flea)): 0.3 mg/l
 Exposure time: 21 d
 Test Type: semi-static test
 Test substance: Fresh water
 Method: OECD Test Guideline 211

bisphenol F-epoxy resin:

Toxicity to daphnia and other : NOEC (Daphnia magna (Water flea)): 0.3 mg/l

ARALDITE® AW 106

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	05/02/2017	400001010251	Date of first issue: 05/02/2017

aquatic invertebrates
(Chronic toxicity)

Exposure time: 21 d
Test Type: semi-static test
Test substance: Fresh water
Method: OECD Test Guideline 211

M-Factor (Chronic aquatic
toxicity)

: No data available

Components:

Bisphenol A epoxy resin:
Toxicity to microorganisms

: IC50 (activated sludge): > 100 mg/l
Exposure time: 3 h
Test Type: static test
Test substance: Fresh water

bisphenol F-epoxy resin:
Toxicity to microorganisms

: IC50 (activated sludge): > 100 mg/l
Exposure time: 3 h
Test Type: static test
Test substance: Fresh water

Toxicity to soil dwelling
organisms

: No data available

Plant toxicity

: No data available

Sediment toxicity

: No data available

Toxicity to terrestrial
organisms

: No data available

Ecotoxicology Assessment

Components:

bisphenol F-epoxy resin:
Acute aquatic toxicity

: This product has no known ecotoxicological effects.

Components:

bisphenol F-epoxy resin:
Chronic aquatic toxicity

: Toxic to aquatic life with long lasting effects.

Toxicity Data on Soil

: No data available

Other organisms relevant to
the environment

: No data available

Persistence and degradability**Components:**

Bisphenol A epoxy resin:
Biodegradability

: Inoculum: Sewage (STP effluent)
Concentration: 20 mg/l
Result: Not readily biodegradable.
Biodegradation: 5 %

ARALDITE® AW 106

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	05/02/2017	400001010251	Date of first issue: 05/02/2017

Exposure time: 28 d
Method: OECD Test Guideline 301F

bisphenol F-epoxy resin:
Biodegradability

: Inoculum: activated sludge
Concentration: 3 mg/l
Result: Not readily biodegradable.
Biodegradation: ca. 0 %
Exposure time: 28 d
Method: Directive 67/548/EEC Annex V, C.4.E.

bisphenol A - epoxy resins, number average MW >700 - <1100:

Biodegradability

: Inoculum: Sewage (STP effluent)
Concentration: 20 mg/l
Result: Not readily biodegradable.
Biodegradation: 5 %
Exposure time: 28 d
Method: OECD Test Guideline 301F

Biochemical Oxygen
Demand (BOD)

: No data available

Chemical Oxygen Demand
(COD)

: No data available

BOD/COD

: No data available

ThOD

: No data available

BOD/ThOD

: No data available

Dissolved organic carbon
(DOC)

: No data available

Physico-chemical
removability

: No data available

Components:

Bisphenol A epoxy resin:
Stability in water

: Degradation half life(DT50): 4.83 d (25 °C) pH: 4
Method: OECD Test Guideline 111
Remarks: Fresh water

Degradation half life(DT50): 7.1 d (25 °C) pH: 9
Method: OECD Test Guideline 111
Remarks: Fresh water

Degradation half life(DT50): 3.58 d (25 °C) pH: 7
Method: OECD Test Guideline 111
Remarks: Fresh water

bisphenol A - epoxy resins, number average MW >700 - <1100:

Stability in water

: Degradation half life(DT50): 4.83 d (25 °C) pH: 4
Method: OECD Test Guideline 111

ARALDITE® AW 106

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	05/02/2017	400001010251	Date of first issue: 05/02/2017

Remarks: Fresh water

Degradation half life(DT50): 7.1 d (25 °C) pH: 9
 Method: OECD Test Guideline 111
 Remarks: Fresh water

Degradation half life(DT50): 3.58 d (25 °C) pH: 7
 Method: OECD Test Guideline 111
 Remarks: Fresh water

Photodegradation : No data available

Impact on Sewage Treatment : No data available

Bioaccumulative potential**Components:**

Bisphenol A epoxy resin:
 Bioaccumulation : Bioconcentration factor (BCF): 31
 Remarks: Does not bioaccumulate.

bisphenol F-epoxy resin:
 Bioaccumulation : Species: Fish
 Bioconcentration factor (BCF): 150
 Remarks: Does not bioaccumulate.

bisphenol A - epoxy resins, number average MW >700 - <1100:
 Bioaccumulation : Species: Fish
 Bioconcentration factor (BCF): 31
 Remarks: Does not bioaccumulate.

Components:

Bisphenol A epoxy resin:
 Partition coefficient: n-octanol/water : log Pow: 3.242 (25 °C)
 pH: 7.1
 Method: OECD Test Guideline 117

bisphenol F-epoxy resin:
 Partition coefficient: n-octanol/water : log Pow: 2.7 - 3.6
 Method: OECD Test Guideline 117

Mobility in soil

Mobility : No data available

Components:

Bisphenol A epoxy resin:
 Distribution among environmental compartments : Koc: 445
 bisphenol F-epoxy resin:
 Distribution among environmental compartments : Koc: 4460 Method: OECD Test Guideline 121
 bisphenol A - epoxy resins, number average MW >700 - <1100:

ARALDITE® AW 106

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	05/02/2017	400001010251	Date of first issue: 05/02/2017

Distribution among environmental compartments : Koc: 445
Stability in soil : No data available

Other adverse effects

Environmental fate and pathways : No data available

Results of PBT and vPvB assessment : No data available

Endocrine disrupting potential : No data available

Adsorbed organic bound halogens (AOX) : No data available

Hazardous to the ozone layer

Ozone-Depletion Potential : Regulation: 40 CFR Protection of Environment; Part 82
Protection of Stratospheric Ozone - CAA Section 602 Class I Substances
Remarks: This product neither contains, nor was manufactured with a Class I or Class II ODS as defined by the U.S. Clean Air Act Section 602 (40 CFR 82, Subpt. A, App.A + B).

Additional ecological information - Product : An environmental hazard cannot be excluded in the event of unprofessional handling or disposal.
Toxic to aquatic life with long lasting effects.

Global warming potential (GWP) : No data available

SECTION 13. DISPOSAL CONSIDERATIONS**Disposal methods**

Waste from residues : The product should not be allowed to enter drains, water courses or the soil.
Do not contaminate ponds, waterways or ditches with chemical or used container.
Send to a licensed waste management company.

Contaminated packaging : Empty remaining contents.
Dispose of as unused product.
Do not re-use empty containers.

SECTION 14. TRANSPORT INFORMATION**International Regulations**

ARALDITE® AW 106

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	05/02/2017	400001010251	Date of first issue: 05/02/2017

IATA

UN/ID No.	: UN 3082
Proper shipping name	: Environmentally hazardous substance, liquid, n.o.s. (BISPHENOL A EPOXY RESIN, BISPHENOL F EPOXY RESIN)
Class	: 9
Packing group	: III
Labels	: Miscellaneous
Packing instruction (cargo aircraft)	: 964
Packing instruction (passenger aircraft)	: 964

IMDG

UN number	: UN 3082
Proper shipping name	: ENVIRONMENTALLY HAZARDOUS SUBSTANCE, LIQUID, N.O.S. (BISPHENOL A EPOXY RESIN, BISPHENOL F EPOXY RESIN)
Class	: 9
Packing group	: III
Labels	: 9
EmS Code	: F-A, S-F
Marine pollutant	: yes

Transport in bulk according to Annex II of MARPOL 73/78 and the IBC Code

Not applicable for product as supplied.

National Regulations**DOT Classification**

UN/ID/NA number	: UN 3082
Proper shipping name	: ENVIRONMENTALLY HAZARDOUS SUBSTANCE, LIQUID, N.O.S. (BISPHENOL A EPOXY RESIN, BISPHENOL F EPOXY RESIN)
Class	: 9
Packing group	: III
Labels	: CLASS 9
ERG Code	: 171
Marine pollutant	: yes(BISPHENOL A EPOXY RESIN, BISPHENOL F EPOXY RESIN)

SECTION 15. REGULATORY INFORMATION**EPCRA - Emergency Planning and Community Right-to-Know Act****SARA 311/312 Hazards** : No SARA Hazards

ARALDITE® AW 106

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	05/02/2017	400001010251	Date of first issue: 05/02/2017

SARA 313 : This material does not contain any chemical components with known CAS numbers that exceed the threshold (De Minimis) reporting levels established by SARA Title III, Section 313.

This product does not contain any hazardous air pollutants (HAP), as defined by the U.S. Clean Air Act Section 112 (40 CFR 61).

California Prop. 65

This product does not contain any chemicals known to State of California to cause cancer, birth defects, or any other reproductive harm.

The components of this product are reported in the following inventories:

CH INV	: The formulation contains substances listed on the Swiss Inventory, On the inventory, or in compliance with the inventory
DSL	: All components of this product are on the Canadian DSL
AICS	: On the inventory, or in compliance with the inventory
NZIoC	: On the inventory, or in compliance with the inventory
ENCS	: On the inventory, or in compliance with the inventory
KECI	: On the inventory, or in compliance with the inventory
PICCS	: On the inventory, or in compliance with the inventory
IECSC	: On the inventory, or in compliance with the inventory
TCSI	: On the inventory, or in compliance with the inventory
TSCA	: On the inventory, or in compliance with the inventory

Inventories

AICS (Australia), DSL (Canada), IECSC (China), REACH (European Union), ENCS (Japan), ISHL (Japan), KECI (Korea), NZIoC (New Zealand), PICCS (Philippines), TCSI (Taiwan), TSCA (USA)

TSCA - 5(a) Significant New Use Rule List of Chemicals


No substances are subject to a Significant New Use Rule.

US. Toxic Substances Control Act (TSCA) Section 12(b) Export Notification (40 CFR 707, Subpt D)

No substances are subject to TSCA 12(b) export notification requirements.

ARALDITE® AW 106

Version	Revision Date:	SDS Number:	Date of last issue: -
1.0	05/02/2017	400001010251	Date of first issue: 05/02/2017

SECTION 16. OTHER INFORMATION**Further information****NFPA:****HMIS® IV:**

HEALTH		2
FLAMMABILITY		1
PHYSICAL HAZARD		0

HMIS® ratings are based on a 0-4 rating scale, with 0 representing minimal hazards or risks, and 4 representing significant hazards or risks. The "*" represents a chronic hazard, while the "/" represents the absence of a chronic hazard.

Revision Date : 05/02/2017

The information and recommendations in this publication are to the best of our knowledge, information and belief accurate at the date of publication, NOTHING HEREIN IS TO BE CONSTRUED AS A WARRANTY, EXPRESS OR OTHERWISE.

IN ALL CASES, IT IS THE RESPONSIBILITY OF THE USER TO DETERMINE THE APPLICABILITY OF SUCH INFORMATION AND RECOMMENDATIONS AND THE SUITABILITY OF ANY PRODUCT FOR ITS OWN PARTICULAR PURPOSE.

THE PRODUCT MAY PRESENT HAZARDS AND SHOULD BE USED WITH CAUTION. WHILE CERTAIN HAZARDS ARE DESCRIBED IN THIS PUBLICATION, NO GUARANTEE IS MADE THAT THESE ARE THE ONLY HAZARDS THAT EXIST.

Hazards, toxicity and behaviour of the products may differ when used with other materials and are dependent upon the manufacturing circumstances or other processes. Such hazards, toxicity and behaviour should be determined by the user and made known to handlers, processors and end users.

The trademarks above are the property of Huntsman Corporation or an affiliate thereof.

NO PERSON OR ORGANIZATION EXCEPT A DULY AUTHORIZED HUNTSMAN EMPLOYEE IS AUTHORIZED TO PROVIDE OR MAKE AVAILABLE DATA SHEETS FOR HUNTSMAN PRODUCTS. DATA SHEETS FROM UNAUTHORIZED SOURCES MAY CONTAIN INFORMATION THAT IS NO LONGER CURRENT OR ACCURATE.