

N109 W13300 ELLSWORTH DRIVE GERMANTOWN, WI 53022
262-253-5900 FAX 262-253-5919

DESCRIPTION:

Resinlab[®] EP1195 is a low viscosity, fast gelling, flame retardant epoxy casting resin system. It is recognized under the Component Recognition Program of Underwriters Laboratories Inc., (File # E186034, Project 96NK25676) for UL Standard 94.

EP1195 Black qualifies for a horizontal burn rating of UL94HB at 1/16" thickness. It also gives excellent resistance to water, salt spray, and good resistance to most inorganic acids and bases and organic solvents.

EP1195 Black was formulated to a 2A:1B by volume mix ratio for use in side-by-side dispensing cartridges and meter/mix and dispense equipment. Cure is normally achieved at room temperature although an elevated temperature cure schedule can be used to reach final properties quickly after product has gelled. EP1195 is a general encapsulant designed for small to medium mass potting applications.

TYPICAL PROPERTIES:

All properties given are at 25 °C unless otherwise noted.

Property:	Value:	Test Method or Source:
Color	Black	Visual
Mix Ratio	Part A to Part B	Calculated
Mix Ratio by weight	2.8 to 1	
Mix Ratio by volume	2 to 1	
Cure Schedule	24 hrs @ 25 °C 1 hr @ 65 °C	
Viscosity - Part A	5,000 cP	Rheometer parallel plate 25mm @ 1/s
Viscosity - Part B	1,400 cP	455300006291
Viscosity - Mixed	2,800 cP	
Specific Gravity - Part A	1.37	Calculated
Specific Gravity - Part B	0.97	
Specific Gravity - Mixed	1.24	
Pot Life defined as the time it takes for initial mixed viscosity to double	10 minutes	Rheometer parallel plate 25mm @1/s 455300006291
Hardness	85 Shore D	455300006287/ASTM D2240
Glass Transition Temperature/Tg	42 °C	453560822409 by DSC
Water Absorption	0.18 %	24 hr immersion 457561824543/ASTM D570
Tensile Properties:		4535601224470/ASTM D638
Strength	5,400 psi	
Elongation	1.2 %	
Modulus	450,000 psi	
Lap Shear Strength		4535601224468/ASTM D1002
0.010" Bond Line, Al to Al	3,000 psi	

N109 W13300 ELLSWORTH DRIVE GERMANTOWN, WI 53022
262-253-5900 FAX 262-253-5919

Property:	Value:	Test Method or Source:
Compressive Properties:		4535601224467/ASTM D695
Ultimate Strength	23,500 psi	
Modulus	116,000 psi	
Flame Resistance UL Certified, File #E186034	Passes with HB Rating @ 1/16"	45376013225560/UL94HB
Thermal Conductivity by LFA	0.3 W/m.K	453560822409/ASTM E1461
Electrical Resistivity:		455300006612/ASTM D257
Volume	6.5×10^{15} ohm-cm	@ 18 °C @ 22 %RH
Surface	5.2×10^{16} ohm/sq	
Dielectric Constant & Dissipation Factor:		455300006513/ASTM D150
@ 100 Hz	3.4, 0.01	
@ 100 kHz	3.2, 0.01	
AC Dielectric Strength	440 V/mil *	DCV6101609; ASTM D149 Method A, immersed in ASTM D3487 Type II Oil
Coefficient of Thermal Expansion by TMA:		455300005340/ASTM E831 TMA, 5 °C/min
below Tg	55 ppm/°C	
above Tg	190 ppm/°C	
Operating Temperature Range	-40 to 150 °C**	
Relative Thermal Index (RTI)	90 °C	UL746B, Table 7.1 Generic Value Based on Composition

* Asterisk denotes values considered typical to associated resin systems or extrapolated from other test results.

** Operating Temperature Range is based on average design requirements and is not intended as a guarantee of suitability for all applications operating at that temperature.

*** This TDS contains values that have been updated. The values reported in this technical data sheet are typical values of the product, and are highly dependent on test conditions and methodology. We actively seek the most precise and accurate ways to measure and interpret performance of our products, and to update estimated values with measured values. The formula has not been revised or changed in any way. Although the values on paper have changed, you can expect the same performance of the product.

N109 W13300 ELLSWORTH DRIVE GERMANTOWN, WI 53022
262-253-5900 FAX 262-253-5919

INSTRUCTIONS:

1. Bring to room temperature prior to use.
2. Cartridge format: Mixer should be attached keeping the cartridge vertical and any air pocket purged this way. After the mixer contains material, the mixer tip can be dropped to dispense pre-bleed amount. Attach a new static mixer with each cartridge, then pre-bleed the first 3 inches of dispensed material or until a uniform color is obtained. Maintain adequate velocity during dispensing to ensure complete mixing.
3. Bulk format: stir until homogeneous weigh and mix parts A and B accurately and thoroughly, scraping sides of container often. Do not pour from mixing container, transfer to a new container as residual unmixed material may cause a tacky spot on the surface of the casting. Maintain adequate velocity during dispensing to ensure complete mixing.
4. Clean up uncured resin with suitable organic solvent such as MEK or acetone.
5. Allow to cure undisturbed until product is fully gelled or tack-free to the touch.

SHELF LIFE AND STORAGE:

6 months at 5 °C or less.
3 months at 25 °C.
Specialty packaging may be less.

Many epoxy resin systems are prone to crystallization as epoxy resin is a super-cooled fluid. This condition may give the product a gritty or grainy appearance (or hazy in clear products). Products in this state will not usually cure to normal and expected properties. In extreme cases it may appear solid and cured. Fluctuating temperatures (within 5 to 50 °C) aggravate this phenomenon. Heating the individual component to 50 to 60 °C while stirring can usually restore products to original state. Storage at 25 +/- 10 °C is optimum for most products.