

N109 W13300 ELLSWORTH DRIVE GERMANTOWN, WI 53022
262-253-5900 FAX 262-253-5919

DESCRIPTION:

Resinlab® EP1238 Black is a two part acrylic/epoxy hybrid adhesive designed for bonding metals and plastics. It cures quickly at room temperature to a tough, semi-rigid material. It has good wetting to most surfaces and has controlled flow characteristics to prevent excessive running or dripping. This product has good vibration and impact resistance. It has good resistance to water, salt spray, inorganic acids and bases and most organic solvents.

EP1238 Black was formulated to a 2A:1B volume mix ratio for use in side-by-side dispensing cartridges and meter/mix and dispense equipment. It will reach handle cure at room temperature within 6 – 12 hours. Cure time can be accelerated by the application of heat. Times and temperatures from 2 hours at 65 °C to 30 minutes at 100 °C are typical for most applications. Time to heat substrate must be taken into account. Cooler temperatures will also extend work time and increase cure times.

TYPICAL PROPERTIES:

All properties given are at 25 °C unless otherwise noted.

Property:	Value:	Test Method or Source:
Color	Black	Visual
Mix Ratio	Part A to Part B	Calculated
Mix Ratio by weight	2.12 to 1	
Mix Ratio by volume	2 to 1	
Cure Schedule	6-12 hours @ 25 °C 2 hrs @ 65 °C 30 min @ 100 °C	
Viscosity - Part A	44,000 cP	TA HR20 Rheometer 25mm parallel plate @
Viscosity - Part B	50,000 cP	1/s DCV6100723
Viscosity - Mixed	47,000 cP *estimated	
Specific Gravity - Part A	1.16	Calculated
Specific Gravity - Part B	1.07	
Specific Gravity - Mixed	1.13	
Pot Life defined as the time it takes for initial mixed viscosity to double	12 minutes	TA HR20 Rheometer parallel plate 25mm @ 1/s DCV6100723
Hardness	80 Shore D	455300006287/ASTM D2240
Glass Transition Temperature/Tg	60 °C	453560822409 by DSC
Water Absorption	0.25 %	24 hr immersion 457561824543/ASTM D570
Tensile Properties:		4535601224470/ASTM D638
Strength	8,500 psi	
Elongation	3 – 4 %	
Modulus	450,000 psi	
T-Peel Strength	25 pli *estimated	455300005588/ASTM D1876

N109 W13300 ELLSWORTH DRIVE GERMANTOWN, WI 53022
262-253-5900 FAX 262-253-5919

Property:	Value:	Test Method or Source:
Compressive Properties:		4535601224467/ASTM D695
Yield Strength	12,000 psi	
Ultimate Strength	16,000 psi	
Modulus	350,000 psi	
Thermal Conductivity by Transient Plane Heat Source (TPS)	< 0.2 W/m.K *estimated	Thermtest TPS Hot Disk ISO 22007-2 45376013225604
Electrical Resistivity:		455300006612/ASTM D257 @ 19 °C @ 18 %RH
Volume	2.1 x 10 ¹⁶ ohm-cm	
Surface	3.4 x 10 ¹⁵ ohm/sq	
Dielectric Constant & Dissipation Factor:		455300006513/ASTM D150
@ 100 Hz	3.9, 0.01	
@ 100 kHz	3.6, 0.03	
AC Dielectric Strength	17 kV/mm *estimated	DCV6101609; ASTM D149 Method A, immersed in ASTM D3487 Type II Oil
Coefficient of Thermal Expansion by TMA:		455300005340/ASTM E831 TMA, 5 °C/min
below Tg	64 ppm/°C	
above Tg	207 ppm/°C	
Operating Temperature Range	-55 to 150 °C**	
Relative Thermal Index (RTI)	90 °C	UL746B, Table 7.1 Generic Value Based on Composition

* Asterisk denotes values considered typical to associated resin systems or extrapolated from other test results.

** Operating Temperature Range is based on average design requirements and is not intended as a guarantee of suitability for all applications operating at that temperature.

*** This TDS contains values that have been updated. The values reported in this technical data sheet are typical values of the product, and are highly dependent on test conditions and methodology. We actively seek the most precise and accurate ways to measure and interpret performance of our products, and to update estimated values with measured values. The formula has not been revised or changed in any way. Although the values on paper have changed, you can expect the same performance of the product.

Additional Performance Data – Lap Shear Adhesion, 455300005642/ASTM D1002:

Substrate Type	Strength	Test Temperature	Bond Line Thickness
Al to Al	4,600 psi *	25 °C	0.010 "
PVC to PVC	280 psi *	25 °C	0.010 "
PC to PC	700 psi *	25 °C	0.010 "
Acrylic to Acrylic	490 psi *	25 °C	0.010 "
ABS to ABS	520 psi *	25 °C	0.010 "

* Extrapolated data source: EP1238

N109 W13300 ELLSWORTH DRIVE GERMANTOWN, WI 53022
262-253-5900 FAX 262-253-5919

INSTRUCTIONS:

1. Bring to room temperature prior to use.
2. Cartridge format: Mixer should be attached keeping the cartridge vertical and any air pocket purged this way. After the mixer contains material, the mixer tip can be dropped to dispense pre-bleed amount. Attach a new static mixer with each cartridge, then pre-bleed the first 3 inches of dispensed material or until a uniform color is obtained. Maintain adequate velocity during dispensing to ensure complete mixing.
3. Bulk format: stir until homogeneous weigh and mix parts A and B accurately and thoroughly, scraping sides of container often. Do not pour from mixing container, transfer to a new container as residual unmixed material may cause a tacky spot on the surface of the casting. Maintain adequate velocity during dispensing to ensure complete mixing.
4. Clean up uncured resin with suitable organic solvent such as MEK or acetone.
5. Allow to cure undisturbed until product is fully gelled or tack-free to the touch.

SHELF LIFE AND STORAGE:

12 months at 25 °C.
Specialty packaging may be less.

Many epoxy resin systems are prone to crystallization as epoxy resin is a super-cooled fluid. This condition may give the product a gritty or grainy appearance (or hazy in clear products). Products in this state will not usually cure to normal and expected properties. In extreme cases it may appear solid and cured. Fluctuating temperatures (within 5 to 50 °C) aggravate this phenomenon. Heating the individual component to 50 to 60 °C while stirring can usually restore products to original state. Storage at 25 +/- 10 °C is optimum for most products.