



# Prep G

## Product

Simson Prep G has been developed as a black pretreatment for use on glass, not having a ceramic coating, in order to provide a UV-protecting coat, before applying special adhesives for bonding glass (also PMMA and PC) in the automotive, bus, ship and railway industries.

## Applications

- Pretreatment of glass substrates without ceramic coating.
- Repair of damaged paint layers on metallic supports.

## Method of use

The substrate should be clean, firm, dry and dust- and grease free. Cleaning of the substrates can be done with e.g. Simson Cleaner 14 or Simson Cleaner I. A small trial before application whether the cleaners will not attack the substrate is recommended. Keep the packaging of Prep G well closed until the moment of use. Prep G reacts with the humidity of the air. Shake bottle before use. Do not re-use a previously opened bottle. For the application of Prep G always use a clean brush, roller or felt applicator. The primer should be applied in one strike. Application temperature between +5°C and +30°C. Do not use when condensation is formed (high air humidity and cold substrates). Prep G should dry for at least 5 minutes. Apply the adhesive within 24 hours.

## ADHESIVES AND SEALANTS

# Prep G

### Technical data

Total solids	ca. 22%	
Density	ca. 0.99 g/ml	
Dry time	> 5 minutes	(20°C/50% R.H.)
Flash point	-1°C	
Appearance	smooth black liquid	

Colour	Packaging	Article code
black	tin 30 ml	023510
black	tin 500 ml	023511
black	tin 1 l	023512

### Coverage

The coverage of Simson Prep G is approximately 10 m<sup>2</sup> per litre.

### Storage stability

Prep G can be stored for 9 months in a closed (unopened) container in a dry place at temperatures between +5°C and +30°C.

### Further information

The following publication is available on request:

- Material Safety Data Sheets (MSDS)

#### Bostik B.V.

Postbus 303  
5201 AH 's-Hertogenbosch  
Tel: +31 (0)73 6 244 244  
Fax: +31 (0)73 6 244 344  
E-mail: [infonl@bostik.com](mailto:infonl@bostik.com)  
Internet: [www.bostik.nl](http://www.bostik.nl)

#### Bostik Belux SA-NV

Meulestedekaai 86  
B-9000 Gent  
Tel: +32 (0)9 255 17 00  
Fax: +32 (0)9 255 17 01  
E-mail: [info@bostik.be](mailto:info@bostik.be)  
Internet: [www.bostik.be](http://www.bostik.be)