

HumiSeal[®] 1C53 Silicone Conformal Coating

Technical Data Sheet

HumiSeal[®] 1C53 is a single component, VOC-free, fast thermal curing silicone conformal coating. The low viscosity and long pot life of HumiSeal[®] 1C53 make it ideal for dipping and spraying. HumiSeal[®] 1C53 demonstrates excellent flexibility and contains an optical brightener for inspection under black light. HumiSeal[®] 1C53 coating is MIL-I-46058C qualified, IPC-CC-830 and RoHS Directive 2011/65/EU compliant and recognized under UL File Number E105698.

Properties of HumiSeal[®] 1C53

Density, per ASTM D1475	0.99 ± 0.01 g/cm ³
Min Solids Content, % by weight per Fed-Std-141, Meth. 4044	98 %
Viscosity, per Fed-Std-141, Meth. 4287	590 ± 100 centipoise
VOC	0 grams/litre
Recommended Coating Thickness	50 - 200 microns
Recommended Curing Conditions	10 - 15 min @ 105 - 130°C
Time Required to Reach Optimum Properties	15 minutes
Recommended Stripper	HumiSeal [®] Stripper 1091
Shelf Life at Recommended Conditions, DOM	12 months
Thermal Shock, 50 cycles per MIL-I-46058C	-65°C to 200°C
Coefficient of Thermal Expansion - TMA	154 ppm/°C
Glass Transition Temperature - DSC	< -65°C
Modulus - DMA	3.5 MPa
Flammability, per UL 94	V-0
Dielectric Withstand Voltage, per MIL-I-46058C	>1500 volts
Dielectric Breakdown Voltage, per ASTM D149	7000 volts
Dielectric Constant, at 1MHz and 25°C per ASTM D150-98	2.4
Dissipation Factor, at 1MHz and 25°C per ASTM D150-98	0.01
Insulation Resistance, per MIL-I-46058C	5.0 x 10 ¹⁴ ohms (500TΩ)
Moisture Insulation Resistance, per MIL-I-46058C	1.0 x 10 ¹⁰ ohms (10GΩ)
Fungus Resistance, per ASTM G21	Passes

Application of HumiSeal[®] 1C53

Conformal coatings can be successfully applied to substrates that have been cleaned prior to coating and also to substrates assembled with low residue, "no clean" materials. Users should perform adequate testing to confirm compatibility between the conformal coating and their particular assembly materials, process conditions and cleanliness level. Please contact HumiSeal for additional information.

Dipping

A controlled rate of immersion and withdrawal (5-15 cm/min) will ensure even deposition of the coating and ultimately a uniform film.

Spraying

HumiSeal[®] 1C53 can be sprayed using conventional spraying equipment. Spray pressure will depend on the specific type of spraying equipment used and operator technique. Spraying should be done in an environment with adequate ventilation so that the vapour and mist are carried away from the operator. The use of thinner is not required or recommended for HumiSeal[®] 1C53.

HumiSeal[®] 1C53 Technical Data Sheet

Brushing

HumiSeal[®] 1C53 may be brushed. Uniformity of the film depends on component density and operator's technique.

Curing

HumiSeal[®] 1C53 is a thermally cured conformal coating. The actual curing temperature of HumiSeal[®] 1C53 is dependent upon several parameters, such as heat sink characteristics of parts being coated, the type of oven used for curing process, as well as oven loading parameters.

The cure mechanism for thermally cured silicones like HumiSeal[®] 1C53 may be inhibited by a variety of materials i.e.; amines, acrylates, certain ingredients from latex rubber, etc. It is recommended that process and material compatibility be considered when incorporating HumiSeal[®] 1C53 into the production environment. Cotton gloves are recommended for operators who will be handling assemblies prior to coating with HumiSeal[®] 1C53.

Storage

HumiSeal[®] 1C53 should be stored at 27°C or below in tightly closed containers away from direct sunlight. Refrigerated storage of HumiSeal[®] 1C53 will extend its shelf life. Prior to use, allow the product to equilibrate for 24 hours at room temperature.

Caution

Application of HumiSeal[®] Conformal Coatings should be carried out in accordance with local and National Health and Safety regulations.

Use only in well-ventilated areas to avoid inhalation of vapours or spray. Avoid contact with skin and eyes.

Consult SDS prior to use.

Contact HumiSeal[®]

HumiSeal North America

201 Zeta Drive
Pittsburgh, PA 15238
USA
Tel: +1 412-828-1500
Toll Free (US only): 866-828-5470
sales@humiseal.com

HumiSeal Technical Center

295 University Avenue
Westwood, MA 02090
USA
Tel: +1 781-332-0734
Fax: +1 781-332-0703
techsupport@humiseal.com

HumiSeal Europe

505 Eskdale Road, IQ Winnersh
Berkshire RG41 5TU
UK
Tel: +44 (0)1189 442 333
Fax: +44 (0)1189 335 799
europesales@chasecorp.com

HumiSeal India

J-154, M.I.D.C Bhosari
Pune 411 026
Maharashtra
India
Tel: +91 20 66308098
indiatechsupport@chasecorp.com

HumiSeal S.A.R.L

4/6 Avenue Eiffel
78420 Carrieres-Sur-Seine
France
Tel: +33 (0) 1 30 09 86 86
Fax: +33 (0) 1 30 09 86 87
humiseal.sarl@chasecorp.com

HumiSeal Asian Support

Tel: 852-9451-6434
Fax: 852-2413-6289
asiatechsupport@humiseal.com

HumiSeal Europe Support

Tel: +44 (0)1189 442 333
Fax: +44 (0)1189 335 799
europetechsupport@chasecorp.com

The information contained here is provided for product selection purposes only and is not to be considered specification or performance data. Under no circumstance will the seller be liable for any loss, damage, expense or incidental or consequential damage of any kind arising in connection with the use or inability to use its product. Specific conditions of sale and Chase's limited warranty are set out in detail in Chase Corporation Terms and Conditions of Sale. Those Terms and Conditions are the only source that contain Chase's limited warranty and other terms and conditions.