



PRODUCT NAME: HM6363

MSDS NAME: THERMOGRIP HM6363

DESCRIPTION: Hot Melt Adhesive/Glue Stick or Pellet

SUGGESTED USES: General Assembly and Automotive Applications

CHARACTERISTICS: Medium open time with good bonding characteristics to a wide range of materials.

TECHNICAL PROPERTIES:

Thermosel Viscosity
(Brookfield - ASTM D3236)


Softening Point - N/A

Approximately
8875 cPs @ 400 °F (204.4 °C)
14250 cPs @ 375 °F (190.6 °C)
20250 cPs @ 350 °F (176.7 °C)
33500 cPs @ 325 °F (162.8 °C)

Suggested Running Temperature: 350 - 400 °F (176.7 - 204.4 °C)

Density
0.96 g/cc @ 77

Typical Viscosity Curve



For performance test characteristics please contact your Bostik sales or technical representative.

STORAGE:

Can be stored 730 days in a clean dry place, in its original package at an average temperature of 25°C or below. Storage temperature should not exceed 40°C.

PACKAGING:

For packaging options please call your Bostik sales or technical representative.

SAFETY AND HANDLING:

Clean-up Procedure: Mineral oil or paraffin wax, not to exceed flash point as stated on the MSDS, followed by a thorough purge with the adhesive itself.

Material Safety Data Sheet should be consulted for proper handling before use.

Wear safety gloves and goggles when handling molten adhesive to minimize the risk of burns.

Keep containers covered to minimize contamination.

Print Date 14-AUG-2009

The information given and recommendations made herein are based on Bostik's research only and are not guaranteed to be accurate. The performance of the product, its shelf life, and application characteristics will depend on many variables, including the kind of materials to which the product will be applied, the environment in which the product is stored or applied, and equipment used for application. Any change in any of these variables can affect the product's performance. Buyers are advised to make their own tests to determine whether the product is suitable for their purposes under their own operating conditions. Bostik accepts no responsibility for the performance of the product for any particular customer or any particular use. Bostik does not warrant the product's suitability for any particular application. The product is sold only pursuant to Bostik's terms and conditions of sale and only subject to the limited warranty contained therein.

BOSTIK SELLS THE PRODUCT WITHOUT WARRANTY AS TO MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, ANY WARRANTY FROM COURSE OF DEALING OR USAGE OF TRADE, OR ANY OTHER WARRANTY, EXPRESSED OR IMPLIED, AND BUYERS AND USERS ASSUME ALL RESPONSIBILITY AND LIABILITY FOR LOSS OR DAMAGE ARISING FROM THE HANDLING AND USE OF BOSTIK'S PRODUCTS. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent. Unless otherwise agreed to in writing, THE BUYER'S SOLE REMEDY FOR NONCOMPLIANCE WITH ANY WARRANTY SHALL BE THE REPLACEMENT OF THE PRODUCT OR REFUND OF THE BUYER'S PURCHASE PRICE. IN NO CASE WILL BOSTIK BE LIABLE FOR INDIRECT, CONSEQUENTIAL, INCIDENTAL, ECONOMIC OR OTHER SIMILAR DAMAGES.

Bostik, Inc. 11320 Watertown Plank Road
Telephone: 414-774-2250

Wauwatosa, WI 53226-3434
Fax: 414-774-8075