



H2016I01

HOT MELT PRESSURE SENSITIVE ADHESIVE

DESCRIPTION

H2016I01 is a very tacky and low viscosity hot melt pressure sensitive ideal for flying insect trap applications.

PACKAGING

For packaging options, please call your Bostik sales or technical representative.

COUNTRY OF MANUFACTURE

United States

HEALTH & SAFETY PRECAUTIONS

The Safety Data Sheet should be consulted for proper handling, clean up and spill containment before use. Keep containers covered to minimize contamination.

TYPICAL PHYSICAL PROPERTIES

Description	Results
Thermosel Viscosity (Brookfield - ASTM D3236)	10000 cP @ 200°F 2250 cP @ 225°F 775 cP @ 250°F 450 cP @ 275°F
Density	0.94 g/cc @ 77°F
Softening Point (Ring and Ball Herzog - ASTM E28)	155°F
Suggested Running Temperature	200 - 250°F

LIMITED WARRANTY

The Limited Warranty for this product can be found at www.Bostik-US.com/resource-center/warranties or by calling 1-800-726-7845 (choose option 2, then option 2 again). TO THE MAXIMUM EXTENT ALLOWED BY LAW, BOSTIK DISCLAIMS ALL OTHER EXPRESS OR IMPLIED WARRANTIES, INCLUDING WITHOUT LIMITATION WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. UNLESS OTHERWISE STATED IN THE LIMITED WARRANTY, THE SOLE REMEDY FOR BREACH OF WARRANTY IS REPLACEMENT OF THE PRODUCT OR REFUND OF THE BUYER'S PURCHASE PRICE. BOSTIK DISCLAIMS ANY LIABILITY FOR DIRECT, INCIDENTAL, CONSEQUENTIAL, OR SPECIAL DAMAGES TO THE MAXIMUM EXTENT ALLOWED BY LAW. DISCLAIMERS OF IMPLIED WARRANTIES MAY NOT BE APPLICABLE TO CERTAIN CLASSES OF BUYERS AND SOME STATES DO NOT ALLOW THE EXCLUSION OR LIMITATION OF INCIDENTAL OR CONSEQUENTIAL DAMAGES, SO THE ABOVE LIMITATIONS MAY NOT APPLY TO YOU. It is the buyer's obligation to test the suitability of the product for an intended use prior to using it. The Limited Warranty extends only to the original purchaser and is not transferable or assignable. Any claim for a defective product must be filed within 30 days of discovery of a problem, and must be submitted with written proof of purchase.

BOSTIK HOTLINE

Smart help
1-800-726-7845

Bostik, Inc.
11320 W. Watertown Plank Road
Wauwatosa, WI 53226
www.bostik-us.com



This document supersedes all previously published literature.
07.07.2015