

LOCTITE EA 9394 AERO

Epoxy Paste Adhesive

(KNOWN AS Hysol EA 9394)

INTRODUCTION

LOCTITE EA 9394 AERO is a two-part structural paste adhesive, which cures at room temperature and possesses excellent strength to 350°F/177°C and higher. Its thixotropic nature and excellent high temperature compressive strength also make it ideal for potting, filling and liquid shim applications. LOCTITE EA 9394 AERO is qualified to MMM-A-132 Rev B, Type I, Class 3, Form 3, Group 1.

The mechanical properties in this data sheet are also valid for LOCTITE EA 9394S AERO. LOCTITE EA 9394S AERO is only available in Semkits and differs from LOCTITE EA 9394 AERO as it has 1 part less thixotrope in the Part B to aid packaging. All other mechanical and handling properties similar.

FEATURES

- Room Temperature Cure
- Good Gap Filling Capabilities
- 350°F/177°C Performance
- Potting Material
- Room Temperature Storage
- Outstanding Mechanical Properties
- Long Pot Life
- Low Toxicity

Uncured Properties

	<u>Part A</u>	<u>Part B</u>	<u>Mixed</u>
Color	Gray	Black	Gray
Viscosity, 77°F Brookfield, HBT	4000-8000 Poise Spdl 7 @ 20 rpm	200-700 Poise Spdl 4 @ 20 rpm	1600 Poise Spdl 5 @ 20 rpm
Viscosity, 25°C Brookfield, HBT	400-800 Pa·S Spdl 7 @ 2.09 rad/sec	20-70 Pa·S Spdl 4 @ 2.09 rad/sec	160 Pa·S Spdl 5 @ 2.09 rad/sec
Density (g/ml)	1.50	1.00	1.36
Shelf Life @ <77°F/25°C	1 year	1 year	

This material will normally be shipped at ambient conditions, which will not alter our standard warranty, provided that the material is placed into its intended storage upon receipt. Premium shipment is available upon request.

LOCTITE EA 9394 AERO

Epoxy Paste Adhesive

(KNOWN AS Hysol EA 9394)

Handling

Mixing - This product requires mixing two components together just prior to application to the parts to be bonded. Complete mixing is necessary. The temperature of the separate components prior to mixing is not critical, but should be close to room temperature (77°F/25°C).

<u>Mix Ratio</u>	<u>Part A</u>	<u>Part B</u>
By Weight	100	17

Note: Volume measurement is not recommended for structural applications unless special precautions are taken to assure proper ratios.

Pot Life (450 gram mass) 90 minutes @ 75°F/25°C
Method - ASTM D 2471 in water bath.

Application

Mixing - Combine Part A and Part B in the correct ratio and mix thoroughly. THIS IS IMPORTANT! Heat buildup during or after mixing is normal. Do not mix quantities greater than 450 grams as dangerous heat buildup can occur causing uncontrolled decomposition of the mixed adhesive. TOXIC FUMES CAN OCCUR, RESULTING IN PERSONAL INJURY. Mixing smaller quantities will minimize the heat buildup.

Applying - Bonding surfaces should be clean, dry and properly prepared. For optimum surface preparation consult the LOCTITE Surface Preparation Guide. The bonded parts should be held in contact until the adhesive is set. Handling strength for this adhesive will occur in 24 hours @ 77°F/25°C, after which the support tooling or pressure used during cure may be removed. Since full bond strength has not yet been attained, load application should be small at this time.

Dual Cartridge Application

We recommend that you do not precondition the kits, dispense adhesive at ambient temperature. If pre-heating is required for the cartridge kits, do not exceed 90°F for a maximum time of four hours.

- Do not assemble the static mixer onto the cartridge while conditioning.
 - Do not place the assembled cartridges upright in the oven.
 - Seat kit into the cartridge sleeve/tray and ensure proper placement against the gun plungers.
Misalignment during triggering of the plungers can result in kit damage.
 - Burp the adhesive at **low pressure** prior to dispensing through the static mixer.
 - Allows for both Piston, A & B sides to be equally level during initial dispensing, thus preventing an adhesive backflow.
 - It's possible that the Piston-B Side may be unlevelled with the Piston-A side due to the heating & positioning of the cartridge. The Part B resin viscosity is much lower than the Part A resin viscosity 200 ml kit failures will occur if the inlet pressure is set too high while triggering the plungers.
 - Start the plungers at **low pressure (20 psi)** then increase to the desired pressure
 - Over heating of the cartridge in an oven and then applying high pressure can result in **kit damage and/or resin blowback.**
-

LOCTITE EA 9394 AERO

Epoxy Paste Adhesive

(KNOWN AS Hysol EA 9394)

- Do not allow the adhesive to sit in the static mixer unattended for more than 90 minutes.
 - The material is curing within the static mixer and when pressure is re-applied back onto the plungers, back pressure will occur and potentially result in cartridge failure.

Failure to follow the recommended procedures stated in this TDS will void the Warranty of the Adhesive.

Note: Special precautions are recommended to minimize carbonate formation in large assemblies subject to extended open times in humid environments. A special memo is available upon request from Henkel providing users with suggestions for minimizing carbonate formation.

Curing - LOCTITE EA 9394 AERO may be cured for 3 to 5 days @ 77°F/25°C to achieve normal performance. Accelerated cures up to 200°F/93°C (for small masses only) may be used as an alternative. For example, 1 hour @ 150°F/66°C will give complete cure.

Cleanup - It is important to remove excess adhesive from the work area and application equipment before it hardens. Denatured alcohol and many common industrial solvents are suitable for removing uncured adhesive. Consult your supplier's information pertaining to the safe and proper use of solvents.

Bond Strength Performance

Tensile Lap Shear Strength - tested per ASTM D1002 after curing for 5 days @ 77°F/25°C. Adherends are 2024-T3 bare aluminum treated with phosphoric acid anodized per ASTM D3933.

<u>Test Temperature, °F/°C</u>	<u>Typical Results</u>	
	<u>psi</u>	<u>MPa</u>
-67/-55	3,300	22.7
77/ 25	4,200	28.9
180/82	3,000	20.7
200/93	2,900	20.0
250/121	2,300	15.8
300/149	1,600	11.0
350/177	1,200	8.3
400/204	600	4.1

LOCTITE EA 9394 AERO

Epoxy Paste Adhesive

(KNOWN AS Hysol EA 9394)

After Exposure to/Test Temperature**Typical Results**

	<u>psi</u>	<u>MPa</u>
Room Temperature Control (no exposure)	4,300	29.6
77°F/25°C Water - 7 days @77°F/25°C	4,100	28.2
Isopropyl Alcohol - 7 days @77°F/25°C	4,000	27.6
Hydraulic Oil - 7 days @77°F/25°C	4,100	28.2
JP-4 Fuel - 7 days @ 77°F/25°C	4,200	28.9

Peel Strength

T-Peel strength tested per ASTM D1876 after curing for 5 days @ 77°F/25°C. Adherends are 2024-T3 AlClad aluminum treated with phosphoric acid anodized per ASTM D3933.

<u>Test Temperature, °F/°C</u>	Typical Results	
	<u>Lb/in</u>	<u>N/2 mm</u>
77/25	5	22

Bell Peel strength tested per ASTM D3167 after curing for 7 days @ 77°F/25°C. Adherends are 2024-T3 AlClad aluminum treated with phosphoric acid anodized per ASTM D3933.

<u>Test Temperature, °F/°C</u>	Typical Results	
	<u>Lb/in</u>	<u>N/25mm</u>
77/25	20	89

Service Temperature

Service temperature is defined as that temperature at which this adhesive still retains 1000 psi/6.9 MPa) using test method ASTM D1002 and is 350°F/177°C.

Bulk Resin Properties

Tensile Properties - tested using 0.125 inch/ 3.18 mm castings per ASTM D638.

Tensile Strength @ 77°F/25°C	6,675 psi	46.0 MPa
Tensile Modulus @ 77°F/25°C	615 ksi	4,237 MPa
Shear Modulus, dry @ 77°F/25°C	212 ksi	1,461 MPa
Shear Modulus, wet @ 77°F/25°C	149 ksi	1,027 MPa
Elongation at Break @77°F/25°C	1.66%	
Shore D Hardness, @ 77°F/25°C	88	
Tg dry	172°F	78°C
Tg wet	154°F	68°C

LOCTITE EA 9394 AERO

Epoxy Paste Adhesive

(KNOWN AS Hysol EA 9394)

Compressive Properties - tested with rectangular specimens 0.5 in/12.7 mm width by 1.0 in/25.4 mm length by 0.5 in/12.7 mm height per ASTM D695.

<u>Compressive Strength, °F/°C</u>	<u>psi</u>	<u>MPa</u>
77/25	10,000	68.9

Electrical Properties - tested per ASTM D149, D150.

	<u>0.1 KHz</u>	<u>1.0 KHz</u>	<u>10.0 KHz</u>
Dielectric Constant	7.72	7.51	7.20
Dissipation Factor	.017	.022	.033
Thermal Conductivity	7.92 x 10 ⁻⁴ cal/sec-cm-°C		[0.331 W/(m•K)]
Volume Resistivity	4.05 x 10 ¹³ ohm-cm		[4.05 x 10 ¹¹ ohm]
Surface Resistivity	4.60 x 10 ¹³ ohm		
Coefficient of Thermal Expansion	55.6µm/m°C @ 40°C		
	80.6µm/m°C @ 100°C		

Handling Precautions

Do not handle or use until the Material Safety Data Sheet has been read and understood.
For industrial use only.

DISPOSAL INFORMATION

Dispose of spent remover and paint residue per local, state and regional regulations. Refer to HENKEL TECHNOLOGIES MATERIAL SAFETY DATA SHEET for additional disposal information.

PRECAUTIONARY INFORMATION

General:

As with most epoxy based systems, use this product with adequate ventilation. Do not get in eyes or on skin. Avoid breathing the vapors. Wash thoroughly with soap and water after handling. Empty containers retain product residue and vapors so obey all precautions when handling empty containers.



LOCTITE EA 9394 AERO Epoxy Paste Adhesive (KNOWN AS Hysol EA 9394)

PART A

CAUTION! This material may cause eye and skin irritation or allergic dermatitis. It contains epoxy resins.

PART B

WARNING! This material causes eye and skin irritation or allergic dermatitis. It contains amines.

Before using this product refer to container label and HENKEL TECHNOLOGIES MATERIAL SAFETY DATA SHEET for additional precautionary, handling and first aid information.

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Rev. 7/2015

Henkel Corporation Aerospace | 2850 Willow Pass Road | Bay Point, CA 94565
PHONE: +1.925.458.8000 | FAX: +1.925.458.8030 | www.henkel.com/aerospace

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

