

LOCTITE STYCAST ES 1901

September 2012

PRODUCT DESCRIPTION

LOCTITE STYCAST ES 1901 provides the following product characteristics:

Technology	Epoxy
Appearance (cured)	clear
Components	Two component - requires mixing
Mix Ratio, by volume - Part A: Part B	1 : 1
Mixing Ratio, by weight Component A: Component B	100 : 105
Cure	Room temperature cure
Application	Potting and Encapsulating

LOCTITE STYCAST ES 1901 is a fast-setting, toughened, medium-viscosity, industrial grade epoxy adhesive. Once mixed, the two-component epoxy cures at room temperature with low shrinkage and forms an ultra clear bondline with excellent peel resistance. When fully cured, the epoxy is resistant to a wide range of chemicals and solvents, and acts as an excellent electrical insulator. LOCTITE STYCAST ES 1901 is ideal for bonding plastic, metal, glass, wood, ceramic, rubber, and masonry materials where flexibility is needed. Designed for a variety of applications such as flex circuits, cable boots, and staking fillet bonds. This material is well suited for applications that require an ultraclear bondline.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Part A Properties

Specific Gravity @ 25°C	1.1
Viscosity @ °C, cps	1,900
Flash Point, °C	>93

Part B Properties

Specific Gravity @ 25°C	1.15
Viscosity @ °C, cps	2,800
Flash Point, °C	>93

Mixed Properties

Specific Gravity @ 25°C	1.13
Viscosity @ 25°C, cPs	2,400
Gel Time, 50 gm mass @ 25 °C, minutes	3
Tack free time, minutes	3.5 to 4

Recommended Curing Conditions

24 hours @ 25 °C (Recommended cure)

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties :

Shore Hardness , Durometer D	55
Glass Transition Temperature, °C	10
Tensile Strength, psi	270
Tensile Elongation, %	80

Electrical Properties:

Dielectric Strength, volts/mil	400
--------------------------------	-----

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Note: Before using this product please purge approximately 30 ml. of material prior to application. Discard purged material in accordance with the Material Safety Data Sheet. A video instruction is available upon request.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 20 °C to 30 °C. Storage below 20 °C or greater than 30 °C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
$\text{kV/mm} \times 25.4 = \text{V/mil}$
$\text{mm} / 25.4 = \text{inches}$
$\text{N} \times 0.225 = \text{lb}$
$\text{N/mm} \times 5.71 = \text{lb/in}$
$\text{psi} \times 145 = \text{N/mm}^2$
$\text{MPa} = \text{N/mm}^2$
$\text{N} \cdot \text{m} \times 8.851 = \text{lb} \cdot \text{in}$
$\text{N} \cdot \text{m} \times 0.738 = \text{lb} \cdot \text{ft}$
$\text{N} \cdot \text{mm} \times 0.142 = \text{oz} \cdot \text{in}$
$\text{mPa} \cdot \text{s} = \text{cP}$

Disclaimer

Note

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation Resin Technology Group, Inc., or Henkel Canada, Inc. the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.1