

LOCTITE[®] AA 392[™]

Known as LOCTITE[®] 392[™]
November 2014

PRODUCT DESCRIPTION

LOCTITE[®] AA 392[™] provides the following product characteristics:

Technology	Acrylic
Chemical Type	Modified acrylic
Appearance (uncured)	Translucent beige to dark amber ^{LMS}
Components	One component - requires no mixing
Viscosity	Medium
Cure	Activator
Secondary Cure	Heat
Application	Bonding

LOCTITE[®] AA 392[™] may be used for applications which require very fast assembly. This adhesive is particularly suited to DC motor assembly, magnet bonding and bonding of pre-coated sheet metal. Automated assembly lines with short cycle times will benefit from the rapid cure characteristics of LOCTITE[®] AA 392[™]. The product has the capability to produce tough, durable bonds with outstanding impact and peel resistance.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Specific Gravity @ 25 °C 1.16

Flash Point - See SDS

Viscosity, Brookfield - HBT, 25 °C, mPa·s (cP):

Spindle TA, speed 2.5 rpm, Helipath 20,000 to 80,000^{LMS}

Spindle TA, speed 20 rpm, Helipath 6,500 to 17,500^{LMS}

TYPICAL CURING PERFORMANCE

LOCTITE[®] AA 392[™] is designed to be used with Activator 7380[™] or 7387[™] and cured at room temperature. Cure characteristics are measured by determining fixture time (handling time) and speed of cure.

Fixture Time

Fixture time is defined as the time to develop a shear strength of 0.1 N/mm².


Fixture Time, seconds:

Steel, with Activator 7380[™] on 1 side:

0.05 mm gap	≤25
0.25 mm gap	≤330


Cure Speed vs. Activator

The graph below shows the shear strength developed with time on steel lap shears using and tested according to ISO 4587.



Cure Speed vs. Temperature

Heat can be used to effect or accelerate cure when surface priming operations are undesirable. Typical heat cure conditions consist of heating and maintaining bondline at a temperature shown in the graph below for the corresponding time specified. Optimum conditions for heat cure should be determined on the actual assemblies.



TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties:

Shore Hardness, ISO 868, Durometer D	65
Elongation, ISO 527-3, %	130
Tensile Strength, ISO 527-3	N/mm ² 18.6 (psi) (2,700)
Tensile Modulus, ISO 527-3	N/mm ² 144.8 (psi) (21,000)

TYPICAL PERFORMANCE OF CURED MATERIAL**Adhesive Properties**

After 24 hours @ 22 °C, Activator 7380™ on 1 side

Lap Shear Strength, ISO 4587:

Steel	N/mm ²	≥11.7 ^{LMS}
	(psi)	(≥1,696)

After 48 hours @ 22 °C, Activator 7380™ on 1 side

Lap Shear Strength, ISO 4587:

Steel :		
0 gap	N/mm ²	17.2
	(psi)	(2,500)
0.25 mm gap	N/mm ²	15.8
	(psi)	(2,300)
0.5 mm gap	N/mm ²	14.5
	(psi)	(2,100)
Aluminum :		
0 gap	N/mm ²	11
	(psi)	(1,600)
Zinc dichromate :		
0 gap	N/mm ²	11
	(psi)	(1,600)

TYPICAL ENVIRONMENTAL RESISTANCE

After 48 hours @ 22 °C, Activator 7380™ on 1 side

Heat Aging

Heat aged for 2000 hours

Lap Shear Strength, ISO 4587:

Steel:		
@ 93 °C	N/mm ²	13.1
	(psi)	(1,900)
@ 121 °C	N/mm ²	9
	(psi)	(1,300)
@ 150 °C	N/mm ²	3.4
	(psi)	(500)

Humidity Resistance

Conditioned in 50°C condensing humidity

Lap Shear Strength, ISO 4587:

Steel:		
1 week	N/mm ²	13
	(psi)	(1,900)
2 weeks	N/mm ²	9.3
	(psi)	(1,350)
4 weeks	N/mm ²	3.4
	(psi)	(500)

Chemical/Solvent Resistance

Aged under conditions indicated and tested @ 22 °C.

Environment	°C	% of initial strength
		720 h
Air reference	87	100
Water/glycol 50/50	87	30
Gasoline	87	10
Motor oil (MIL-L-46152)	87	100

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Safety Data Sheet (SDS).

Directions for use:

1. For best performance bond surfaces should be clean and free from grease.
2. To ensure a fast and reliable cure, Activator 7380™ or 7387™ should be applied to one of the bond surfaces and the adhesive to the other surface. Parts should be assembled within 15 minutes.
3. The recommended bondline gap is 0.1 mm. Where bond gaps are large (up to a maximum of 0.5 mm), or faster cure speed is required, Activator 7380™ or 7387™ should be applied to both surfaces. Parts should be assembled immediately (within 1 minute).
4. Excess adhesive can be wiped away with organic solvent.
5. Bond should be held clamped until adhesive has fixtured.
6. Product should be allowed to develop full strength before subjecting to any service loads (typically 24 to 72 hours after assembly, depending on bond gap, materials and ambient conditions).

Loctite Material Specification^{LMS}

LMS dated January 3, 2003. Test reports for each batch are available for the indicated properties. LMS test reports include selected QC test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Quality.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 8 °C to 21 °C. Storage below 8 °C or greater than 28 °C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

°C x 1.8) + 32 = °F
 kV/mm x 25.4 = V/mil
 mm / 25.4 = inches
 µm / 25.4 = mil
 N x 0.225 = lb
 N/mm x 5.71 = lb/in
 N/mm² x 145 = psi
 MPa x 145 = psi
 N·m x 8.851 = lb·in
 N·m x 0.738 = lb·ft
 N·mm x 0.142 = oz·in
 mPa·s = cP

Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our

knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.5