



LOCTITE® 425™

February 2011

PRODUCT DESCRIPTION

LOCTITE® 425™ provides the following product characteristics:

Technology	Cyanoacrylate
Chemical Type	Ethyl cyanoacrylate / Aliphatic ester
Appearance	Dark blue liquid ^{LMS}
Components	One part - requires no mixing
Viscosity	Low
Cure	Humidity
Application	Low strength threadlocking / retaining
Key Substrates	Metals and Plastics

LOCTITE® 425™ is designed as a fast curing, low strength adhesive for locking metal and plastics fasteners. The product is designed for pre- or post-application. LOCTITE® 425™ cures quickly on plated metal and plastics fasteners; fixturing is achieved in less than 2 minutes and full strength within 24 hours. This product is commonly used for tamperproofing the head of screws or potentiometers. Fixture speed can be increased by application of a LOCTITE® Cyanoacrylate activator - e.g. 7113™. This product is typically used in applications with an operating range of -54 °C to +85 °C.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Specific Gravity @ 25 °C	1.1
Viscosity, Brookfield - LVF, 25 °C, mPa·s (cP):	
Spindle 1, speed 30 rpm	40 to 80 ^{LMS}
Flash Point - See MSDS	

TYPICAL CURING PERFORMANCE

Under normal conditions, the atmospheric moisture initiates the curing process. Although full functional strength is developed in a relatively short time, curing continues for at least 24 hours before full chemical/solvent resistance is developed.

TYPICAL PROPERTIES OF CURED MATERIAL

Electrical Properties:	
Volume Resistivity, IEC 60093, Ω·cm	>1×10 ¹⁵
Surface Resistivity, IEC 60093, Ω	>1×10 ¹⁵
Dielectric Breakdown Strength, IEC 60243-1, kV/mm	19.7
Dielectric Constant / Dissipation Factor, IEC 60250:	
100 Hz	4.5 / 0.037
10 kHz	4.2 / 0.04

TYPICAL PERFORMANCE OF CURED MATERIAL

Adhesive Properties

Cured for 24 hours @ 22 °C, on untorqued zinc plated fasteners

Torque Strength:

Fastener Size	Breakaway	Prevail
2 - 56	N·m 0.02 (lb.in.) (0.25)	N·m 0.02 (lb.in.) (0.25)

4 - 40	N·m 0.12 (lb.in.) (1.1)	N·m 0.14 (lb.in.) (1.3)
6 - 32	N·m 0.25 (lb.in.) (2.2)	N·m 0.23 (lb.in.) (2.0)
8 - 32	N·m 0.29 (lb.in.) (2.6)	N·m 0.24 (lb.in.) (2.1)
10 - 32	N·m 0.36 (lb.in.) (3.2)	N·m 0.23 (lb.in.) (2.0)
3/8 x 24	N·m 1.1 to 8.5 ^{LMS} (lb.in.) (9.7 to 75.2)	N·m 1.1 to 8.5 ^{LMS} (lb.in.) (9.7 to 75.2)

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials

For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

Directions for use:

1. For best performance bond surfaces should be clean and free from grease.
2. This product performs best in thin bond gaps (0.05 mm).
3. Excess adhesive can be dissolved with Loctite cleanup solvents, nitromethane or acetone.

Loctite Material Specification^{LMS}

LMS dated September 01, 1995. Test reports for each batch are available for the indicated properties. LMS test reports include selected QC test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Quality.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 2 °C to 8 °C. Storage below 2 °C or greater than 8 °C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.



Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 1.2