

LORD® Accelerator 26

Description

LORD® Accelerator 26 is a no-mix curative designed for use with LORD acrylic adhesives. LORD Accelerator 26 can be used with LORD 200, 500 and Maxlok™ series acrylic adhesives.

Features and Benefits

Convenient – provides room temperature cure with all LORD acrylic adhesives.

Extended Work Time – provides extended assembly time as adhesive does not begin cure until it comes in contact with surface coated with dry accelerator.

Easy to Apply – applies easily by brush, wipe, spray or dip methods onto one or both bonding surfaces.

Fast Cure – dries in approximately 15 minutes to an off-white crystalline film.

Environmentally Friendly – does not contain chlorinated solvents.

Environmentally Resistant – resists common environmental conditions when used with LORD acrylic adhesives.

Application

Surface Preparation – Remove grease, loose contamination or poorly adhering oxides from metal surfaces. Normal amounts of mill oils and drawing compounds usually do not present a problem in adhesion. Most plastics require a simple cleaning before bonding. Some may require abrading for optimum performance.

Applying – Apply a light coat of accelerator by brush, wipe, spray or dip method onto one or both bonding surfaces.

LORD Accelerator 26 applied to one surface will cure bondline thicknesses up to 0.015 in (0.38 mm). For bondline thicknesses between 0.015-0.03 in (0.38-0.76 mm), apply accelerator to both bonding surfaces.

Drying/Curing – LORD Accelerator 26 will dry in approximately 15 minutes to an off-white crystalline film. If accelerator does not dry within 60 minutes, dispose of material in compliance with regulations.

Once dry, apply adhesive resin on other bonding surface, and join the parts. Cure begins once adhesive comes in contact with accelerator. Handling strength and complete cure times will vary depending on acrylic adhesive used.

Typical Properties*

Appearance	Clear to Opaque, Colorless to Amber Liquid
Viscosity, cP @ 77°F (25°C) Brookfield LVT Spindle 1, 30 rpm	<10
Density lb/gal (g/m³)	7.5-8.5 (0.9-1.0)
Solids Content by Weight, %	10
Flash Point, °F (°C)	>109 (>43)

*Data is typical and not to be used for specification purposes.

LORD TECHNICAL DATA

Coated parts may be stored for up to four weeks if kept below 80°F (26°C) and out of direct sunlight. Keep parts covered to avoid contamination.

Cleanup – Clean equipment and tools prior to the adhesive cure with hot water and detergent or an organic solvent such as ketones. Once adhesive is cured, heat the adhesive to 400°F (204°C) or above to soften the adhesive. This allows the parts to be separated and the adhesive to be more easily removed.

Shelf Life/Storage

Shelf life is six months when stored at 40-70°F (4-21°C) in original, unopened container. Exposure to temperatures greater than 80°F (27°C) will shorten shelf life.

Cautionary Information

Before using this or any LORD product, refer to the Material Safety Data Sheet (MSDS) and label for safe use and handling instructions.

For industrial/commercial use only. Must be applied by trained personnel only. Not to be used in household applications. Not for consumer use.

Values stated in this technical data sheet represent typical values as not all tests are run on each lot of material produced. For formalized product specifications for specific product end uses, contact the Customer Support Center.

Information provided herein is based upon tests believed to be reliable. In as much as LORD Corporation has no control over the manner in which others may use this information, it does not guarantee the results to be obtained. In addition, LORD Corporation does not guarantee the performance of the product or the results obtained from the use of the product or this information where the product has been repackaged by any third party, including but not limited to any product end-user. Nor does the company make any express or implied warranty of merchantability or fitness for a particular purpose concerning the effects or results of such use.

LORD, Maxlok and "Ask Us How" are trademarks of LORD Corporation or one of its subsidiaries.

LORD provides valuable expertise in adhesives and coatings, vibration and motion control, and magnetically responsive technologies. Our people work in collaboration with our customers to help them increase the value of their products. Innovative and responsive in an ever-changing marketplace, we are focused on providing solutions for our customers worldwide ... Ask Us How.

LORD Corporation World Headquarters

111 Lord Drive
Cary, NC 27511-7923
USA

Customer Support Center (in United States & Canada)

+1 877 ASK LORD (275 5673)

www.lord.com

For a listing of our worldwide locations, visit LORD.com.