

LORD® 506 Acrylic Adhesive

with LORD Accelerator 4, 17 or 19

Description

LORD® 506 acrylic adhesive when cured with LORD Accelerator 4, 17 or 19 creates a semi-flexible adhesive system that will quickly bond a wide variety of thermoplastics and thermoset plastics.

LORD 506 acrylic adhesive can be mixed with either LORD Accelerator 4, LORD Accelerator 17 or LORD Accelerator 19. LORD Accelerator 4 is a no-mix accelerator applied to the substrate before the acrylic adhesive. LORD Accelerators 17 and 19 must be mixed into the acrylic adhesive prior to application. LORD Accelerator 19 is available in off-white or black. For further detailed information on LORD Accelerator 4, LORD Accelerator 17 and LORD Accelerator 19, refer to the applicable data sheet.

Features and Benefits

Versatile – bonds a wide variety of substrates including ABS, acrylic, polycarbonate, FRP, prepared metals, urethane, phenolic, polysulfone, and vinyl; can be used with both Mix-In and No-Mix accelerators.

Convenient – cures very quickly at room temperature.

Durable – accommodates shock and sudden stress loading.

Temperature Resistant – performs at temperatures from -40°F to +300°F (-40°F to +149°C).

Environmentally Resistant – resists dilute acids, alkalis, solvents, greases, oils and moisture; provides excellent resistance to indirect UV exposure and weathering.

Typical Properties*

Appearance	Colorless to Amber Gel
Viscosity, cP @ 77°F (25°C) Brookfield HBT Spindle 3, 5 rpm	20,000-70,000
Density	
lb/gal	8.25-8.65
(kg/m ³)	(989-1036)
Flash Point (Closed Cup), °F (°C)	53 (11)

*Data is typical and not to be used for specification purposes.

Application

Surface Preparation – Remove grease, loose contamination or poorly adhering oxides from metal surfaces. Normal amounts of mill oils and drawing compounds usually do not present a problem in adhesion. Most plastics require a simple cleaning before bonding. Some may require abrading for optimum performance.

Mixing

- No-Mix Accelerator
LORD 506 acrylic adhesive and LORD Accelerator 4 are not mixed prior to application.
- Mix-In Accelerator
Mix LORD 506 acrylic adhesive with the proper amount of LORD Accelerator 17 or 19. Handheld cartridges will automatically dispense the correct volumetric ratio of each component. Even color distribution visually indicates a thorough mix. Once mixed, the adhesive cures rapidly.

Applying

- No-Mix Accelerator
Apply LORD Accelerator 4 to one or both substrate surfaces. Allow accelerator to dry. For further details on the use of LORD Accelerator 4, refer to the LORD Accelerator 4 data sheet.

Once accelerator is dry, apply adhesive to the other substrate surface using a handheld cartridge or automatic dispense equipment. Mate the two surfaces and slide into correct position within the working time of the adhesive.

- Mix-In Accelerator

Apply mixed adhesive using handheld cartridges or automatic meter/mix/dispense equipment.

Handheld Cartridges

1. Load the cartridge into the applicator gun and remove the end caps.
2. Level the plungers by expelling a small amount of adhesive to ensure both sides are level.
3. Attach mixing tip and expel a mixer's length of adhesive.
4. Apply adhesive to substrate and mate the parts within the working time of the adhesive. Clamp in position until adhesive reaches handling strength.

Meter/Mix/Dispense Equipment

Contact your LORD representative if assistance is needed using this equipment. When using such equipment, all wetted parts must be made of stainless steel and all hoses should be Teflon®-lined high pressure hose.

Curing – Cure begins immediately once adhesive and accelerator come in contact. Handling strength is achieved within 8-12 minutes. Complete cure will take 24 hours at room temperature. Mating surfaces should be fixtured as soon as possible (within 4-6 minutes) after adhesive application.

Teflon is a registered trademark of E.I. duPont de Nemours and Company.

Typical Properties* of Adhesive Mixed with Recommended Accelerator

	A4	A17	A19	A19 Black
Mix Ratio by Volume, Adhesive to Accelerator	No-Mix	10:1	10:5	10:5
Solids Content, %	100	100	100	100
Working Time, min @ 75°F (24°C)	—	8-10	12-14	12-14
Time to Handling Strength**, min @ 75°F (24°C)	20-25	12-14	8-10	8-10
Mixed Appearance	—	Tan Paste	Tan Paste	Grey Paste
Cured Appearance	—	Tan to Green	Tan to Green	Black

*Data is typical and not to be used for specification purposes.

**Dependent on ambient air temperature and mass; established when adhesive reaches 100 psi.

LORD TECHNICAL DATA

Shelf Life/Storage

Shelf life is six months when stored below 80°F (27°C) in original, unopened container. Storage temperatures of 40-50°F (4-10°C) are recommended. If stored cold, allow product to return to room temperature before using.

Cautionary Information

Before using this or any LORD product, refer to the Safety Data Sheet (SDS) and label for safe use and handling instructions.

For industrial/commercial use only. Must be applied by trained personnel only. Not to be used in household applications. Not for consumer use.

Values stated in this technical data sheet represent typical values as not all tests are run on each lot of material produced. For formalized product specifications for specific product end uses, contact the Customer Support Center.

Information provided herein is based upon tests believed to be reliable. In as much as LORD Corporation has no control over the manner in which others may use this information, it does not guarantee the results to be obtained. In addition, LORD Corporation does not guarantee the performance of the product or the results obtained from the use of the product or this information where the product has been repackaged by any third party, including but not limited to any product end-user. Nor does the company make any express or implied warranty of merchantability or fitness for a particular purpose concerning the effects or results of such use.

LORD and "Ask Us How" are trademarks of LORD Corporation or one of its subsidiaries.

LORD provides valuable expertise in adhesives and coatings, vibration and motion control, and magnetically responsive technologies. Our people work in collaboration with our customers to help them increase the value of their products. Innovative and responsive in an ever-changing marketplace, we are focused on providing solutions for our customers worldwide ... Ask Us How.

LORD Corporation
World Headquarters

111 Lord Drive
Cary, NC 27511-7923
USA

Customer Support Center (in United States & Canada)

+1 877 ASK LORD (275 5673)

www.lord.com

For a listing of our worldwide locations, visit LORD.com.