

# LORD® 7556 Urethane Adhesive

## Description

LORD® 7556 adhesive is an equal-mix, two-component clear urethane adhesive system used to bond Lexan®, ABS, polycarbonate and other plastics. This adhesive will also bond primed metals.

## Features and Benefits

**Non-Flammable** – does not require explosion-proof equipment.

**Environmentally Recommended** – does not contain ozone depleting chemicals.

**Environmentally Resistant** – resists sunlight, weathering, humidity and salt spray.

**Chemically Resistant** – solvent resistant when cured. Painting and most cleaning processes do not affect bond strength.

**Non-Sag** – remains in position when applied on vertical or overhead surfaces, allowing for greater process flexibility.

## Application

**Surface Preparation** – Surfaces should be free of grease, dirt and other contaminants. For plastics, clean the surface with a dry rag wipe or a rag dampened with solvent. For metals, prime or grit blast the surface, then solvent wash for optimum bond performance.

**Mixing** – Mix resin with the appropriate curative at a 1:1 ratio, by volume. Handheld cartridges will automatically dispense the correct volumetric ratio of each component. Once mixed, the adhesive cures rapidly.

**Applying** – Apply adhesive using handheld cartridges. Assemble parts within working time of the adhesive.

**Curing** – LORD 7556 adhesive will cure to full strength in 24 hours at 77°F (25°C).

**Cleanup** – Clean equipment and tools prior to the adhesive cure with solvents such as acetone or methyl ethyl ketone (MEK). Once adhesive is cured, heat the adhesive to 300°F (149°C) or above to soften the adhesive. This allows the parts to be separated and the adhesive to be more easily removed.

*Lexan is a trademark of SABIC Innovative Plastics.*

## Typical Properties\*

	7556-A Resin	7556-B Curative	7556-C Curative
Appearance	Translucent Paste	Translucent Paste	Clear Liquid
Viscosity, cP @ 77°F (25°C)	40,000-160,000	95,000-300,000	80,000-300,000
Density			
lb/gal	9.64-10.04	9.2-9.6	9.2-9.6
(kg/m³)	(1155-1203)	(1102-1150)	(1102-1150)
Flash Point (Closed Cup), °F (°C)	>200 (>93)	>200 (>93)	>200 (>93)

\*Data is typical and not to be used for specification purposes.

# LORD TECHNICAL DATA

## Shelf Life/Storage

Shelf life is six months when stored in a clean, dry environment at 70-80°F (21-27°C) in original, unopened container.

After opening, protect adhesive from excessive exposure to moisture by replacing protective cap on the cartridge.

## Cautionary Information

Before using this or any LORD product, refer to the Safety Data Sheet (SDS) and label for safe use and handling instructions.

*For industrial/commercial use only.* Must be applied by trained personnel only. Not to be used in household applications. Not for consumer use.

## Typical Properties\* of Resin Mixed with Curative

	7556-A/B	7556-A/C
Mix Ratio, by Volume		
Resin to Curative	1:1	1:1
Solids Content by Weight, %	100	100
Working Time, min	3-5	4-6
	@ 77°F (25°C)	@ 90°F (32°C)
Time to Handling Strength, min	60	90-140
	@ 77°F (25°C)	@ 73°F (23°C)

\*Data is typical and not to be used for specification purposes.

Values stated in this technical data sheet represent typical values as not all tests are run on each lot of material produced. For formalized product specifications for specific product end uses, contact the Customer Support Center.

Information provided herein is based upon tests believed to be reliable. In as much as LORD Corporation has no control over the manner in which others may use this information, it does not guarantee the results to be obtained. In addition, LORD Corporation does not guarantee the performance of the product or the results obtained from the use of the product or this information where the product has been repackaged by any third party, including but not limited to any product end-user. Nor does the company make any express or implied warranty of merchantability or fitness for a particular purpose concerning the effects or results of such use.

LORD and "Ask Us How" are trademarks of LORD Corporation or one of its subsidiaries.

LORD provides valuable expertise in adhesives and coatings, vibration and motion control, and magnetically responsive technologies. Our people work in collaboration with our customers to help them increase the value of their products. Innovative and responsive in an ever-changing marketplace, we are focused on providing solutions for our customers worldwide ... Ask Us How.

### LORD Corporation World Headquarters

111 Lord Drive  
Cary, NC 27511-7923  
USA

### Customer Support Center (in United States & Canada)

+1 877 ASK LORD (275 5673)

[www.lord.com](http://www.lord.com)

For a listing of our worldwide locations, visit [LORD.com](http://LORD.com).