

Chemlok® 459X Primer

Technical Data Sheet

Chemlok® 459X primer is designed for promoting adhesion to thermoplastic elastomers (TPE), thermoplastic polyolefins (TPO) and EPDM. Chemlok 459X primer is in xylene solvent, diluted for direct application.

Chemlok 459X primer can be used in conjunction with urethane and epoxy adhesives, as well as with a variety of double-sided tapes. It may also serve as a primer to enhance the adhesion of polyurethane coatings on cured EPDM and other difficult-to-bond elastomers.

Features and Benefits:

Versatile – enhances adhesion to difficult-to-bond elastomers, increasing the adhesion of coatings, double-sided tape and adhesives.

Easy to Apply – low viscosity allows for easy application; no dilution necessary.

Application:

Surface Preparation – Wipe surface to be primed with a suitable solvent, or wash with detergent and water, then rinse.

Mixing – No mixing is required before or during use.

Applying – Apply primer by brush, dip or spray method. For optimum adhesion, the dry film thickness of Chemlok 459X primer should be approximately 2.5 micron (0.1 mil).

Drying/Curing – Allow primer to air-dry for 30-60 minutes at room temperature with good air flow, or use an oven at 93-121°C (200-250°F) for 5-10 minutes. A heat cycle generally improves adhesion.

Cleanup – Use a dry cloth wipe to remove wet primer. Remove dried primer with xylene or a ketone-type solvent.

Shelf Life/Storage:

Shelf life is six months from date of shipment when stored by the recipient at 21-27°C (70-80°F) in original, unopened container.

Cautionary Information:

Before using this or any Parker LORD product, refer to the Safety Data Sheet (SDS) and label for safe use and handling instructions.

For industrial/commercial use only. Must be applied by trained personnel only. Not to be used in household applications. Not for consumer use.

Typical Properties*

Appearance	Amber Liquid
Viscosity, cps @ 25°C (77°F) Brookfield LVT Spindle 1, 60 rpm	~10
Density kg/m ³ (lb/gal)	850.0 - 880.0 (7.1 - 7.3)
Solids Content by Weight, %	2.7 - 4.1
Flash Point (Seta), °C (°F)	27 (81)
Solvents	Xylene

*Data is typical and not to be used for specification purposes.



ENGINEERING YOUR SUCCESS.

Values stated in this document represent typical values as not all tests are run on each lot of material produced. For formalized product specifications for specific product end uses, contact the Customer Support Center.

Information provided herein is based upon tests believed to be reliable. In as much as Parker LORD has no control over the manner in which others may use this information, it does not guarantee the results to be obtained. In addition, Parker LORD does not guarantee the performance of the product or the results obtained from the use of the product or this information where the product has been repackaged by any third party, including but not limited to any product end-user. Nor does the company make any express or implied warranty of merchantability or fitness for a particular purpose concerning the effects or results of such use.

WARNING — USER RESPONSIBILITY. FAILURE OR IMPROPER SELECTION OR IMPROPER USE OF THE PRODUCTS DESCRIBED HEREIN OR RELATED ITEMS CAN CAUSE DEATH, PERSONAL INJURY AND PROPERTY DAMAGE.

This document and other information from Parker-Hannifin Corporation, its subsidiaries and authorized distributors provide product or system options for further investigation by users having technical expertise.

The user, through its own analysis and testing, is solely responsible for making the final selection of the system and components and assuring that all performance, endurance, maintenance, safety and warning requirements of the application are met. The user must analyze all aspects of the application, follow applicable industry standards, and follow the information concerning the product in the current product catalog and in any other materials provided from Parker or its subsidiaries or authorized distributors.

To the extent that Parker or its subsidiaries or authorized distributors provide component or system options based upon data or specifications provided by the user, the user is responsible for determining that such data and specifications are suitable and sufficient for all applications and reasonably foreseeable uses of the components or systems.

©2020 Parker Hannifin - All Rights Reserved

Information and specifications subject to change without notice and without liability therefor. Trademarks used herein are the property of their respective owners.

OD DS3145E 10/20 Rev.3



Parker LORD
Engineered Materials Group

111 LORD Drive
Cary, NC 27511-7923
USA

www.lord.com