

**Technical Data Sheet**

**Electrical Insulation**

## **CONATHANE® EN-2553**

**Two-Component Polyurethane Potting Compound**

**ELANTAS PDG, Inc.**

1405 Buffalo Street  
Olean, NY 14760  
USA  
Tel +1 716 372-9650  
Fax +1 716 372-1594  
info.elantas.pdg@altana.com  
[www.elantas.com](http://www.elantas.com)

5200 North Second Street  
St. Louis, MO 63147  
USA  
Tel +1 314 621-5700  
Fax +1 314 436-1030  
info.elantas.pdg@altana.com  
[www.elantas.com](http://www.elantas.com)

## CONATHANE® EN-2553

### Product Description

CONATHANE® EN-2553 is a two-component, filled, flame-retardant polyurethane potting system.

### Areas of Application

Potting and encapsulation of electronic components, modules, circuit boards, assemblies and related devices.

### Features and Benefits

- UL RTI 120
- UL94 V-0
- Low stress cure for protection of sensitive components
- Excellent thermal shock resistance

### Application Methods

- Hand-mix Bench Potting / Casting
- Meter-mix Bench Potting / Casting
- Meter-mix Vacuum Potting / Casting

### Transportation / Storage

Store below 25°C / 77°F in a dry controlled environment out of direct sunlight. This material should be suitable for use stored under these conditions in the original sealed containers for twelve (12) months from the date of shipment.

Failure to store the product as recommended above may lead to deterioration in product performance.

This product is sensitive to moisture and atmospheric humidity. Containers, once opened, should be used immediately or blanketed with dry air or nitrogen (CONAP® Dri-Purge) before resealing.

Mix and degas individual components thoroughly prior to use.

CONATHANE® EN-2553 Part A may crystallize upon storage or during shipment. If this has occurred, heat to 60°C, mix thoroughly, and cool to room temperature before processing.

### Health / Safety

Refer to the Safety Data Sheet.

---

### Typical Properties of Material as Supplied

Property	Conditions	Value	
		CONATHANE® EN-2553 Part A Urethane Prepolymer	CONATHANE® EN-2553 Part B Curative
Viscosity	25°C / 77°F	300 cP	8,500 cP
Specific Gravity	25°C / 77°F	1.24	1.49
Color		Brown	Black or Blue
Mix Ratio	Parts by weight Parts by volume	17 20	100 100

## CONATHANE® EN-2553

### Typical Properties of Mixed Materials

Property	Conditions	Value	Units
Viscosity (initial)	25°C / 77°F	4,500	cP
Work Life	25°C / 77°F	55	minutes

### Regulatory Information

Property	
RoHS Compliance	CONATHANE® EN-2553 Part A Urethane Prepolymer and CONATHANE® EN-2553 Part B Curative comply with Directive 2011/65/EU of the European Parliament and of the Council of 8 June 2011 (RoHS 2.0) as amended 31 March 2015.

### Application / Curing Schedule

Mix the EN-2553 Part A and EN-2553 Part B in the ratio specified above until homogeneous. Components may be preheated up to 60°C if reduced viscosity is required. If hand-mixing, degas at >27 in. Hg before use.

Cure 7 days at 25°C / 77°F – or – 16 hours at 80°C / 176°F

The cure schedules above are based on time after the unit reaches the specified temperature and are recommendations only. The user is responsible for determining the optimum cure conditions for his application.

### Typical Electrical Properties

Property	Test Method	Conditions	Value	Units
Dielectric Strength	ASTM D149	25°C / 77°F	560	volts / mil
Dielectric Constant	ASTM D150	100 Hz @ 25°C / 77°F	4.8	
		1 kHz @ 25°C / 77°F	4.2	
		1 MHz @ 25°C / 77°F	3.6	
Dissipation Factor	ASTM D150	100 Hz @ 25°C / 77°F	0.13	
		1 kHz @ 25°C / 77°F	0.17	
		1 MHz @ 25°C / 77°F	0.02	
Volume Resistivity	ASTM D257	25°C / 77°F	3.1 x 10 <sup>14</sup>	ohm-cm
Surface Resistivity	ASTM D257	25°C / 77°F	3.5 x 10 <sup>15</sup>	ohms / sq.

# CONATHANE<sup>®</sup> EN-2553

## Typical Physical Properties

Property	Test Method	Conditions	Value	Units
Color	Visual	25°C / 77°F	Black or Blue	
Shore Hardness	ASTM D2240	25°C / 77°F	A 95	
Tensile Strength	ASTM D412	25°C / 77°F	1,050	psi
Ultimate Elongation	ASTM D412	25°C / 77°F	60	%
Tear Strength	ASTM D624	25°C / 77°F	140	pli
Flammability	UL94	3.0 mm	V-0	

The above properties are typical values and are not intended for specification use.

ELANTAS PDG, Inc. warrants the chemical composition of its products within stated tolerances, but does not guarantee that a product will be appropriate for any particular application. Any recommendation, performance of tests or suggestion is offered merely as a guide and is not a substitute for a thorough evaluation by the user. No representative of ELANTAS PDG, Inc. has the authority to offer a warranty that a product will perform satisfactorily in manufacturing an article and no such representation should be relied upon.

The user may forward, distribute, and/or photocopy this document only if unaltered and complete, and should refrain from any unauthorized use. This document may not be copied to a website without specific authorization from ELANTAS PDG, Inc.