

Technical Data Sheet

Electronic & Engineering Materials

CONAP[®] CE-1171

One-Component Acrylic Conformal Coating

ELANTAS PDG, Inc.

1405 Buffalo Street
Olean, NY 14760
USA
Tel +1 716 372-9650
Fax +1 716 372-1594
info.elantas.pdg@altana.com
www.elantas.com

5200 North Second Street
St. Louis, MO 63147
USA
Tel +1 314 621-5700
Fax +1 314 436-1030
info.elantas.pdg@altana.com
www.elantas.com

CONAP® CE-1171

Product Description

CONAP® CE-1171 is a transparent, solvent-based, fast-curing, single-component acrylic conformal coating.

Areas of Application

CONAP® CE-1171 provides an excellent electrical and moisture barrier for thin film applications on components and printed circuit boards.

Features and Benefits

- QPL Listed for MIL-I-46058C for Type AR
- IPC-CC-830B
- Halogen-free (IEC 61249-2-21)
- Excellent hydrolytic stability
- UL94 V-0
- Flexible coating
- Excellent adhesion to phenolic and epoxy-glass laminates; even in harsh environments
- Excellent reparability
- Tracer dye for inspection under UV lighting

Application Methods

- Spray
- Dip
- Brush

Transportation / Storage

Store at or below 25°C / 77°F in a dry controlled environment out of direct sunlight. This material should be suitable for use stored under these conditions in the original sealed containers for twelve (12) months from the date of shipment.

This product is sensitive to moisture and atmospheric humidity. Containers, once opened, should be used immediately or blanketed with dry air or nitrogen (CONAP® Dri-Purge) before resealing.

Failure to store the product as recommended above may lead to deterioration in product performance.

Health / Safety

CAUTION: Material is flammable. Do NOT use in the presence of open flames or sparks.

Refer to the Safety Data Sheet

Typical Properties of Material as Supplied

Property	Conditions	Value	Units
Viscosity	25°C / 77°F	900	cP
Specific Gravity	25°C / 77°F	0.98	
Color		Amber, slight haze	
Solids Content	135°C for 45 min	30	%
Flash Point	ASTM D93	18 65	°C °F

CONAP® CE-1171

Regulatory Information

Property	Test Method	Value	Units
Volatile Organic Content	ASTM D3960	5.7	pounds / gallon
RoHS Compliance	CONAP® CE-1171 Acrylic Coating complies with Directive 2011/65/EU of the European Parliament and of the Council of 8 June 2011 (RoHS 2.0) as amended 31 March 2015.		

Application / Curing Schedule

Performance of the CONAP® CE-1171 cured film is dependent on process controls used in application of the coating. Cleanliness of the substrate is a major factor in promoting adhesion and preventing under-film corrosion. Assemblies must be clean, oil-free, and dry. For specific recommendations, please request Technical Bulletin TI-4007 *Application Information for CONATHANE® and CONAP® conformal coatings*.

CE-1171 can be applied by spraying, dipping or brushing. If viscosity reduction is desired, dilutions of 10 – 20% by weight with the CONAP® S-22 Solvent are recommended for most applications. CONAP® S-22 Solvent meets Rule 66/3 exemption criteria. For some spray applications, dilutions up to 1:1 by volume may be required to avoid cobwebbing.

A minimum of two coats of CE-1171 is recommended for optimal protection. A total cured film thickness of 2 ± 1 mils is recommended. CE-1171 may be recoated after the previous film is tack-free.

Curing of the film is dependent upon the evaporation of the solvents. The coating will typically dry tack-free in 20 minutes and cure in 24 hours at 25°C / 77°F. Alternatively, dry tack-free can be completed in 15 minutes and cure can be completed in 60 minutes at 60°C / 140°F.

The cure schedules above are based on time after the unit reaches the specified temperature and are recommendations only. The user is responsible for determining the optimum cure conditions for his application.

Reparability

CONAP® CE-1171 has only fair resistance to solvents. Fully cured films of CE-1171 can easily be removed by immersion in solvents such as CONAP® S-8, CONAP® S-13, CONAP® S-22, toluene or ketones. This facilitates repair of the coating and removal of any damaged components.

After removing the coating, follow normal cleaning procedures and recoat.

CONAP® CE-1171

Typical Physical Properties

Property	Test Method	Conditions	Value
Color	Visual	25°C / 77°F	Slight haze
Solvent Resistance			Fair
Hydrolytic Stability	MIL-I-46058C	after 120 days @ 85°C / 95% RH	No discoloration or degradation
Flexibility	MIL-I-46058C	1/8" diameter mandrel	No cracking or crazing
Thermal Shock	MIL-STD-810B	-65 to 125°C (-85 to 257°F)	No cracking or deformation
Flame Resistance	FED STD-406		Self-extinguishing
Fungus Resistance	ASTM G-21		Non-nutrient
Solderability			Excellent
Inspection		UV Light	Fluorescent

Typical Electrical Properties

Property	Test Method	Conditions	Value	Units
Insulation Resistance	MIL-I-46058C	2 mil @ 25°C / 50% RH after 10 d @ 65°C / 95% RH	>1.5 x 10 ¹⁶	ohms
			2.5 x 10 ¹⁰	ohms
Dielectric Strength	ASTM D-149	25°C / 77°F	3000 min	volts/mil
Dielectric Withstanding Voltage	MIL-I-46058C	1,500 VAC	No flashover or breakdown	
Dielectric Constant	ASTM D-150	100 Hz @ 25°C / 77°F	2.7	
Dissipation Factor	ASTM D-150	100 Hz @ 25°C / 77°F	0.01	
Volume Resistivity	ASTM D-257	25°C / 77°F	2 x 10 ¹⁵	ohm-cm

The above properties are typical values and are not intended for specification use.

ELANTAS PDG, Inc. warrants the chemical composition of its products within stated tolerances, but does not guarantee that a product will be appropriate for any particular application. Any recommendation, performance of tests or suggestion is offered merely as a guide and is not a substitute for a thorough evaluation by the user. No representative of ELANTAS PDG, Inc. has the authority to offer a warranty that a product will perform satisfactorily in manufacturing an article and no such representation should be relied upon.

The user may forward, distribute, and/or photocopy this document only if unaltered and complete, and should refrain from any unauthorized use. This document may not be copied to a website without specific authorization from ELANTAS PDG, Inc.