



URETHANE U100N-HV

NON-SAG URETHANE ADHESIVE

TECHNICAL DATA

Product Description

Resin Design's Urethane U100N-HV is a room temperature curing two part polyurethane system designed to be used for high performance bonding applications. This one to one mix ratio product cures at room temperature in 12-24 hours to a tough and flexible polymer.

APPLICATIONS

FEATURES

- Two component system
- Room temperature cure
- Moisture resistant
- Flexible
- High viscosity

RECOMMENDED SUBSTRATES

- Glass
- Wood
- Metals
- Polycarbonates

UNCURED PROPERTIES

Property	Value	Test Method
Solvent Content	No Nonreactive Solvents	N/A
Composition, PT A:B	Isocyanate : Polyol	N/A
Mixed Color	Clear	N/A
Viscosity @ 25C, cps, spn 7 @20RPM, PT A	50,000 to 200,000	QPTTEST001
Viscosity @ 25C, cps, spn 7 @20RPM, PT B	25,000 to 50,000	QPTTEST001
Specific Gravity @ 25C, PT A:B	1.15	QPTTEST002
Specific Gravity @ 25C, PT A:B	1.09	QPTTEST002
Mix Ratio by Volume, PT A:B	1:1	N/A

CURED MECHANICAL PROPERTIES

Property	Value	Test Method
Hardness, Shore A	85	QPTTEST012
Tensile Lap Shear, Polycarbonate, psi	540	N/A
Elongation @ 25C, %	>220	N/A
Moisture Resistance	Excellent	N/A
Operating Temperature, C	-20 to 120	N/A
Dielectric Strength, Volts/mil	420	N/A
Dielectric Constant, 1 MHz	3.2	N/A
Dissipation Factor, 1MHz	0.02	N/A
Thermal Conductivity, W/mK	0.25	N/A
CTE, ppm/C	120	N/A
Water Absorption @1 hour boil, %	<2	N/A
Linear Shrinkage	1.1	N/A
Tensile Strength, psi, N/(mm ²)	>1500	QPTTEST005

CURE OVERVIEW

Property	Value	Test Method
Gel Time @ 25C, min	6-8	QPTTEST020
Cure Time @ Room Temperature, hr	24	N/A
Cure Time @ 65C, min	15 to 30	N/A

Storage:

Store material in cool, dry location at a temperature between 10°C to 25°C. Keep from freezing. Material is sensitive to moisture. Refer to packaging specific quote for shelf life information. Consult SDS for safe handling recommendations.

Revision Number: 10 Date: 09 November, 2017

Resin Designs 11 State Street Woburn, MA 01801 www.resindesigns.com P 781-935-3133 F 781-935-3144

RESIN DESIGNS, LLC MAKES NO EXPRESS OR IMPLIED REPRESENTATIONS OR WARRANTIES, INCLUDING WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR OTHERWISE, WITH RESPECT TO THIS PRODUCT AND GUARANTEES NO PARTICULAR OUTCOME OR RESULT FROM ITS USE. RESIN DESIGNS' LIABILITY TO CUSTOMER WITH RESPECT TO THIS PRODUCT SHALL IN NO EVENT EXCEED THE AMOUNT PAID BY CUSTOMER FOR IT.