

**Technical Data Sheet**

**Electrical Insulation**

## **CONAPOXY® FR-1080**

**Two-Component Epoxy Potting Compound**

**ELANTAS PDG, Inc.**

1405 Buffalo Street  
Olean, NY 14760  
USA  
Tel +1 716 372-9650  
Fax +1 716 372-1594  
info.elantas.pdg@altana.com  
[www.elantas.com](http://www.elantas.com)

5200 North Second Street  
St. Louis, MO 63147  
USA  
Tel +1 314 621-5700  
Fax +1 314 436-1030  
info.elantas.pdg@altana.com  
[www.elantas.com](http://www.elantas.com)

# CONAPOXY® FR-1080

## Product Description

CONAPOXY® FR-1080 is a two-component, unfilled epoxy potting system.

## Areas of Application

Potting and encapsulation of electrical / electronic devices such as modules, transformers, and coils as well as strain sensitive applications.

## Features and Benefits

- Class H (180°C) rated
- Long work life
- Elevated temperature cure

## Application Methods

- Hand-mix bench potting / casting
- Meter-mix bench potting / casting
- Meter-mix vacuum potting / casting

## Transportation / Storage

Store at or below 25°C / 77°F in a dry controlled environment out of direct sunlight. This material should be suitable for use stored under these conditions in the original sealed containers for twelve (12) months from the date of shipment.

Failure to store the product as recommended above may lead to deterioration in product performance.

This product is sensitive to moisture and atmospheric humidity. Containers, once opened, should be used immediately or blanketed with dry air or nitrogen (CONAP® Dri-Purge) before resealing.

Mix and degas individual components thoroughly, prior to use.

## Health / Safety

Refer to the Safety Data Sheet.

See ELANTAS PDG Technical Bulletins *TI-100 - Handling Precautions for Epoxy Resins* and *TI-4005 - Epoxy Reaction Potential Hazards* for additional information.

## Typical Properties of Material as Supplied

Property	Conditions	Value	
		CONAPOXY® FR-1080 Part A Resin	CONAPOXY® FR-1080 Part B Hardener
Viscosity	25°C / 77°F	4,000 cP	300 cP
Specific Gravity	25°C / 77°F	1.03	1.23
Color		amber	dark brown
Mix Ratio	Parts by weight Parts by volume	100 100	83 67
Flash Point	ASTM D93	>94°C >201°F	>94°C >201°F

# CONAPOXY® FR-1080

### Typical Properties of Mixed Materials

Property	Conditions	Value	Units
Viscosity (initial)	25°C / 77°F	2,500	cP
Work Life	25°C / 77°F	>2	hours
Gel Time	100°C / 77°F	1 – 2	hours

### Regulatory Information

RoHS Compliance	CONAPOXY® FR-1080 Part A Resin and CONAPOXY® FR-1080 Part B Hardener comply with Directive 2011/65/EU of the European Parliament and of the Council of 8 June 2011 (RoHS 2.0) as amended 31 March 2015.
-----------------	---

### Application / Curing Schedule

Mix the CONAPOXY® FR-1080 Part A Resin and FR-1080 Part B Hardener in the ratio specified above until homogeneous. Components may be preheated up to 60°C if reduced viscosity is required. If hand-mixing, degas at >27 in. Hg vacuum before use.

Cure 4 - 16 hours at 120°C / 248°F and post cure 2 hours at 180°C / 356°F for maximum properties.

The cure schedules above is based on time after the unit reaches the specified temperature and is a recommendation only. The user is responsible for determining the optimum cure conditions for his application.

### Typical Physical Properties

Property	Test Method	Conditions	Value	Units
Shore Hardness	ASTM D2240	25°C / 77°F	D 90	
Tensile Strength	ASTM D412	25°C / 77°F	8,200	psi
Ultimate Elongation	ASTM D412	25°C / 77°F	2	%
Tear Strength	ASTM D412	25°C / 77°F	250	pli
Flexural Strength	ASTM D790	25°C / 77°F	12,800	psi
Flexural Modulus	ASTM D790	25°C / 77°F	390,000	psi
Compressive Strength	ASTM D695	25°C / 77°F	4,200	psi
Linear Shrinkage	ASTM D2566	25°C / 77°F	1.4	%

# CONAPOXY® FR-1080

## Typical Electrical Properties

Property	Test Method	Conditions	Value	Units
Dielectric Strength	ASTM D149	1/16" - 25°C / 77°F	600	volts / mil
		1/16" - 105°C / 221°F	450	volts / mil
Dielectric Constant	ASTM D150	1 kHz @ 25°C / 77°F	3.1	
		1 kHz @ 105°C / 221°F	3.3	
Dissipation Factor	ASTM D150	1 kHz @ 25°C / 77°F	0.004	
		1 kHz @ 105°C / 221°F	0.004	
Volume Resistivity	ASTM D257	1 kHz @ 25°C / 77°F	$9.7 \times 10^{16}$	ohm-cm
		1 kHz @ 105°C / 221°F	$2.9 \times 10^{14}$	ohm-cm
Surface Resistivity	ASTM D257	1 kHz @ 25°C / 77°F	$5.5 \times 10^{16}$	ohm
		1 kHz @ 105°C / 221°F	$5.7 \times 10^{14}$	ohm

The above properties are typical values and are not intended for specification use.

ELANTAS PDG, Inc. warrants the chemical composition of its products within stated tolerances, but does not guarantee that a product will be appropriate for any particular application. Any recommendation, performance of tests or suggestion is offered merely as a guide and is not a substitute for a thorough evaluation by the user. No representative of ELANTAS PDG, Inc. has the authority to offer a warranty that a product will perform satisfactorily in manufacturing an article and no such representation should be relied upon.

The user may forward, distribute, and/or photocopy this document only if unaltered and complete, and should refrain from any unauthorized use. This document may not be copied to a website without specific authorization from ELANTAS PDG, Inc.