

**Technical Data Sheet**

**Electronic & Engineering Materials**

## **CONATHANE® TU-901**

**Two-Component Polyurethane Tooling Elastomer**

**ELANTAS PDG, Inc.**

1405 Buffalo Street  
Olean, NY 14760  
USA  
Tel +1 716 372-9650  
Fax +1 716 372-1594  
info.elantas.pdg@altana.com  
[www.elantas.com](http://www.elantas.com)

5200 North Second Street  
St. Louis, MO 63147  
USA  
Tel +1 314 621-5700  
Fax +1 314 436-1030  
info.elantas.pdg@altana.com  
[www.elantas.com](http://www.elantas.com)

# CONATHANE® TU-901

## Product Description

CONATHANE® TU-901 is an unfilled, two-component, room temperature curing, 100%-solids polyurethane system.

It consists of CONATHANE® TU-401 Part A Urethane Prepolymer and CONATHANE® TU-901 Curative.

## Areas of Application

Highly recommended for use in potting or casting applications requiring excellent UV stability and elastomeric properties.

Common applications include potting and casting of industrial wheels, metal forming pads, flexible molds, washers, gaskets, bushings and vibration, shock or sound dampening pads.

## Features and Benefits

- Non-MbOCA curing system
- Excellent UV stability
- Excellent physical properties
- Good chemical and solvent resistance

## Application Methods

- Hand-mix Bench Potting / Casting
- Meter-mix Bench Potting / Casting
- Meter-mix Vacuum Potting / Casting

## Transportation / Storage

Store below 25°C / 77°F in a dry controlled environment out of direct sunlight. This material should be suitable for use stored under these conditions in the original sealed containers for twelve (12) months from the date of shipment.

Failure to store the product as recommended above may lead to deterioration in product performance.

This product is sensitive to moisture and atmospheric humidity. Containers, once opened, should be used immediately or blanketed with dry air or nitrogen (CONAP® Dri-Purge) before resealing.

Mix individual components thoroughly before use.

## Health / Safety

Refer to the Safety Data Sheet.

---

## Typical Properties of Material as Supplied

Property	Conditions	Value		Units
		CONATHANE® TU-401 Part A Urethane Prepolymer	CONATHANE® TU-901 Part B Curative	
Viscosity	25°C / 77°F	8,500	450	cP
Specific Gravity	25°C / 77°F	1.04	1.01	
Appearance		Clear Light Amber	Clear Amber	
Mix Ratio	Parts by weight	100	44	
	Parts by volume	100	45	

## CONATHANE® TU-901

### Typical Properties of Mixed Materials

Property	Conditions	Value	Units
Viscosity (initial)	25°C / 77°F	4,000	cP
Work Life	25°C / 77°F	20 – 30	minutes

### Application / Curing Schedule

Mix the TU-401 Part A and TU-901 Part B in the ratio specified above until homogeneous. Components may be preheated up to 60°C if reduced viscosity is required. If hand mixing, degas at >27 in. Hg vacuum before use.

Cure 7 - 21 days at 25°C / 77°F – **or** – 16 hours at 80°C / 176°F

Demold time of 24 hours at 25°C / 77°F – **or** – 2 hours at 80°C / 176°F

The cure schedules above are based on time after the unit reaches the specified temperature and are recommendations only. The user is responsible for determining the optimum cure conditions for his application.

### Typical Mechanical Properties

Property	Test Method	Conditions	Value	Units
Appearance	Visual	25°C / 77°F	light amber	
Shore Hardness	ASTM D2240	25°C / 77°F	A 90	
Tensile Strength	ASTM D412	25°C / 77°F	4,000	psi
		100% modulus	600	psi
		200% modulus	875	psi
		300% modulus	1,000	psi
Ultimate Elongation	ASTM D412	25°C / 77°F	750	%
Graves Tear Strength	ASTM D412	25°C / 77°F	400	pli
Linear Shrinkage	ASTM D2566	25°C / 77°F	<0.5	%
		80°C / 160°F	1.0	%
Flammability	UL94	1/8" thickness	pass V-2	
UV Resistance	ASTM G53	Weatherometer without visual degradation	8000	hours

## CONATHANE® TU-901

### Typical Electrical Properties

Property	Test Method	Conditions	Value	Units
Dielectric Strength	ASTM D149	1/16" @ 25°C / 77°F	580	volts / mil
Dielectric Constant	ASTM D150	100 Hz @ 25°C / 77°F	5.3	
		1 kHz @ 25°C / 77°F	5.1	
		1 MHz @ 25°C / 77°F	4.3	
Dissipation Factor	ASTM D150	100 Hz @ 25°C / 77°F	0.07	
		1 kHz @ 25°C / 77°F	0.02	
		1 MHz @ 25°C / 77°F	0.08	
Arc Resistance	MIL-M-24041C		> 120	seconds
Volume Resistivity	ASTM D257	25°C / 77°F	7.6 x 10 <sup>12</sup>	ohm-cm
Surface Resistivity	ASTM D257	25°C / 77°F	3.5 x 10 <sup>14</sup>	ohms / sq.

The above properties are typical values and are not intended for specification use.

ELANTAS PDG, Inc. warrants the chemical composition of its products within stated tolerances, but does not guarantee that a product will be appropriate for any particular application. Any recommendation, performance of tests or suggestion is offered merely as a guide and is not a substitute for a thorough evaluation by the user. No representative of ELANTAS PDG, Inc. has the authority to offer a warranty that a product will perform satisfactorily in manufacturing an article and no such representation should be relied upon.

The user may forward, distribute, and/or photocopy this document only if unaltered and complete, and should refrain from any unauthorized use. This document may not be copied to a website without specific authorization from ELANTAS PDG, Inc.