

# MOLYKOTE® MI-60 Grease

Synthetic lithium-soap-based grease with solid lubricants

## Features

- Good low-temperature characteristics
- Good plastic compatibility
- Low coefficient of friction
- Contains no silicone oil

## Composition

- Polyalphaolefin
- Lithium soap
- Solid lubricants

## Applications

Special grease for plastic-to-plastic and plastic-to-metal pairings at low to moderate speeds and moderate to high loads (e.g., safety steering wheels).

## How to use

Clean contact points. Apply with brush, spatula, grease gun or automatic lubrication device, as is normally the case with lubricant greases. Can be used in centralized lubrication systems. During long interruptions (e.g., overnight), release pressure from the lubrication system. Do not mix with other greases. Because of the different plastic grades, compatibility tests for swelling and shrinkage, stress cracking, changes in strength and hardness should be carried out.

## Handling precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION.

## Usable life and storage

When stored at or below 20°C in the original unopened containers, this product has a usable life of 36 months from the date of production.

## Typical properties

Specification writers: These values are not intended for use in preparing specifications. Please contact your local MOLYKOTE® sales representative prior to writing specifications on this product.

Standard <sup>(1)</sup>	Test	Unit	Result
	Color		Yellow
<b>Consistency, density, viscosity</b>			
DIN 51 818	Consistency class, NLGI		1-2
ISO 2137	Worked penetration	mm/10	285-315
ISO 2811	Density at 20°C	g/ml	0.9
DIN 51 562	Base oil viscosity at 40°C	mm <sup>2</sup> /s	29
<b>Temperature</b>			
	Service temperature range	°C	-50 to +150
ISO 2176	Drop point	°C	200
ASTM D147880	Low-temperature torque test at -40°C		
	Starting torque	Nm	112x10 <sup>-3</sup>
	Torque after 20 minutes running time	Nm	59x10 <sup>-3</sup>
<b>Load-carrying capacity, wear protection, service life</b>			
	Four-ball tester		
DIN 51 350 pt.4	Weld load	N	4,600
DIN 51 350 pt.5	Wear scar at 400 N load	mm	0.4
<b>Coefficient of friction</b>			
	Steel ball against plastic surface (POM) $\mu$ <sup>(2)</sup>		0.03
<b>Resistance</b>			
DIN 51 808	Oxidation resistance, pressure drop 100 h, 99°C	bar	0.05

<sup>(1)</sup>DIN: Deutsche Industrie Norm. ISO: International Standardization Organization. ASTM: American Society for Testing and Materials.

<sup>(2)</sup>Ø/ball = 12.7 mm, load = 6.3 N, v = 10 mm/s, 24 h.

Continued on next page

## Typical properties (continued)

Standard <sup>(1)</sup>	Test	Unit	Result
<b>Corrosion protection</b>			
DIN 51 802	SKF-Emcor method Degree of corrosion		0
<b>Oil separation</b>			
DIN 51 817	Standard test	%	4.1

<sup>(1)</sup>DIN: Deutsche Industrie Norm. ISO: International Standardization Organization. ASTM: American Society for Testing and Materials.

## Packaging

This product is available in different standard container sizes. Detailed container size information should be obtained from your nearest MOLYKOTE<sup>®</sup> sales office or MOLYKOTE<sup>®</sup> distributor.

*DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.  
© 1998-2019 DuPont.*

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.