

# Fortasun™ PV-8007 Neutral Sealant

High-performance silicone adhesive/sealant with fast green strength

## Features

- Adhesion to typical PV substrates
- Protects against mechanical shock and thermal cycling stress
- Fast green strength
- UL RTI 105°C (221°F)
- UL 94 HB
- UL HAI=1, HWI=1, CTI=0

## Composition

- One-part, neutral alkoxy-cure silicone sealant

## Applications

- Bonding and sealing photovoltaic module components
- Used for frame sealing, junction box bonding and sealing of bus bar connections

## Typical properties

Specification writers: These values are not intended for use in preparing specifications. Please contact DuPont before writing specifications on this product.

CTM <sup>1</sup>	ASTM <sup>2</sup>	Property	Unit	Result
<b>As supplied</b>				
0176		Color		White
		Consistency		Non-slump paste
0364	D2452	Extrusion rate <sup>3</sup>	g/minute	170
		Green strength (1 min.) <sup>4</sup>	Pa	1500
0095		Tack-free time <sup>5</sup>	Minutes	15
<b>Physical properties – cured 7 days at 23°C (75°F) and 50% relative humidity</b>				
0022	D0792	Specific gravity at 23°C (75°F)		1.56
0022	D2240	Durometer hardness, Shore		57
0137A	D412	Tensile strength	MPa	1.5-1.8
0137A	D412	Elongation at break	%	150-200
0137A	D412	Modulus (100%)	MPa	1.2-1.5
0249	D257	Volume resistivity	Ohms/cm	1.0179 x10 <sup>+14</sup>
0114	D149	Dielectric strength	Volts/mm	434.3
			kV/mm	17.1

<sup>1</sup>CTMs (Corporate Test Methods) correspond to standard ASTM tests in most instances. Copies of CTMs are available upon request.

<sup>2</sup>ASTM – American Society for Testing and Materials.

<sup>3</sup>Extrusion rate measured using 3.18mm diameter nozzle at 0.62 MPa

<sup>4</sup>Defined as maximum resistance to constant stress 1 minute after sealant/adhesive application (2mm thick lap shear)

<sup>5</sup>Tack-free time is the time required for the product to develop a non-tacky surface based on adhesion to a polyethylene film.

## Description

Fortasun™ PV-8007 Neutral Sealant is designed to provide longterm sealing and protection against moisture, environmental degradation, mechanical and thermal shock, and vibration where a room-temperature curing product is preferred. It not only seals and protects, but its high elasticity after cure allows flexibility in harsh conditions, suitable for photovoltaic framing and junction box bonding. May also be used for sealing bus bar connections.

## How to use

### Substrate preparation

All surfaces must be clean and dry. Degrease and wash off any contaminants that could impair adhesion. Suitable solvents include isopropyl alcohol, acetone, or methyl ethyl ketone.

Certain plastics may require specific surface treatment to obtain optimum adhesion. Contact DuPont technical support for further information.

### How to apply

Apply a bead of Fortasun™ PV-8007 Neutral Sealant to one of the prepared surfaces, then quickly cover with the other substrate to be bonded.

On exposure to moisture, the freshly applied material will “skin over” in about 10 minutes at room temperature and 50% relative humidity. Any tooling should be completed before this skin forms. The surface is easily tooled with a spatula. Fortasun™ PV-8007 Neutral Sealant will be tack free in about 15 minutes.

### Cure time

After skin formation, cure continues inward from the surface. In 24 hours (at room temperature and 50% relative humidity), Fortasun™ PV-8007 Neutral Sealant will cure to a depth of about 2 mm. Very deep sections, especially when access to atmospheric moisture is restricted, will take longer to cure completely. Cure time is also extended at lower humidity levels. Before handling and packaging bonded components, users are advised to wait a sufficiently long time to ensure that the integrity of the adhesive seal is not affected. This will depend on many factors and should be determined by the user for each specific application.

## Handling precautions

Product safety information required for safe use is not included in this document. Before handling, read product and material safety data sheets and container labels for safe use, physical, and health hazard information. The material safety data sheet is available on [photovoltaics.dupont.com](http://photovoltaics.dupont.com) or from your DuPont representative.

## Usable life and storage

When stored at or below 30°C (86°F) in the original unopened containers, Fortasun™ PV-8007 Neutral Sealant has a usable life of 12 months from the date of manufacture.

Because Fortasun™ PV-8007 Neutral Sealant cures by reaction with moisture in air, keep the container tightly sealed when not in use. A plug of used material may form in the tip of a tube or cartridge during storage. This is easily removed and does not affect the remaining contents. In pails, a skin may form on the surface. This should be removed before placing in dispensing equipment.

## Packaging information

Fortasun™ PV-8007 Neutral Sealant is available in cartridges and pails. For further details, please refer to your DuPont contact.

## Limitations

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

## Health and environmental information

To support Customers in their product safety needs, DuPont has an extensive Product Stewardship organization and a team of Product Safety and Regulatory Compliance (PS&RC) specialists available in each area.

For further information, please see our web site, [photovoltaics.dupont.com](http://photovoltaics.dupont.com) or consult your local DuPont representative.

## Limited warranty information—please read carefully

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

The DuPont sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

DuPont specifically disclaims any other express or implied warranty of fitness for a particular purpose or merchantability.

DuPont disclaims liability for any incidental or consequential damages.

## Materials Matter™



# Fortasun™

Solar Silicones

[photovoltaics.dupont.com](http://photovoltaics.dupont.com)

DuPont™, the DuPont Oval Logo, and all products, unless otherwise noted, denoted with ™, SM or ® are trademarks, service marks or registered trademarks of affiliates of DuPont de Nemours, Inc. ©2019 DuPont de Nemours, Inc. All rights reserved. (06/19) Form. No. 06-1075B-01