



Technical Data Sheet

DOWSIL™ 20 Release Coating

FEATURES & BENEFITS

- Easy to use
- Does not discolor molded parts
- Solvent dilutable
- In most cases, a single application provides release through numerous molding cycles
- Provides heat stable, non-carbonizing, non-oily parting film
- Minimum build-up on molds and dies

COMPOSITION

- Polydimethylsiloxane and high molecular weight silicone resin in solvent

Release coating for plastics, adhesives, and elastomeric products

APPLICATIONS

- In fabricating plastic parts, provides durable parting film for epoxies, melamimes, methacrylates, phenolics, polyesters, and polyurethanes.
- Releases silicone glass laminates and tubes and parts made from silicone molding compounds.
- Provides release for wood forming operations, metal making, and rubber gaskets.

TYPICAL PROPERTIES

Specification Writers: These values are not intended for use in preparing specifications.

Test ¹	Property	Unit	Result
0005	Color		Colorless/ light straw
0208	Active material content	% w/w	50
0001A	Specific gravity @ 77°F (25°C)	g/ml	0.93
0004	Viscosity	cst	11.0
0021A	Flash point – closed cup	°C	32
	Solvent		Stoddard and Xylene
	Suitable solvents		Aliphatic and aromatic hydrocarbons

¹CTM: Corporate Test Method, copies of CTMs are available on request.

DESCRIPTION

DOWSIL™ 20 Release Coating provides a durable parting film which effectively releases plastics, adhesives, and other elastomeric products that are sometimes difficult to release from mold surfaces, even with other silicones.

HOW TO USE

Dilution

For easier application and finer control of the amount applied to mold surfaces, DOWSIL 20 Release Coating should be diluted to one part coating to 5–10 parts solvent. If wetting is a problem, blend 10 parts DOWSIL 20 Release Coating with 80 parts isopropanol (99%) and 10 parts toluene, rather than the previously mentioned solvents. Whenever using solvents, always

provide adequate ventilation and follow the precautions on the manufacturer's label.

To break in molds with porous surfaces, a more concentrated solution – equal parts solvent and DOWSIL 20 Release Coating – may be used. Once the mold has been broken in, a more dilute solution may be used.

Frequency of application and proper concentration for optimum release should be established by small-scale trial runs under actual operating conditions before use in operation.

After dilution, DOWSIL 20 Release Coating can be applied by spraying, brushing, or wiping. Mold surfaces should be cleaned prior to

application. Best parting characteristics are obtained when this product is applied in a very thin film.

Avoid excess.

Thick films do not give good release and may even cause sticking. Difficult release may also result from uneven dispersion or failure to wet surfaces completely. This may be corrected by rubbing out the release material until a thin, dry film is obtained.

After application, allow the mold surface to dry until completely free of diluent. Because the solvents used to dilute DOWSIL 20 Release Coating may be flammable, special care must be taken when applying the dilution to hot surfaces.

Cure

Although not essential, a heat cure produces better release and increased durability of the parting film. Heating the molds for 5–10 minutes at 93–204°C (200–400°F) is suggested.

Finishing Molded Parts

The silicone release film formed by DOWSIL 20 Release Coating may, in some cases, interfere with the painting and bonding of molded parts. If a finish coat or bonding is involved, the effect of a silicone release agent should be thoroughly tested before use.

Should painting or bonding of molded parts be an issue, Dow offers release agents that are compatible with many organic coatings and adhesive systems. These alternative release products provide good release and offer the advantage that residual film transferred to the molded part can be removed from the molded part without requiring extraordinary cleaning procedures prior to painting or bonding. Information about these Dow release materials is available upon request.

HANDLING PRECAUTIONS

DOWSIL 20 Release Coating is supplied in a flammable solvent. Avoid heat, sparks, and open flame. Always provide adequate ventilation.

**PRODUCT SAFETY
INFORMATION REQUIRED FOR
SAFE USE IS NOT INCLUDED IN
THIS DOCUMENT. BEFORE
HANDLING, READ PRODUCT
AND SAFETY DATA SHEETS
AND CONTAINER LABELS FOR
SAFE USE, PHYSICAL AND
HEALTH HAZARD
INFORMATION. THE SAFETY
DATA SHEET IS AVAILABLE ON
THE DOW WEBSITE AT
WWW.CONSUMER.DOW.COM,
OR FROM YOUR DOW SALES
APPLICATION ENGINEER, OR
DISTRIBUTOR, OR BY CALLING
DOW CUSTOMER SERVICE.**

USABLE LIFE AND STORAGE

When stored at or below 30°C (86°F) in the original unopened containers, this product has a usable life of 24 months from the date of production. This product is classed as a flammable, with a flash point of 32°C (89.6°F). Handle and store with appropriate precautions.

PACKAGING INFORMATION

This product is available in 20 kg and 170 kg containers, net weight.

Samples are available in 500 ml containers, net weight.

LIMITATIONS

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

HEALTH AND ENVIRONMENTAL INFORMATION

To support customers in their product safety needs, Dow has an extensive Product Stewardship organization and a team of product safety and regulatory compliance specialists available in each area.

For further information, please see our website, www.consumer.dow.com or consult your local Dow representative.

LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

**TO THE FULLEST EXTENT
PERMITTED BY APPLICABLE
LAW, DOW SPECIFICALLY
DISCLAIMS ANY OTHER
EXPRESS OR IMPLIED
WARRANTY OF FITNESS FOR A
PARTICULAR PURPOSE OR
MERCHANTABILITY.**

**DOW DISCLAIMS LIABILITY
FOR ANY INCIDENTAL OR
CONSEQUENTIAL DAMAGES.**

www.consumer.dow.com



®Trademark of The Dow Chemical Company

UNRESTRICTED – May be shared with anyone

®™Trademark of The Dow Chemical Company ("Dow") or an affiliated company of Dow

DOWSIL™ 20 Release Coating

© 2017 The Dow Chemical Company. All rights reserved.