

LOCTITE STYCAST ES 4512

December 2016

PRODUCT DESCRIPTION

LOCTITE STYCAST ES 4512 provides the following product characteristics:

Technology	Epoxy
Appearance, Resin (Component A)	Black
Appearance, Hardener (Component B)	Tan
Appearance (cured)	Black
Components	Two components - requires mixing
Mix Ratio, by volume - Part A: Part B	100 : 106
Mixing Ratio, by weight Component A: Component B	100 : 100
Cure	Room temperature cure
Application	Potting and Encapsulating

LOCTITE STYCAST ES 4512 is a two-component casting system with excellent handling properties. This low cost, flexible system is filled with a non-abrasive filler for machine metering/dispensing or regular hand mixer applications.

UL Classification

Classified by Underwriters Laboratories Inc.[®] UL-94 "Test for Flammability of Plastic Materials" and meets the requirements of 94VO in a 1.8 mm cross section.

TYPICAL PROPERTIES OF UNCURED MATERIAL**Part A Properties**

Density, @ 25 °C, g/cm ³	1.57
Filler Content, %	50
Solids Content, %	100
Viscosity, Brookfield - RVF, 25 °C, mPa·s (cP):	
Spindle 6, speed 2 rpm	55,000
Spindle 6, speed 20 rpm	28,000

Part B Properties

Density, @ 25 °C, g/cm ³	1.48
Filler Content, %	60
Solids Content, %	100
Viscosity, Brookfield - RVF, 25 °C, mPa·s (cP):	
Spindle 5, speed 20 rpm	6,300

Mixed Properties

Density, @ 25 °C, g/cm ³	1.55
Peak Exotherm Temperature, °C:	
200 g mass	90
Pot Life @ 25 °C, minutes:	
200 g mass	60
Gel Time @ 25 °C, hours	5
Viscosity @ 25 °C, mPa·s (cP)	19,000

TYPICAL CURING PERFORMANCE Recommended Curing Conditions

36 to 48 hours @ 25 °C (Recommended cure)
3 hours @ 60°C (Alternate cure)

TYPICAL PROPERTIES OF CURED MATERIAL**Physical Properties :**

Glass Transition Temperature, ISO 11357-2, °C	50
Coefficient of Thermal Expansion ASTM D7012, K ⁻¹ :	
Pre Tg (Alpha 1)	66×10 ⁻⁶
Post Tg (Alpha 2)	150×10 ⁻⁶
Coefficient of Thermal Conductivity, ISO 8302, W/(m-K)	0.644
Linear Shrinkage, ASTM D792, %	0.1
Shore Hardness, ISO 868, Durometer D	88
Water Absorption, ISO 62, %:	
24 hours in water @ 25 °C	0.32
Elongation , ISO 527-2,%	6.3

Tensile Strength Tests - Hysol:

Tensile Strength, ISO 527-2	N/mm ² 18.4 (psi) (2,670)
Compressive Strength, ISO 604	N/mm ² 80.7 (psi) (11,700)
Flexural Strength, ISO 178	N/mm ² 34.3 (psi) (4,975)
Tear Strength, ISO 34-2, Die D	N/mm 42.0 (lb./in.) (240)

Electrical Properties:

Dielectric Breakdown Strength IEC 60243-1, kV/mm	44.7
Volume Resistivity, IEC 60093, Ω·cm:	
@ 25 °C	5.9×10 ¹⁴
@ 105 °C	2.8×10 ¹⁰
Surface Resistivity, IEC 60093, Ω:	
@ 25 °C	3.0×10 ¹⁵
@ 105 °C	1.8×10 ¹⁵
Dielectric Constant / Dissipation Factor, IEC 60250:	
@ 25 °C:	
100 Hz	4.6 / 0.038
1 kHz	4.4 / 0.03
10 kHz	4.3 / 0.026
100 kHz	4.1 / 0.023
@ 105 °C:	
100 Hz	35.7 / 1.43
1 kHz	9.2 / 0.5
10 kHz	7.8 / 0.1
100 kHz	7.2 / 0.08

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

STORAGE:

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Liquid Storage - Liquids should be stored at 25°C or below, in closed containers. If stored below 25°C, the material MUST be allowed to come to room temperature, in the sealed container, to avoid moisture contamination.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

(°C x 1.8) + 32 = °F
 kV/mm x 25.4 = V/mil
 mm / 25.4 = inches
 N x 0.225 = lb
 N/mm x 5.71 = lb/in
 psi x 145 = N/mm²
 MPa = N/mm²
 N·m x 8.851 = lb·in
 N·m x 0.738 = lb·ft
 N·mm x 0.142 = oz·in
 mPa·s = cP

Reference 1

Disclaimer**Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling

and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage: [Except as otherwise noted] All trademarks in this document are trademarks and/or registered trademarks of Henkel and its affiliates in the U.S. and elsewhere.