

# MOLYKOTE® G-0010

## Multipurpose Bearing Grease

Multipurpose polyurea-thickened bearing grease

### Features

- Wide temperature range
- Extreme-pressure lubrication
- Excellent corrosion-preventive properties
- Shear-resistant

### Composition

- Modern polyurea thickener
- Mineral base oil
- Corrosion inhibitor

### Applications

Electrical motors, fan bearings, water pump bearings, and dryers in chemical and paper industries.

### Description

MOLYKOTE® G-0010 Multipurpose Bearing Grease is a mineral-oil-based grease thickened by a di-urea system. MOLYKOTE® G-0010 Grease offers excellent low-temperature properties and load-carrying characteristics. MOLYKOTE® G-0010 Grease provides premium rust prevention and, due to its polyurea thickener, superior shear and oxidation stability.

### How to use

Apply using conventional grease application methods (i.e., clean brush, grease gun and manual or automated dispensing equipment).

### Handling precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION.

### Usable life and storage

When stored between 0 and 40°C in the original unopened containers, this product has a usable life of 60 months from the date of production.

### Typical properties

Specification writers: These values are not intended for use in preparing specifications. Please contact your local MOLYKOTE® sales representative prior to writing specifications on this product.

Standard	Test	Unit	Result
	Color		Green
	Base oil type		Mineral oil
	Thickener type		Polyurea
<b>Consistency, viscosity</b>			
ASTM D217	Consistency	NLGI Class	2
	Worked penetration	mm/10	265-295
ASTM D445	Base oil viscosity @ 40°C	mm <sup>2</sup> /s	125
<b>Temperature</b>			
	Service temperature range (est.)	°C	-30 to +170
		°F	-20 to +340
ASTM D2265	Dropping point	°C (°F)	> 260 (> 525)
<b>Oil separation/evaporation</b>			
FTMS 791C-321.2	Oil separation (24 hrs/ 100°C)	mass-%	2.3
	Evaporation loss (24 hrs/ 100°C)	mass-%	0.1
<b>Load-carrying capacity, wear protection, speed</b>			
ASTM D2596	Four ball tester weld load	kg	315
ASTM D2266	Wear scar under (40 kg; 75°C; 1 hr)	mm	0.60
	Dn value (D <sub>R</sub> x rpm; estimated)	M	400
ASTM D1743	Corrosion prevention		1, 1, 1 Pass

<sup>(1)</sup>ASTM: American Society for Testing and Materials. FTMS: Federal Test Methods.

## Packaging

This product is available in 400 g cartridges, 16 kg pails, and 180 kg drums.

*DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.  
© 2003-2019 DuPont.*

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.