

### Approvals and conformities

<i>Ball Aerospace &amp; Technologies</i>	<i>BMS29.98</i>
<i>BOEING</i>	<i>52841092, 9M03235/AttachA, BMS10-90, D290-75502-22C, MB0125-080, SCGMS56016, STM0724</i>
<i>Cincinatti Electronics</i>	<i>635907-1</i>
<i>CYTEC SOLVEY</i>	<i>LMS 11953</i>
<i>HONEYWELL</i>	<i>P8251333</i>
<i>ILC Dover</i>	<i>ST41P1218</i>
<i>ITT, Space Systems</i>	<i>561454</i>
<i>LOCKHEED MARTIN</i>	<i>LAC-37-4462-002, MAP-CK10787-1000, STM40601</i>
<i>NORTHROP GRUMMAN</i>	<i>53825TW</i>
<i>Raytheon</i>	<i>HMS15-2135</i>
<i>Rockwell Collins</i>	<i>KB0125005</i>

Aeroglaze® A276 coating is a reflective, moisture-curing polyurethane coating designed for product finishing applications on substrates used in aircraft and aerospace applications. Aeroglaze A276 coating cures to a high gloss white finish.

### Features & Benefits

- **Low Outgassing:** exhibits low gassing properties in high vacuum environments.
- **Chemically Resistant:** cures to a hard surface that is resistant to most acids, alkaline detergents, lubricants and chemicals.
- **Color Retention:** provides excellent colorfast, non-chalking finish.

## DIRECTIONS FOR USE

### Surface Preparation

Thoroughly clean surfaces to remove all dust, oil and grease. For most substrates, apply primer to ensure proper adhesion and performance of the coating. Contact your SOCOMORE representative for recommended Aeroglaze primer required for your application.

### Application

Apply coating by spray methods, or by brush to small areas. Aeroglaze A276 coating is best applied at 13-35°C (55-95°F), with substrate temperatures at least 2.8°C (5°F) above the dew point.

#### • Spraying

Apply coating using HVLP spray equipment. Dilute coating with 10-25% Aeroglaze 9958 thinner, by volume. Hold the gun at right angles to the surface, approximately 20.3-30.5 cm (8-12 in) away, and apply with a 50% overlap.

#### • Brushing

If necessary, use a brush to touch-up small areas. Add up to 5% of Aeroglaze 9958 thinner to facilitate

application properties.

Depending on surface characteristics, the optimum dry film thickness of Aeroglaze A276 coating should be 38.1-50.8 micron (1.5-2.0 mil). Wet film thicknesses above 127 micron (5 mil) can cause bubbling and sagging. Coverage rate is 7.4-9.8 m<sup>2</sup>/L (300-400 ft<sup>2</sup>/gal).

### Curing

Aeroglaze A276 coating cures by reacting with moisture in the air. Cure rate is dependent on the temperature, relative humidity and amount of air circulation needed to remove the solvent.

Under the acceptable curing conditions, the coating will develop its ultimate properties in approximately 14 days. Lower temperatures and humidities will retard cure, while higher temperatures and humidities may cause bubbling.

Aeroglaze A276 coating may be recoated after the first application within 4 hours minimum and 24 hours maximum. Recoat time is dependent on temperature and humidity. High temperature and humidity promote fast cure while low temperature and humidity slow down the cure. In high temperature and high humidity conditions, recoat within 8 hours to prevent intercoat adhesion failure.

If the maximum recoat time is exceeded, the surface must be roughened by sanding with fine sandpaper before recoating.

### Cleanup

Use Aeroglaze 9958 thinner to clean equipment. Do not use lacquer thinners, water or solvents containing alcohols.

## TECHNICAL CHARACTERISTICS

### Typical Properties\*

Property	Value
Appearance	White Liquid
Viscosity, cps @ 25°C (77°F), ASTM D 2196-86, Brookfield LVT	100-400
Density, ASTM D 1475-85	1.12-1.17 kg/L (9.37-9.77 lb/gal)
Solids Content by Weight, ASTM D 2369-87 modified	54-58%
Flash Point (Seta), ASTM D 3278-82, Closed Cup	19°C (67°F)
Volatile Organic Content (VOC) ASTM D 3960-87	503 g/L (4.2 lb/gal)
Outgassing** ASTM E 595-77	0.99% TML***, 0.08% CVCM****
Solar Absorptivity, Gier-Dunkle Integrating Sphere	0.23

\* Data is typical and not to be used for specification purposes.

\*\* 15 day cure at room temperature, 24 hours at 50°C (122°F).

\*\*\* Total Mass Loss

\*\*\*\* Collected Volatile Condensable Materials

## PRECAUTIONS FOR USE AND STORAGE

Shelf life is one year from date of shipment when stored in original, unopened container. Store indoors away from heat, sparks and open flames. To maintain product freshness, keep container closed when not in use and nitrogen purge after opening if possible.

Before using this or any SOCOMORE product, refer to the Safety Data Sheet (SDS) and label for safe use

and handling instructions.

For industrial/commercial use only. Must be applied by trained personnel only. Not to be used in household applications. Not for consumer use.

**Limitations**

- Not for immersion service. Do not apply to wet or damp substrates.
- Aeroglaze A276 coating contains aliphatic isocyanate monomer. Spray only in properly ventilated areas with specified respiratory protection.

Manufactured for SOCOMORE by: LORD Corporation, Saegertown, PA

**This technical data sheet replaces and cancels the previous one.**

The above details have been compiled to the best of our knowledge. They have, however, an indicative value only and we therefore make no warranties and assume no liability in connection with any use of this information, particularly if a third party's rights are affected by the use of our products. The above information has been compiled based upon tests carried out by BABBCO. All data is subject to change as Socomore deems appropriate. The data given is not intended to substitute for any testing you must conduct in order to determine the suitability of the product for your particular purposes. Please check your local legislation applicable to the use of this product. Should you need any further information please contact us.