

# MOLYKOTE® G-1067 Grease

Synthetic grease designed for automotive components

## Features & benefits

- Wide temperature range (-50°C to 120°C)
- Compatible with most plastics
- Good lubricant for GFRP (glass-fiber-reinforced plastics)

## Composition

- Polyalphaolefin
- Lithium soap
- White solid lubricants

## Applications

Automotive rail parts, lubrication of glass-fiber-reinforced plastic parts.

## Description

MOLYKOTE® G-1067 Grease is a polyalphaolefin grease designed for automotive body and plastic components.

## How to use

Apply using conventional grease application methods (i.e., clean brush and manual or automated dispensing equipment).

## Handling precautions

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION.

## Usable life and storage

When stored closed below 40°C in original containers, this product has a usable life of 36 months from the date of production.

## Packaging

Detailed container size information should be obtained from your nearest MOLYKOTE® sales office or MOLYKOTE® distributor.

## Typical properties

Specification writers: These values are not intended for use in preparing specifications. Please contact your local MOLYKOTE® sales representative prior to writing specifications on this product.

Standard <sup>(1)</sup>	Test	Unit	Result
	Appearance		White
JIS K 2220	Penetration (worked 60 strokes)		342
	Temperature range	°C	-50 to 120
JIS K 2220	Bleed (24 hrs, 100°C)	%	0.0
JIS K 2220	Evaporation (22 hrs, 99°C)	%	0.1
JIS K 2220	Dropping point	°C	210
JIS K 2220	Copper corrosion test (24 hrs, 100°C)		1a
ASTM D2266	4 ball test, wear scar (1,200 rpm, 392 N, 1 hr)	mm	0.67
JIS K 2220	Low-temperature torque		
	(-40°C) Starting torque	mN*m	46
	Running torque	mN*m	22

<sup>(1)</sup>JIS: Japanese Industrial Standard. ASTM: American Society for Testing and Materials.

## Friction test

Test machine: Oscillating friction tester

Test parts: 30% glass fiber contained PA66 roller



Hot dip galvanizing steel plate

Load: 0.2 kg

Stroke: 40 mm

Speed: 30 cpm

Grease: 0.01 g



DuPont™, the DuPont Oval Logo, and all trademarks and service marks denoted with ™, SM or ® are owned by affiliates of DuPont de Nemours, Inc. unless otherwise noted.  
© 2013-2019 DuPont.

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.