

Product Information

Silicone Sealant

DOW CORNING

Dow Corning® HM-2510 Assembly Sealant

FEATURES & BENEFITS

- Instant Green Strength
- 100% Silicone
- Low VOC (exempt in California)
- Safe to handle – nonhazardous composition and by-products
- Neutral Cure
- Adheres to most common substrates
- Open time up to 15 minutes
- Pot life up to 24 hours
- Excellent clarity
- Service temperatures from -58 to 300°F (-50 to 150°C)
- Can be used with standard hot melt dispensing equipment
- Immediate green strength allows parts to be moved immediately
- Long open time, long pot life and moderate application temperature (250°F [121°C]) offer a user friendly application
- High viscosity at room temperature resists flow of material reducing sealant squeeze out and clean up

COMPOSITION

- Moisture curing, 100 percent silicone, reactive hot-melt sealant

Hot melt silicone assembly sealant

APPLICATIONS

- *Dow Corning*® HM-2510 Assembly Sealant is designed for use as an assembly sealant. This product utilizes hot melt technology to dispense the material which utilizes silicone technology to achieve instant green strength when dispensed and cures to strong moisture cured silicone sealant.

TYPICAL PROPERTIES

Specification Writers: These values are not intended for use in preparing specifications. Please contact your local Dow Corning sales office or your Global Dow Corning Connection before writing specifications on this product.

Test*	Property	Unit	Result
CTM 0719	Viscosity at 248°F (120°C)	Poise	1100
CTM 0086	Nonvolatile Content	Percent	>98.5
CTM 0243	Open Time	Minutes	15
CTM 0243	Green Strength at 15 minutes	Psi	6
CTM 0243	Green Strength at 60 minutes	Psi	7
CTM 1345	Cure Time, 1/8" bead	Days	2
CTM 0099	Durometer – Shore A	Points	38
ASTM D412	Tensile Strength	Psi	670
ASTM D412	Elongation	Percent	1900
ASTM D412	Modulus at 50% Elongation	Psi	80
CTM 0044	Specific Gravity, uncured		1.07
CTM 0176	Appearance		Water Clear
ASTM C711	Service Temperature Range	°F (°C)	-58 to 300 (-50 to 150)
ASTM D4498	Heat- Fail Temp in Shear	°F (°C)	482 (250)

*CTM: Corporate Test Method, copies of CTM's are available on request.

ASTM: American Society for Testing and Materials

DESCRIPTION

Dow Corning® HM-2510 Assembly Sealant is a 100 percent silicone, neutral cure sealant formulated to have immediate green strength which offers assembly improvements and uses in other production applications. Products made with this can be immediately handled.

As a viscoelastic material, when cured and then exposed to high temperatures this product will soften but recovers to its typical properties when cooled down.

LISTINGS/ SPECIFICATIONS

FDA Regulations 21 CFR 177.2600 for aqueous applications.

National Sanitation Foundation list 61 for use with potable water.

National Sanitation Foundation list 51 food and equipment materials for aqueous and dry solids.

Recognized under UL QMFZ2.

**HANDLING
PRECAUTIONS
PRODUCT SAFETY
INFORMATION REQUIRED FOR
SAFE USE IS NOT INCLUDED IN
THIS DOCUMENT. BEFORE
HANDLING, READ PRODUCT
AND SAFETY DATA SHEETS
AND CONTAINER LABELS FOR
SAFE USE, PHYSICAL AND
HEALTH HAZARD
INFORMATION. THE SAFETY
DATA SHEET IS AVAILABLE ON
THE DOW CORNING WEBSITE
AT DOWCORNING.COM, OR
FROM YOUR DOW CORNING
SALES APPLICATION
ENGINEER, OR DISTRIBUTOR,
OR BY CALLING
DOW CORNING CUSTOMER
SERVICE.**

USABLE LIFE AND STORAGE

Dow Corning HM-2510 Assembly Sealant has a shelf life of 12 months from date of manufacture when stored in original, unopened containers in a clean and dry environment below 90°F (32°C).

LIMITATIONS

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

HEALTH AND ENVIRONMENTAL INFORMATION

To support customers in their product safety needs, Dow Corning has an extensive Product Stewardship organization and a team of Product Safety and Regulatory Compliance (PS&RC) specialists available in each area.

For further information, please see our website, dowcorning.com or consult your local Dow Corning representative.

LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow Corning's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

**TO THE FULLEST EXTENT
PERMITTED BY APPLICABLE
LAW, DOW CORNING
SPECIFICALLY DISCLAIMS
ANY OTHER EXPRESS OR
IMPLIED WARRANTY OF
FITNESS FOR A PARTICULAR
PURPOSE OR
MERCHANTABILITY.**

DOW CORNING DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.

We help you invent the future.™

dowcorning.com