



AI TECHNOLOGY INC
 70 Washington Road
 Princeton Jct., NJ 08550
 (609) 799-9388 fax (609) 799-9308
 E-Mail: ait@aitechnology.com
 Internet: <http://www.aitechnology.com>

**COOL-GREASE
 CGR8010-XT**

**Non Curing
 Electrically Conductive
 Interfacial Compound**

IDEAL FOR:

- EMI Seal
- Thermal Interface
- Electrical Interface

DESCRIPTION:

CGR8010-XT is a silver filled, ULTRA-HIGH thermally conductive paste. The non-curing nature of this electro-conductive thermal grease makes it ideal as an interfacial compound for extreme thermal and electrical transfer for power devices. It is non-silicone based for long-term non-drying applications.

TYPICAL PROPERTIES*

Electrical Resistivity	<5x10 ⁻² ohm-cm
Tensile Elongation (%)	N/A
Current Carrying Capability	> 10 Amp/mm ²
Cured Density (gm/cc)	5.0**
Thermal Conductivity	>90 Btu-in/hr-ft ² -°F >12.9 W/m-°C
Linear Thermal Expansion Coeff. (ppm/°C)	Non-curing
Maximum Continuous Operation Temp. (°C)	150
Avg. Viscosity(0.5 rpm, 25°C) (Brookfield DV-1, Spindel CP51)	117,000 cp

* Properties given are typical values and not intended for use in preparing specifications. The user is advised to evaluate the product in the manner the product is intended to be used in manufacturing and in the final product.

CURE SCHEDULES:

<u>Temperature</u>	<u>Time</u>
**Non-Curing	

AVAILABILITY:

CGR8010-XT is available in syringes for automatic needle dispense applications or in jars.

APPLICATION PROCEDURES:

(1) Dispense adhesive onto clean substrate.

SHELF LIFE:

<u>Storage temperature</u>	<u>Shelf Life</u>
25°C	1 yr

The information contained herein is believed to be reliable. All recommendations or suggestions are made without guarantee inasmuch as conditions and methods of commercial use are beyond our control. Properties given are typical values and not intended for use in preparing specifications. The user is advised to evaluate the product in the manner the product is to be used in manufacturing and in the final product. Under no circumstance shall A.I. Technology be liable for accidental, consequential or other damages arising from the use or handling of this product.

While AI Technology owns all proprietary rights of material formulations of its products, specific usage in the manufacturing of certain products may involve patent rights of other companies.