



## 2008

2008 is a single-component low-viscosity cyanoacrylate adhesive. It is extremely fast setting and specifically formulated for all types of rubber bonding applications. 2008 is also appropriate for use in medical device assemblies, and is certified to ISO biocompatibility standards 10993-5, 10993-10 and 10993-11.

<b>Technology / Base</b>	Ethyl
<b>Type of Product</b>	Cyanoacrylate
<b>Components</b>	One Component
<b>Curing</b>	Humidity
<b>Appearance / Color</b>	Clear
<b>Consistency</b>	Wicking Liquid

### Technical Data

Rheology	Value	Condition/Method
Viscosity	15 +/- 5 cPs	Brookfield SC4-21, 20°C to 25°C (68°F to 77°F)
<b>Density</b>		
Specific Gravity	1.06	
<b>Uncured Material Characteristics</b>		
Flash Point	85°C (185°F)	
Set Time	Steel ABS EPDM	25 sec 3 sec 2 sec
Shelf Life		12 mo
<b>Cured Material Characteristics</b>		
Full Cure Time		24 hours
Cure Appearance		Clear
Service Temperature		-55 to 95°C
RoHS Compliant		yes
<b>Cured Mechanical Properties</b>	See Graphs and Table Below	

### General Instructions

Surfaces to be bonded should be clean and dry. Dispense a drop or drops to one surface only. Apply only enough to leave a thin film layer after compression. Press parts together and hold firmly for a few seconds. Good contact is essential. An adequate bond develops in less than one minute and maximum strength is attained in 24 hours. Wipe off excess adhesive from the top of the container and recap. Products if left uncapped may deteriorate by contamination from moisture in the air. Because products cure by polymerization, whitening may appear on the surface of the container or the bonded materials. This will not affect adhesive performance.

### Curing Performance

Ambient surface moisture initiates the curing process. Handling strength is reached in a short time, and will vary based on environmental conditions, bond line gap, and other factors. Product will continue to cure for at least 24 hours before full strength and solvent resistance is developed.

### Storage


Containers should be stored in a cool, dry, dark area. Storage temperature 15.5°C - 25°C (60°F - 77°F), without exposure to direct light or heat. Do not refrigerate.

### Specifications and Approvals

10993-5, 10993-10, 10993-11

Mil-A-46050C, Type II Class I, A-A-3097, Type II Class 1

### Time Until Full Cure (% of RT strength)




### Safety & Disposal

For safe handling information and disposal instructions on this product, consult the Safety Data Sheet (SDS)



**Performance Range by Substrate (N/mm<sup>2</sup>)**



**Performance of Cured Adhesive**


Substrate	N/mm <sup>2</sup>	PSI
Steel	13.8 to 18.8	2000 to 2730
Rubber*	5.1 to 15.2	735 to 2200
AL	3.1 to 3.5	450 to 510
PC**	22.3 to 24.9	3240 to 3605
PVC**	18.3 to 26.7	2660 to 3875
ABS**	12.0 to 18.3	1740 to 2660

\*Rubber figures given are typical. Your results may vary by specific rubber type.

\*\*Tested to ASTM 4501

\*\*\*n/r = not recommended


**Heat Aging (aged at temp indicated and tested @ 22°C)**



**Solvent Resistance**

Solvent	Example	Resistance
Alcohol	Ethanol, Methanol	+++
Ester (aromatic)	Ethylacetate	+++
Ketone (aromat)	Acetone, Benzophenone	---
Aliphatic hydrocarbon	Petrol, Heptanes, Hexane	++-
Aromatic hydrocarbons	Benzyl, Toluol, Xylol	++-
Halogenated hydrocarbons	Methylenchloride, Chloroform, Chlorobenzol	---
Weak aqueous	Nitrite, muriatic acid, sulphuric acid, phosphoric acid	+++ (--- if concentrated)
Weak aqueous base	sodium hydroxide solution, caustic potash	+++ (--- if concentrated)

**Hot Strength (%RT strength, tested at temperature)**



Date Modified: 13 March 2017

H.B. Fuller Company  
 9001 W. Fey Drive  
 Frankfort, IL 60423  
 +1.800.552.0299  
[www.hbfuller.com](http://www.hbfuller.com)

Connecting what matters.™

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience, and we believe this information to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

® and ™ are trademarks of H.B. Fuller Company or one of its affiliated entities.



**NOTE TO USER:** by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

H.B. Fuller  
[www.hbfuller.com](http://www.hbfuller.com)