

Liquid Optical Clear Adhesive (LOCA)

PRODUCT DESCRIPTION

Devcon® Tru-Bond™ LOCA products are high clarity, fast curing, UV light curing products. They are engineered to eliminate the air gap between the cover lens of touch panels and display devices. These liquid dispensed, ultra-low hardness products help reduce stresses that contribute to Mura while helping to increase the impact resistance and durability of the assembly.

PHYSICAL PROPERTIES (uncured)

Chemical Class	Acrylic
Appearance(uncured)	Clear Liquid
Components	Single-Requires no Mixing
Viscosity @25°C, Brookfield RV Spindle 4, 10 rpm, cps	5,000
Specific gravity @25°C	0.96

After 500 hours @ 85°C/85% RH

L*	>99
a*	-0.18
b*	0.44
Transmission @550nm, ASTM D1003, %	>99.5
Haze, ASTM D1003, %	<0.4

PHYSICAL PROPERTIES (cured)

Curing condition: LED 365 lamp, illumination intensity=150 mW/cm², total energy=1500 mJ/cm².

Shore hardness, ASTM D2240	3500
Specific gravity @25°C	0.99
Volume shrinkage, %	2.33
Refractive Index @ 25°C, ISO 489	1.46
Tg, °C	-61
Elongation, ASTM D638, %	600
Tensile strength, ASTM D638, MPa	0.1
Dielectric constant @ 1MHz	5.5
Storage modulus @25°C, KPa	12

After 500 hours @ 85°C

L*	>99
a*	-0.16
b*	0.46
Transmission @550nm, ASTM D1003, %	>99.5
Haze, ASTM D1003, %	<0.4

After 500 cycles @ -40°C (30min) to 85°C (30min)

L*	>99
a*	-0.08
b*	0.16
Transmission @550nm, ASTM D1003, %	>99.5
Haze, ASTM D1003, %	<0.4

OPTICAL PROPERTIES OF CURED MATERIALS

Optical testing specimen: 0.1 mm thick layer adhesive

between 2 pcs 1 mm thick panel glass

Curing condition: LED 365 lamp, illumination

intensity=150 mW/cm², total energy=1500 mJ/cm²

Equipment: Konica Minolta CA3600

L* a* b*, ASTM E308

L*	>99
a*	-0.06
b*	0.15
Transmission @550nm, ASTM D1003, %	>99.5
Haze, ASTM D1003, %	<0.4

After 500 hours exposure to 0.89 W/m² UV light @ 50°C

L*	>99
a*	-0.08
b*	0.63
Transmission @550nm, ASTM D1003, %	>99.5
Haze, ASTM D1003, %	<0.4

MECHANICAL PROPERTIES OF CURED MATERIALS

Cross bonding tensile test can show the bonding strength on the vertical direction. The specimen is 0.15 mm thick 6 mm diameter layer adhesive between 2 pcs 25.4*76.2*1 mm panel glass. The 2 pcs panel glass were cross bonded together. The specimens were cured on LED 365 lamp, with 150 mW/cm² illumination intensity and 1500 mJ/cm² total energy.

Cross bond tensile strength

N/mm ²	0.14
psi	20.3



Tru-Bond™ LOCA 5000

UV/Visible Light Cure Adhesive

Technical Data Sheet

Rev02, Oct 2016
Preliminary

PRECAUTIONS

Please refer to the appropriate material safety data sheet (MSDS) prior to using this product.

STORAGE

Store the unopened product in a cool, dry, well ventilated location away from sources of heat. Optimal storage temperatures should range between **10 °C (50 °F) and 32 °C (90 °F)**. **Do not expose the product to light.** It may polymerize upon prolonged exposure to ambient or artificial light. Product removed from the containers during use should not be returned to original containers in order to avoid potential contamination.

CONVERSIONS

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$

$\text{kV/mm} \times 25.4 = \text{V/mil}$

$\text{mm} / 25.4 = \text{inches}$

$\mu\text{m} / 25.4 = \text{mil}$

$\text{N} \times 0.225 = \text{lb}$

$\text{N/mm} \times 5.71 = \text{lb/in}$

$\text{N/mm}^2 \times 145 = \text{psi}$

$\text{MPa} \times 145 = \text{psi}$

$\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$

$\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$

$\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$

$\text{mPa}\cdot\text{s} = \text{Cp}$

WARRANTY

ITW will replace any material found to be defective. Because the storage, handling and application of this material are beyond our control, we can accept no liability for the results obtained.

NOTE

The following supersedes any provision in your company's forms, letters and papers. ITW makes NO WARRANTY, WHETHER EXPRESSED OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE FOR THIS PRODUCT. No statements or recommendations contained in the product literature are to be construed as inducements to infringe any relevant patent, now or thereafter in existence. UNDER NO CIRCUMSTANCES SHALL ITW BE LIABLE FOR INCIDENTAL, CONSEQUENTIAL OR OTHER DAMAGES FROM ALLEGED NEGLIGENCE BREACH OF WARRANTY, STRICT LIABILITY OR ANY OTHER THEORY, ARISING OUT OF THE USE OR HANDLING OF THIS PRODUCT. The sole liability of ITW for any claims arising out of the manufacture, use or sale of its products shall be to refund the buyer's purchase price, provided such products have been demonstrated in ITW sole opinion, to justify such refund.

For technical assistance, please call:

North America	1-800-933-8266
China	86-21-54265119
Japan	81-6-6330-7118
Korea	82-2-2088-3560
India	91-8455-224705
Europe	44 (0)1933 354 550

FOR INDUSTRIAL USE ONLY

