

LOCTITE[®] IS Resinol[™] AT[™]

Known as LOCTITE[®] Resinol[™] AT[™]
October 2016

PRODUCT DESCRIPTION

LOCTITE[®] IS Resinol[™] AT[™] provides the following product characteristics:

Technology	Acrylic
Chemical Type	Methacrylate monomers
Appearance (uncured)	Colorless to pale yellow liquid ^{LMS}
Fluorescence	Positive under UV light ^{LMS}
Emulsification	Homogeneous milky white dispersion ^{LMS}
Components	One component - requires no mixing
Viscosity	Low
Cure	Room temperature cure
Application	Sealing

LOCTITE[®] IS Resinol[™] AT[™] is a low viscosity liquid sealant designed for sealing porosity in metal castings and powder metal parts. It may also be used to seal microscopic voids in other materials. This product is typically applied with a vacuum impregnation process that removes air from the pores and then fills the pores with liquid sealant. The liquid polymerizes to form a tough thermoset polymer that permanently seals the pores. Liquid sealant is easily washed off with plain water and parts treated with this product are unchanged cosmetically or dimensionally. This product is used to seal castings and powder metal parts against leakage of coolants, lubricants, fuels, hydraulic fluids, air and other fluids in automotive powertrains, steering systems, air conditioning and other components.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Density @ 21 °C, g/cm ³	1.06
Surface Tension, ASTM D 1590, dynes/cm	33
Viscosity, Cannon Fenske, ISO 3104, mPa·s (cP): Cannon Fenske #100	5 to 15 ^{LMS}
Flash Point - See SDS	

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties

Coefficient of Thermal Expansion, ISO 11359-2 K ⁻¹	160×10 ⁻⁰⁶
Density @ 25 °C, g/cm ³	1.24
Shore Hardness, ISO 868, Durometer D	74
Design Limit, Continuous Temperature, °C	177
Design Limit, Temperature Exposure less than 24 hours, °C	204

Compressive Modulus, ISO 604	N/mm ² 1,170 (psi) (169,500)
Flexural Modulus, ASTM D790	N/mm ² 1,070 (psi) (155,000)

TYPICAL ENVIRONMENTAL RESISTANCE

Data shown herein should not be used in place of actual part testing. Sealing performance depends as much upon the surrounding substrate as it does upon the sealant. The parent material provides substantial protection against oxygen and pressure loads. Smaller pores, longer leak paths and lower differential pressures yield better durability. The testing described herein provides standard comparisons of LOCTITE[®] sealants on a consistent interface. *Predicting the performance of real world applications using extrapolations from this data is not recommended.* The performance of any sealant should be experimentally validated against the specific demands of a particular application, preferably using actual production methods.

Durability Performance

Standard test pieces were sealed with LOCTITE[®] IS Resinol[™] AT[™] and subjected to accelerated life testing under adverse conditions. The test specimen was 3.2 mm thick FC0208 sintered powder metal of 6.8 g/mL density (12% porous substrate). Samples were tested at 4 atmospheres internal pressure. Leak rates were measured using volume/time at pressure under water. Initial leak rates were over 10,000 mL/minute.

Environment	°C	% of initial leak			
		500 h	1000 h	2000 h	4100 h
21% Oxygenated Air (control)	23	0	0	0	0
Unleaded gasoline	23	0	0	0	0
Motor oil (10W-30)	121	0	0	0	0
ATF (Dexron III)	121	0	0	0	0
Water/glycol 50/50	121	0	0	0	0
Brake Fluid (Dot 3)	121	0	0	0	0
21% Oxygenated Air	121	0.0	0.0	0.0	0.0

High Temperature Resistance

At temperatures above 160 °C, organic polymers may react with available oxygen. In porosity, the surrounding substrate typically protects the sealant from air. Oxidation may cause the sealant to discolor without compromising the seal. Exterior surfaces are affected first; therefore, cross-sections that are thicker than 3.2 mm enjoy proportionately higher resistance. Applications that include working fluids other than oxygenated air resist elevated temperatures better.

Conditioning	Environment	% Leak
4100 hours salt fog	40 °C, Condensing	0
1000 Thermal Cycles	-40 °C to + 121 °C, 2 hour period	0
Acid Exposure	24 hours in pH 1 sulfuric acid	0
Caustic Exposure	24 hours in pH 13 sodium hydroxide	0
Hot Strength	100 psi air, part @ 176 °C	0

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Safety Data Sheet (SDS).

Directions for use

Porosity sealants typically require catalyzation and must be handled with chemically compatible materials and equipment.

Use of process equipment designed, built and maintained to LOCTITE® standards is recommended to ensure consistent performance. Consult a LOCTITE® Porosity Sealing Specialist for specific application assistance, process development and equipment selection.

1. Impregnate LOCTITE® IS Resinol™ AT™ into the parts by using any of the following impregnation methods:
 - Wet Vacuum
 - Wet Vacuum/Pressure
 - Dry Vacuum/Pressure
 - Pressure Impregnation.
2. Centrifuge or drip drain the parts to reclaim excess sealant from the parts.
3. Wash parts in water (detergent solution optional) with agitation as necessary to achieve good cleaning.
4. Parts can be placed in an optional surface activator rinse to help cure excessive surface porosity.
5. Soak parts in final rinse at temperatures between 25°C and 55°C to remove activator rinse and warm the parts for quick drying upon removal. Note: corrosion inhibitors may be added to final rinse if required.

Anaerobic Cure Mechanism

Liquid LOCTITE® IS Resinol™ AT™ cures in the absence of freely available oxygen. Surface bleedout normally associated with hot water cure is eliminated.

Cure rate depends on the part temperature, dimension and chemical activity of the surrounding porosity. In general, parts can be pressure tested within 5 to 30 minutes after processing.

Waste Rinse Water Disposal

Waste rinse water generated during the porosity sealing

process can, in general, be adequately handled by conventional biological treatment methods. Since both the circumstances of use and local environmental requirements vary, waste disposal recommendations are location specific. Depending on the particular parameters, a LOCTITE® Porosity Sealing Specialist can characterize effective waste disposal options for a wide range of solutions from passive handling to zero discharge.

Loctite Material Specification^{LMS}

LMS dated February 19, 2010. Test reports for each batch are available for the indicated properties. LMS test reports include selected QC test parameters considered appropriate to specifications for customer use. Additionally, comprehensive controls are in place to assure product quality and consistency. Special customer specification requirements may be coordinated through Henkel Quality.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 8 °C to 21 °C. Storage below 8 °C or greater than 28 °C can adversely affect product properties. Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Conversions

(°C x 1.8) + 32 = °F
 kV/mm x 25.4 = V/mil
 mm / 25.4 = inches
 µm / 25.4 = mil
 N x 0.225 = lb
 N/mm x 5.71 = lb/in
 N/mm² x 145 = psi
 MPa x 145 = psi
 N·m x 8.851 = lb·in
 N·m x 0.738 = lb·ft
 N·mm x 0.142 = oz·in
 mPa·s = cP

Note:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.2