

Dynasolve™ 700 Series—711, 715, 750, 760



Cured Polymer Cleaning Solvents



The Dynasolve 700 series solvents are reactive formulated solvents which are used to remove anhydride-cured epoxy, urethane, and silicone. The solvents are used in both industrial and electronic applications. The four products differ in terms of aluminum compatibility, the presence or not of the solvent NMP, and REACH compliance (see comparison table below).

CLEANING APPLICATIONS

Depotting and decapsulating electronic components
Industrial polymer removal and cleaning

ADVANTAGES:

More efficient than acetone, MEK & other solvents
All-in-one product works on several types of polymers
Formulated to be highly selective
High resin loading capacity allows for reuse and reduced cost of ownership

MATERIALS REMOVED:

Anhydride-cured epoxy
Urethane
Silicone

PRODUCT USAGE GUIDELINES

(SEE SDS FOR EH&S INFORMATION):

- Heat Dynasolve 700 Series solvent and immerse part.
 - Heat to 245°F (118°C) for anhydride cured epoxy
 - Heat to 200°F (93°C) for urethane or silicone
- Observe carefully. If polymer appears unaffected after 1 hour, increase temperature to 250° – 300°F (121° – 148°C).
- After successful removal of material, rinse with alcohol or water.
- If polymer appears unaffected after 2 hours, call for technical support.

MATERIAL COMPATIBILITY:

Recommended materials including:

Most metals
Teflon™
Polyethylene & polypropylene
Neoprene

Avoid materials including:

Galvanized steel & titanium
Liquid Isocyanate
Vinyl
Lucite®, plexiglass & polystyrene

DYNASOLVE 700 SERIES COMPARISON TABLE

	Dynasolve 711	Dynasolve 715	Dynasolve 750	Dynasolve 760
Contains NMP	Yes	No	Yes	No
REACH Compliant	No	Yes	No	Yes
24 hr. Aluminum Compatibility	Yes	Yes	No	No
Flash Point	102°F (39°C)	106°F (41°C)	106°F (41°C)	106°F (41°C)
Boiling Point	248°F (120°C)	248°F (120°C)	248°F (120°C)	248°F (120°C)
Specific Gravity	0.99	0.99	1.01	1.01



For more information, please contact us at:

VERSUM MATERIALS, LLC
VERSUMMATERIALS.COM

The information contained herein is offered without charge for use by technically qualified personnel at their discretion and risk. All statements, technical information and recommendations contained herein are based on tests and data which we believe to be reliable, but the accuracy or completeness thereof is not guaranteed and no warranty of any kind is made with respect thereto.