

Multi-Cure® 9001-E-V3.1 Resilient, Clear Encapsulant

9001-E-V3.1 encapsulant is a performance upgrade of the flexible “instant curing” Dymax 9001 UV/Visible light-curable encapsulant, with improved moisture and thermal cycle resistance, and adhesion to various component substrates. Curing completely in as little as five seconds upon exposure to longwave UV and visible light, this material is environmentally resistant with good ionic and electrical properties. Multi-Cure® 9001-E-V3.1 encapsulant displays excellent adhesion to printed circuit boards and electronic components and is especially well suited for chip-on-board, chip-on-flex, and multi-chip modules. This product is in full compliance with RoHS directives 2015/863/EU.

UNCURED PROPERTIES (not specifications)

Solvent Content	None, 100% Solids	
Isocyanate Content	None	
Chemical Class	Modified Urethane	
Appearance	Liquid	
Color	Colorless	
Solubility	Alcohols/Chlorinated Solvents/Ketones	
Viscosity (20 rpm)	4,500 cP (nominal)	ASTM D-2556

CURED PROPERTIES (not specifications)

PHYSICAL

Durometer Hardness	D45 (nominal)	ASTM D-2240
Elongation at Break	150%	ASTM D-638
Tensile at Break	750 psi	ASTM D-638
Modulus of Elasticity	2,500 psi	ASTM D-638
Water Absorption (24 h)	1.0%	ASTM D-570
Boiling Water Absorption (2 h)	2.6%	ASTM D-570
Thermal Limit	150°C	DSTM D-200*
Glass Transition, T _g	40°C	DSTM 256*
Coefficient of Thermal Expansion, α ₁	95 x 10 ⁻⁶ in/in/°C	ASTM E-831
Coefficient of Thermal Expansion, α ₂	180 x 10 ⁻⁶ in/in/°C	ASTM E-831
Linear Shrinkage	2%	ASTM D-2556

*DSTM Refers to Dymax Standard Test Method

Thermal Shear Stress (-55°C to 125°C) on:

Aluminum	16.4 psi
FR-4	16.9 psi
Gold	17.0 psi
Silicon	17.5 psi
Solder	16.0 psi

Ionic Purity:

Extractable Chloride	<10 ppm
Sodium	<10 ppm
Potassium	<10 ppm
Fluoride	<10 ppm

RELIABILITY

Thermal Shock (0.25 mil wire)	>2,000 cycles (-40°C to 125°C)
Humidity	>1,000 h, 85°C/85% RH



© 2009-2012 Dymax Corporation. All rights reserved. All trademarks in this guide, except where noted, are the property of, or used under license by Dymax Corporation, U.S.A.

Technical data provided is of a general nature and is based on laboratory test conditions. Dymax does not warrant the data contained in this bulletin. Any warranty applicable to the product, its application and use is strictly limited to that contained in Dymax standard Conditions of Sale. Dymax does not assume responsibility for test or performance results obtained by users. It is the user's responsibility to determine the suitability for the product application and purposes and the suitability for use in the user's intended manufacturing apparatus and methods. The user should adopt such precautions and use guidelines as may be reasonably advisable or necessary for the protection of property and persons. Nothing in this communication shall act as a representation that the product use or application will not infringe on a patent owned by someone other than Dymax or act as a grant of license under any Dymax Corporation Patent. Dymax recommends that each user adequately test its proposed use and application before actual repetitive use, using the data in this communication as a general guideline. Technical Data Collection Prior to 2009 REV. 12/21/2018

Dymax Corporation
+1.860.482.1010 | info@dymax.com | www.dymax.com

Dymax Europe GmbH
+49 611.962.7900 | info_de@dymax.com | www.dymax.de

Dymax Engineering Adhesives Ireland Ltd.
+353 21.237.3016 | info_ie@dymax.com | www.dymax.ie

Dymax Oligomers & Coatings
+1.860.626.7006 | info_oc@dymax.com | www.dymax-oc.com

Dymax UV Adhesives & Equipment (Shanghai) Co. Ltd.
+86.21.37285759 | dymaxasia@dymax.com | www.dymax.com.cn

Dymax UV Adhesives & Equipment (Shenzhen) Co. Ltd.
+86.755.83485759 | dymaxasia@dymax.com | www.dymax.com.cn

Dymax Asia (H.K.) Limited
+852.2460.7038 | dymaxasia@dymax.com | www.dymax.com.cn

Dymax Asia Pacific Pte. Ltd.
+65.6752.2887 | info_ap@dymax.com | www.dymax-ap.com

Dymax Korea LLC
+82.2.784.3434 | info_kr@dymax.com | www.dymax.com/kr

ELECTRICAL

Dielectric Strength	500 Volts/Mil	ASTM D-1304
Volume Resistivity	555 x 10 ¹² ohm cm	ASTM D-1304
Surface Resistivity	6,300 x 10 ¹² ohm	ASTM D-1304
Dissipation Factor, 1 MHz	0.046 (23°C)	ASTM D-1304
Dielectric Constant, 1 MHz	3.27 (23°C)	ASTM D-1304

HOW TO CURE WITH UV/VISIBLE LIGHT & IR:**I. Clear adhesive completely exposed to UV/Visible light:**

<u>Exposure Time</u>	<u>UV/Visible Lamp</u>	<u>Light Intensity</u>	<u>Distance</u>	<u>Spectral Output</u>
30 sec	5000-EC	150 mW/cm ²	3 inches	300-500 nm

Multi-Cure[®] 9001-E-V3.1 encapsulant cures upon exposure to high-intensity UV/Visible light in wavelengths between 300-500 nm in 10-30 seconds. The speed of light cure depends on the thickness of the encapsulant layer and the intensity from the light source.

II. Heat cure shadowed areas following UV exposure:

Heat may be used as a secondary cure mechanism when some encapsulant is shielded from light. Light cure must be done prior to heat cure. Any of the following schedules may be used:

<u>Minimum Adhesive Temperature</u>	<u>Time</u>
110°C (225°F)	60 Minutes
120°C (250°F)	30 Minutes
150°C (300°F)	15 Minutes

DISPENSING AND HANDLING ADHESIVE

Avoid prolonged exposure to ambient fluorescing lighting. Failing to do so may cause the encapsulant to polymerize prematurely.

Multi-Cure[®] 9001-E-V3.1 encapsulant may be dispensed from a variety of automatic bench-top syringe applicators or other equipment. Skin contact should be avoided. Use barrier hand cream. Wear impervious gloves. Do not wear absorbent gloves. Uncured adhesive may be removed with hand soap and water. Avoid eye contact. Wipe excess adhesive with paper towels and remove residue with isopropanol.

STORAGE AND SHELF LIFE

Store material in a cool, dark place when not in use. Do not expose to UV light or sunlight. Material may polymerize upon prolonged exposure to ambient light. Replace lid immediately after use. This material has an 18-month shelf life from date of manufacture, unless otherwise specified, when stored between 10°C (50°F) and 35°C (90°F) in the original, unopened container. This product does not support fungal or bacterial growth.

CAUTION

For industrial use only. Avoid breathing vapors. Avoid contact with eyes and clothing. In case of skin contact, immediately flush with water for at least 15 minutes; for eyes, get medical attention. Wash clothing before reuse. Keep out of reach of children. Do not take internally. If swallowed, vomiting should be induced at once and a physician called. For specific information, refer to the product's Material Safety Data Sheet before use.

GENERAL INFORMATION

This product is intended for industrial use only. Keep out of the reach of children. Avoid breathing vapors. Avoid contact with skin, eyes, and clothing. Wear impervious gloves. Repeated or continuous skin contact with uncured material may cause irritation. Remove material from skin with soap and water. Never use organic solvents to remove material from skin and eyes. For more information on the safe handling of this material, please refer to the Safety Data Sheet before use.

The data provided in this document are based on historical testing that Dymax performed under laboratory conditions as they existed at that time, and are for informational purposes only. The data are neither specifications nor guarantees of future performance in a particular application. Dymax does not guarantee that this product's properties are suitable for the user's intended purpose.

Numerous factors—including, without limitation, transport, storage, processing, the material with which the product is used, and the ultimate function or purpose for which the product was obtained—may affect the product's performance and/or may cause the product's actual behavior to deviate from its behavior in the laboratory. None of these factors are within Dymax's control.



Conclusions about the behavior of the product under the user's particular conditions, and the product's suitability for a specific purpose, cannot be drawn from the information contained in this document.

It is the user's responsibility to determine (i) whether a product is suitable for the user's particular purpose or application and (ii) whether it is compatible with the user's intended manufacturing process, equipment, and methods. Under no circumstances will Dymax be liable for determining such suitability or compatibility. Before the user sells any item that incorporates Dymax's product, the user shall adequately and repetitively test the item in accordance with the user's procedures and protocols. Unless specifically agreed to in writing, Dymax will have no involvement in, and shall under no circumstances be liable for, such testing.

Dymax makes no warranties, whether express or implied, concerning the merchantability of this product or its fitness for a particular purpose. Nothing in this document should be interpreted as a warranty of any kind. Under no circumstances will Dymax be liable for any injury, loss, expense or incidental or consequential damage of any kind allegedly arising in connection with the user's handling, processing, or use of the product. It is the user's responsibility to adopt appropriate precautions and safeguards to protect persons and property from any risk arising from such handling, processing, or use.

The specific conditions of sale for this product are set forth in Dymax's Conditions of Sale which are available at <https://www.dymax.com/index.php/en/resources/sales-terms-conditions>. Nothing contained herein shall act as a representation that the product use or application is free from patents owned by Dymax or any others. Nothing contained herein shall act as a grant of license under any Dymax Corporation Patent.

Except as otherwise noted, all trademarks used herein are trademarks of Dymax. The "®" symbol denotes a trademark that is registered in the U.S. Patent and Trademark Office.

The contents of this document are subject to change. Unless specifically agreed to in writing, Dymax shall have no obligation to notify the user about any change to its content.