

# Light Weld® 425 **Optically Clear Structural Adhesive for Glass Assembly**

Dymax Light Weld® 425 forms water-white bonds in seconds to glass substrates upon exposure to longwave (365 nanometer) UV light. These durable bonds are dishwasher safe and exhibit exceptional tensile strength as well as vibration and impact resistance. Acceptable bonds form to a variety of other substrates such as ceramic, ferrite and metal surfaces. Light Weld® 425 should be evaluated for applications where exceptional moisture resistance is required. This product is in full compliance with RoHS directives 2015/863/EU.

## **UNCURED PROPERTIES (not specifications)**

Solvent Content None 100% Solids Composition Appearance Clear Flash Point 95°C (200°F) Solubility Isopropyl Alcohol

**Toxicity** Low

4,000 cP Viscosity (@ 20 rpm) **ASTM D-1084** 

## **CURED PROPERTIES (not specifications)**

#### **PHYSICAL**

Linear Shrinkage

Durometer Hardness	D80	ASTM D-2240
Tensile at Break	6,200 psi	ASTM D-638
Elongation at Break	7.3%	ASTM D-638
Tensile at Yield	7,300 psi	ASTM D-638
Elongation at Yield	3.5%	ASTM D-638
Tensile (Compression) Glass-to-Glass	4,000 psi	DSTM D-250*
Modulus of Elasticity	500,000 psi	ASTM D-638
Water Absorption	0.7%	ASTM D-570
Refractive Index	1.50	Bausch & Lomb Refractometer

1.9%

## UV LIGHT CURE DATA (Using 365 nm wavelenth UV light [1]

	Cure Time	Intensity <sup>[2]</sup>	Dymax
	(seconds)	mW/cm <sup>2</sup>	<u>Lamps</u>
Fixture between glass slides	>1	50	2000-ÉC
Nominal Cure Depth (0.25")	60	50	2000-EC
Tack Free Cure Time	30	250	5000-EC
	2	2,500	Fusion F-450**

<sup>\*\*</sup>Equip Fusion with D-bulb<sup>[2]</sup>



© 2004-2009 Dymax Corporation. All rights reserved. All trademarks in this guide, except where noted, are the property of, or used under license by Dymax Corporation, U.S.A.

Technical data provided is of a general nature and is based on laboratory test conditions. Dymax does not warrant the data contained in this bulletin. Any warranty applicable to the product, its application and use is strictly limited to that contained in Dymax standard Conditions of Sale. Dymax does not assume responsibility for test or performance results obtained by users. It is the user's responsibility to determine the suitability for the product application and purposes and the suitability for use in the user's intended manufacturing apparatus and methods. The user should adopt such precautions and use guidelines as may be reasonably advisable or necessary for the protection of property and persons. Nothing in this communication shall act as a representation that the product use or application will not infringe on a patent owned by someone other than Dymax or act as a grant of license under any Dymax Corporation Patent. Dymax recommends that each user adequately test its proposed use and application before actual repetitive use, using the data in this communication as a general guideline.

REV. 12/20/2018

Dymax Corporation

1.860.482.1010 | info@dymax.com | www.dymax.com

Dymax Europe GmbH +49 611.962.7900 | info\_de@dymax.com | www.dymax.de

Dymax Engineering Adhesives Ireland Ltd. +353 21.237.3016 | info\_ie@dymax.com | www.dymax.ie

Dymax Oligomers & Coatings +1.860.626.7006 | info\_oc@dymax.com | www.dymax-oc.com

Dymax UV Adhesives & Equipment (Shanghai) Co. Ltd. +86.21.37285759 | dymaxasia@dymax.com | www.dymax.com.cn

Dymax UV Adhesives & Equipment (Shenzhen) Co. Ltd. +86.755.83485759 | dymaxasia@dymax.com | www.dymax.com.cn

Dymax Asia (H.K.) Limited

+852.2460.7038 | dymaxasia@dymax.com | www.dymax.com.cn

Dymax Asia Pacific Pte. Ltd. +65.6752.2887 | info\_ap@dymax.com | www.dymax-ap.com

Dymax Korea LLC

+82.2.784.3434 | info\_kr@dymax.com | www.dymax.com/kr

<sup>\*</sup>DSTM refers to Dymax Standard Test Method





#### 425 Product Data Sheet

#### **DISPENSING AND HANDLING ADHESIVE**

Dymax 425 is available in various packaging sizes such as syringes, cartridges, bottles, and pails. It may be dispensed with a variety of automatic bench-top syringe applicators or other equipment as required. Direct any questions relating to dispensing and curing systems for specific applications to Dymax Application Engineering.

Wear impervious gloves and/or barrier cream. Repeated or continuous skin contact with liquid adhesive will cause irritation and should be avoided. Do not wear absorbent gloves. Remove adhesive from skin with soap and water. Never use solvents to remove adhesive from skin or eyes.

#### STORAGE AND SHELF LIFE

Store material in cool, dark place when not in use. Do not expose to UV light or sunlight. Material may polymerize upon prolonged exposure to ambient light. Replace lid immediately after use. This material has an 18-month shelf life from date of manufacture, unless otherwise specified, when stored between 10°C (50°F) and 35°C (90°F) in the original, unopened container.

#### **CAUTION**

For industrial use only. Avoid breathing vapors. Avoid contact with eyes and clothing. In case of contact, immediately flush with water for at least 15 minutes; get medical attention. Wash clothing before reuse. Keep out of reach of children. Do not take internally. If swallowed, induce vomiting at once and call a physician. Repeated or continuous skin contact with liquid adhesive will cause irritation and should be avoided. For specific information, refer to the product Material Safety Data Sheet.

## **GENERAL INFORMATION**

This product is intended for industrial use only. Keep out of the reach of children. Avoid breathing vapors. Avoid contact with skin, eyes, and clothing. Wear impervious gloves. Repeated or continuous skin contact with uncured material may cause irritation. Remove material from skin with soap and water. Never use organic solvents to remove material from skin and eyes. For more information on the safe handling of this material, please refer to the Safety Data Sheet before use.

The data provided in this document are based on historical testing that Dymax performed under laboratory conditions as they existed at that time, and are for informational purposes only. The data are neither specifications nor guarantees of future performance in a particular application. Dymax does not guarantee that this product's properties are suitable for the user's intended purpose.

Numerous factors—including, without limitation, transport, storage, processing, the material with which the product is used, and the ultimate function or purpose for which the product was obtained—may affect the product's performance and/or may cause the product's actual behavior to deviate from its behavior in the laboratory. None of these factors are within Dymax's control. Conclusions about the behavior of the product under the user's particular conditions, and the product's suitability for a specific purpose, cannot be drawn from the information contained in this document.

It is the user's responsibility to determine (i) whether a product is suitable for the user's particular purpose or application and (ii) whether it is compatible with the user's intended manufacturing process, equipment, and methods. Under no circumstances will Dymax be liable for determining such suitability or compatibility. Before the user sells any item that incorporates Dymax's product, the user shall adequately and repetitively test the item in accordance with the user's procedures and protocols. Unless specifically agreed to in writing, Dymax will have no involvement in, and shall under no circumstances be liable for, such testing.

Dymax makes no warranties, whether express or implied, concerning the merchantability of this product or its fitness for a particular purpose. Nothing in this document should be interpreted as a warranty of any kind. Under no circumstances will Dymax be liable for any injury, loss, expense or incidental or consequential damage of any kind allegedly arising in connection with the user's handling, processing, or use of the product. It is the user's responsibility to adopt appropriate precautions and safeguards to protect persons and property from any risk arising from such handling, processing, or use.

The specific conditions of sale for this product are set forth in Dymax's Conditions of Sale which are available at <a href="https://www.dymax.com/index.php/en/resources/sales-terms-conditions">https://www.dymax.com/index.php/en/resources/sales-terms-conditions</a>. Nothing contained herein shall act as a representation that the product use or application is free from patents owned by Dymax or any others. Nothing contained herein shall act as a grant of license under any Dymax Corporation Patent.

Except as otherwise noted, all trademarks used herein are trademarks of Dymax. The "®" symbol denotes a trademark that is registered in the U.S. Patent and Trademark Office.

The contents of this document are subject to change. Unless specifically agreed to in writing, Dymax shall have no obligation to notify the user about any change to its content.