

Dynasolve™ 200 Series—218, 220, 225 and 230



Cured Silicone Cleaning Solvents



The Dynasolve 200 Series solvents are reactive formulated solvents which are used to remove cured silicones in both electronic and industrial applications. The four products vary based on aggression level and flash point, so the best product for a given application depends on the desired balance of aggression and flash point (see comparison table below).

CLEANING APPLICATIONS

Depotting and decapsulating electronic components

Conformal coating removal

Industrial silicone removal and cleaning

ADVANTAGES:

More efficient than acetone, MEK & other solvents

Formulated to be highly selective

Non-chlorinated

Ability to use at room temperature

High resin loading capacity allows for reuse and reduced cost of ownership

MATERIALS REMOVED:

Conformal coatings

Encapsulants/potting compounds

RTVs

Industrial silicones

PRODUCT USAGE GUIDELINES

(SEE SDS FOR EH&S INFORMATION):

1. Ensure the part is completely free of water.
2. Immerse part in Dynasolve 200 Series solvent.
 - Dynasolve 220, 225, and 230 should be used at room temperature.
 - Dynasolve 218 should be used at 125°F (52°C).
3. Once cured silicone has been removed, it is critical to rinse with alcohol prior to rinsing with water.
4. Observe carefully. If silicone is unaffected by Dynasolve 200 series solvent after 4 hours, call for technical support.

MATERIAL COMPATIBILITY:

Recommended materials including:

All metals

Teflon™

Polyethylene & polypropylene

Avoid materials including:

Nylon

PVC

Do not immerse in aluminum for more than 8 hours

DYNASOLVE 200 SERIES COMPARISON TABLE

	Dynasolve 218	Dynasolve 220	Dynasolve 225	Dynasolve 230
Aggression Level	Low	Low	Medium	High
Flash Point	165°F (73°C)	111°F (44°C)	48°F (9°C)	18°F (-7°C)
Usage Temp	125°F (52°C)	Room Temp	Room Temp	Room Temp
Boiling Point	> 365°F (> 185°C)	> 320°F (> 160°C)	> 235°F (> 112°C)	> 200°F (> 93°C)
Specific Gravity	0.84	0.83	0.81	0.31



For more information, please contact us at:

VERSUM MATERIALS, LLC
VERSUMMATERIALS.COM

The information contained herein is offered without charge for use by technically qualified personnel at their discretion and risk. All statements, technical information and recommendations contained herein are based on tests and data which we believe to be reliable, but the accuracy or completeness thereof is not guaranteed and no warranty of any kind is made with respect thereto.