

Dynasolve™ 699



Cured Acrylic Cleaning Solvent



Dynasolve 699 is a formulated solvent which is used to remove acrylic and methacrylate materials in both electronic and industrial applications.

CLEANING APPLICATIONS:

Removal of acrylic conformal coatings
Removal of methacrylate based adhesives and materials
Industrial acrylic removal and cleaning

ADVANTAGES:

More efficient than acetone, MEK & other solvents
Formulated to be highly selective
Can be used at room temperature
High flash point
High resin loading capacity allows for reuse and reduced cost of ownership

SPECIFICATIONS:

Specific gravity:	1.06
Boiling point:	395°F (201°C)
Flash point:	188°F (87°C)

MATERIALS REMOVED:

Cured acrylic materials
Methacrylate adhesives

PRODUCT USAGE GUIDELINES

(SEE SDS FOR EH&S INFORMATION)

1. Immerse part in Dynasolve 699 at room temperature.
2. Observe carefully. If acrylic appears unaffected after 1 hour, increase temperature to 150° – 200°F (65° – 93°C).
3. After successful removal of acrylic material, rinse with alcohol or water.
4. If acrylic is unaffected by Dynasolve 699 after 2 hours, call for technical support.

MATERIAL COMPATIBILITY:

Recommended materials including:

All metals
Teflon®
Polyethylene & polypropylene

Avoid materials including:

Viton®
PVC
Urethane



For more information, please contact us at:

VERSUM MATERIALS, LLC
VERSUMMATERIALS.COM

The information contained herein is offered without charge for use by technically qualified personnel at their discretion and risk. All statements, technical information and recommendations contained herein are based on tests and data which we believe to be reliable, but the accuracy or completeness thereof is not guaranteed and no warranty of any kind is made with respect thereto.