

BONDERITE S-FN 330 ACHESON

Known as Emralon 330
November 2015

PRODUCT DESCRIPTION

BONDERITE S-FN 330 ACHESON provides the following product characteristics:

Technology	Lubricant
Product Type	Fluorocarbon dispersion in solvent
Application	Dry film lubricant

BONDERITE S-FN 330 ACHESON is one of a series of Henkel resin-bonded lubricant coatings formulated to provide dry film lubrication in a variety of industrial and consumer applications.

BONDERITE S-FN 330 ACHESON is a dispersion of fluorocarbon in a thermosetting binder, designed to be applied by spray.

It produces a low friction coating free of stick-slip characteristics.

The product is recommended for metal substrates.

For wood, rubber and plastics specially designed types of BONDERITE exist.

BONDERITE S-FN 330 ACHESON is a one-package product which is not affected by low-temperature storage conditions.

Application Areas

- Fasteners
- Carburettor parts
- Lock mechanisms
- Valves (for water, gas or oil)
- Gears
- Bearings

TECHNICAL DATA

(of wet product)

Lubricant	fluorocarbon
Binder	thermosetting resin
Solids content, %	25 to 26
Viscosity (Brookfield), mPas	60 to 150
Density, kg/m ³	~960
Flash Point (open cup), °C	10
Theoretical coverage	~22 m ² /kg at 10 µm dry coating thickness
Color	blue
Diluent	Methyl Ethyl Keton

(as a cured coating)

Colour	green
Coefficient of friction (static and kinetic)	0.7
Flexibility, 3.2 mm radius bend on 0.8 mm	no loss of adhesion

steel test panels

Salt spray resistance* (ASTM B 117) greater than 500 hrs

Humidity resistance* (98% RH at 49°C) greater than 500 hrs

Service temperature:

continuous, °C 150

intermittent, °C 160

Chemical resistance: resistant to oils, alcohols, ketones, chlorinated hydrocarbons, dilute acids, esters and aromatic hydrocarbons, gasohol.

*Coating cured at 160°C for 60 minutes; substrate: zinc phosphated steel; coating thickness: 0.025 mm.

DIRECTION OF USE

Preliminary Statement

Prior to use it is necessary to read the **Material Safety Data Sheet** for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed. Please also refer to the local safety instructions and contact Henkel for analytical support.

Pretreatment

Substrates should be clean and dry before application. A solvent wipe and air dry is usually sufficient. For critical applications requiring maximum adhesion, mechanical or chemical pretreatment such as grit blasting, phosphating, anodising or etching is recommended. Specific recommendations will be provided upon request.

Mixing

BONDERITE S-FN 330 ACHESON can be spray applied undiluted. However, to obtain maximum smoothness, dilute the product with methyl ethyl ketone (MEK) in the ratio of three parts product (by weight) to one part solvent.

Application

Use an external-atomizing spray gun with 2 to 3 bar air pressure and adjust the gun to give a well-atomized spray.

For optimum performance, the final coating thickness should be 10 to 25 µm.

For thicker coatings use multiple passes pausing a few minutes between passes to permit air drying.

When properly applied, the coating will be even and free of runs, blisters or "fish eyes".

Electrostatic spray equipment suitable for products with very low internal resistance may be used to apply BONDERITE S-FN 330 ACHESON.

Curing

For optimum results, BONDERITE S-FN 330 ACHESON should be cured on either one of the three following curing cycles:

1. 60 minutes/ 160°C (substrate temperature)
2. 30 minutes/ 180°C (substrate temperature)
3. 10 minutes/ 200°C (substrate temperature)

Cleaning up

Spray guns, tanks, mixing hardware and spills of BONDERITE S-FN 330 ACHESON can easily be cleaned with MEK. Cured coatings can be removed by sand blasting or soaking in hot caustic solutions.

Storage

Recommended Storage Temperature, °C	5 to 30
Shelf-life, months (in unopened original packaging)	24

Classification

Please refer to the corresponding **Material Safety Data**

Sheets for details on:

- Hazards identification**
- Transport information**
- Regulatory information**

ADDITIONAL INFORMATION**Disclaimer****Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.0