

N109 W13300 ELLSWORTH DRIVE GERMANTOWN, WI 53022
262-253-5900 FAX 262-253-5919

DESCRIPTION:

Resinlab[®] EP9651 Black is a REACH compliant version of EP965 Black. It is a two part unfilled black epoxy encapsulant designed for applications with small to medium sized castings and for bonding a variety of materials. It provides good wetting and adhesion to most surfaces and is free flowing to penetrate voids while releasing any trapped air.

EP9651 Black cures at room temperature within 24 hours to a smooth, high gloss tough polymer with thermal shock and cycle resistance. Cure time can be accelerated by the application of heat after the product has gelled. It is resistant to water, acids, bases and most organic solvents. It maintains the same properties and performance of EP965 Black.

EP9651 Black is formulated at a 1:1 volume mix ratio for use in side-by-side dispensing cartridges and meter/mix and dispense equipment.

TYPICAL PROPERTIES:

All properties given are at 25 °C unless otherwise noted.

<i>Property:</i>	<i>Value:</i>	<i>Test Method or Source:</i>
Color	Black	Visual
Mix Ratio	Part A to Part B	Calculated
Mix Ratio by weight	1.16 to 1	
Mix Ratio by volume	1 to 1	
Cure Schedule	24 hrs @ 25 °C 1 hr @ 65 °C 20 min @ 100 °C	
Viscosity - Part A	17,000 cP	TA HR20 Rheometer 25mm parallel plate @
Viscosity - Part B	15,000 cP	1/s DCV6100723
Viscosity - Mixed	15,000 cP	
Specific Gravity - Part A	1.16	Calculated
Specific Gravity - Part B	1.01	
Specific Gravity - Mixed	1.09	
Pot Life defined as the time it takes for initial mixed viscosity to double	10 minutes	TA HR20 Rheometer parallel plate 25mm @ 1/s DCV6100723
Gel Time 100cc Sample	52 minutes	455300005339/Gardco Gel Timer
Hardness	80 Shore D	455300006287/ASTM D2240
Glass Transition Temperature/Tg	54 °C	453560822409 by DSC
Water Absorption	0.15 %	24 hr immersion 457561824543/ASTM D570
Peak Exotherm	120 °C after 22 minutes for 40 mL sample	455300005593 by Type K thermocouple
Tensile Properties:		4535601224470/ASTM D638
Strength	9,000 psi	
Elongation	5 %	
Modulus	380,000 psi	

N109 W13300 ELLSWORTH DRIVE GERMANTOWN, WI 53022
262-253-5900 FAX 262-253-5919

Property:	Value:	Test Method or Source:
Lap Shear Strength		4535601224468/ASTM D1002
0.010" Bond Line, Al to Al	900 psi	
Compressive Properties:		4535601224467/ASTM D695
Ultimate Strength	27,000 psi	
Modulus	168,000 psi	
Operating Temperature Range	-55 to 150 °C**	
Relative Thermal Index (RTI)	90 °C	UL746B, Table 7.1 Generic Value Based on Composition

* Asterisk denotes values considered typical to associated resin systems or extrapolated from other test results.

** Operating Temperature Range is based on average design requirements and is not intended as a guarantee of suitability for all applications operating at that temperature.

*** This TDS contains values that have been updated. The values reported in this technical data sheet are typical values of the product, and are highly dependent on test conditions and methodology. We actively seek the most precise and accurate ways to measure and interpret performance of our products, and to update estimated values with measured values. The formula has not been revised or changed in any way. Although the values on paper have changed, you can expect the same performance of the product.

INSTRUCTIONS:

1. Bring to room temperature prior to use.
2. Cartridge format: Mixer should be attached keeping the cartridge vertical and any air pocket purged this way. After the mixer contains material, the mixer tip can be dropped to dispense pre-bleed amount. Attach a new static mixer with each cartridge, then pre-bleed the first 3 inches of dispensed material or until a uniform color is obtained. Maintain adequate velocity during dispensing to ensure complete mixing.
3. Bulk format: stir until homogeneous weigh and mix parts A and B accurately and thoroughly, scraping sides of container often. Do not pour from mixing container, transfer to a new container as residual unmixed material may cause a tacky spot on the surface of the casting. Maintain adequate velocity during dispensing to ensure complete mixing.
4. Clean up uncured resin with suitable organic solvent such as MEK or acetone.
5. Allow to cure undisturbed until product is fully gelled or tack-free to the touch.

N109 W13300 ELLSWORTH DRIVE GERMANTOWN, WI 53022
262-253-5900 FAX 262-253-5919

SHELF LIFE AND STORAGE:

12 months at 25 °C.
Specialty packaging may be less.

Many epoxy resin systems are prone to crystallization as epoxy resin is a super-cooled fluid. This condition may give the product a gritty or grainy appearance (or hazy in clear products). Products in this state will not usually cure to normal and expected properties. In extreme cases it may appear solid and cured. Fluctuating temperatures (within 5 to 50 °C) aggravate this phenomenon. Heating the individual component to 50 to 60 °C while stirring can usually restore products to original state. Storage at 25 +/- 10 °C is optimum for most products.