

**PRODUCT DESCRIPTION**

LOCTITE® provides the following product characteristics:

Technology	Acrylic
Chemical Type	Methacrylate
Appearance (Part A)	Amber
Appearance (Part B)	Black
Appearance (Mixed)	Gray
Cure	Room temperature cure
Components	Two component - requires mixing
Mix Ratio, by volume – Part A: Part B	4:1
Product Benefits	<ul style="list-style-type: none"> • Superior impact and peel strength • Little or no surface preparation • Rapid room temperature cure • Excellent environmental Resistance • Compatible with metal pre-treatment and paint bake cycles. • Contains 10mil spacer
Application	Bonding

LOCTITE® H3405 is a two component, room temperature curing methacrylate adhesive system. The product is designed to have excellent bond strength on multiple substrates which includes a variety of metals including galvanized steel, plastics and composites. LOCTITE® H3405 offers superior peel and impact resistance.

TYPICAL PROPERTIES OF UNCURED MATERIAL**Part A:**

Specific Gravity @ 25°C: 0.97

Viscosity, Cone & Plate, 25 °C, mPa·s (cP):

PP25 @ shear rate ²⁰Sec⁻¹: 25,000-50,000

Flash Point – See SDS

PART B:

Specific Gravity @ 25°C: 1.41

Viscosity, Cone & Plate, 25 °C, mPa·s (cP):

PP25 @ shear rate ²⁰Sec⁻¹: 17,000-25,000

Flash Point – See SDS

Working Time @ 25°C

(Maximum time before assembly):

Aluminum: 3-5 minutes

TYPICAL CURING PERFORMANCE**Fixture Time**

Fixture time is defined as the time to develop a shear strength of 100 psi

Fixture Time @ 22° C: 8-12 minutes:

2024 T3 Bare Aluminum

Peak Exotherm Temperature

Peak Exotherm Temperature, 20-gram mass:

Peak Temperature Time: 7-13 minutes

TYPICAL PERFORMANCE OF CURED MATERIAL**Adhesive Properties****Cured for 24 hours @ 22° C**

Lap Shear Strength, ISO 4587:

2024 T3 Bare Aluminum >19.3 N/mm²
(2800 PSI)

Side Impact @ 22° C

Ground Steel 12.2 kJ/m²**Cured for 1 hour 22C, 5 min water soak, 25 mins 200C, 24 hours RT**

Lap Shear Strength, ISO 4587:

2024 T3 Bare Aluminum >24.8 N/mm²
(3600 PSI)

Side Impact @ -20° C

Ground Steel 14.2 kJ/m²**GENERAL INFORMATION**

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials

For safe handling information on this product, consult the Material Safety Data Sheet (SDS)

Directions for use:

1. For high strength, structural bonds, remove surface contaminants such as paint, oxide films, oils, dust, mold release agents and all other surface contaminants
2. Use gloves to minimize skin contact. DO NOT use solvents for cleaning hands.

3. **Dual Cartridges:** To begin using a new cartridge, remove cartridge cap and dispense a small amount of adhesive, making sure both parts A&B are extruding. Attach nozzle and dispense approximately 25 to 50mm, before applying onto part to be bonded. Partially used cartridges can be stored with the mixing nozzle attached. To reuse, remove and discard old nozzle, attach the new nozzle, dispense approximately 25 to 50mm, before applying onto part to be bonded.
Bulk Containers: Normally material is dispensed through volumetric metered mixing equipment, attached to static mix nozzles.
4. For maximum bond strength apply adhesive evenly to both surfaces to be joined.
5. Application to the substrates should be made as soon as possible. Larger quantities and/or higher temperatures will reduce the working time.
6. Join the adhesive coated surfaces and allow to cure. Higher temperatures will speed up curing.
7. Keep assembled parts from moving during cure. The bond should be allowed to develop full strength before subjecting to any service load.
8. Excessive uncured adhesive can be cleaned up with ketone type solvents.

Storage

The product is classified as flammable and must be stored in an appropriate manner in compliance with relevant regulations. Do not store near oxidizing agents or combustible materials. Store product in the unopened container in a dry location. Storage information may also be indicated on the product container labeling.

Optimal Storage: 2 °C to 8 °C. Storage below 2 °C or greater than 28 °C can adversely affect product properties. Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\mu\text{m} / 25.4 = \text{mil}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N m} \times 8.851 = \text{lb in}$
 $\text{N m} \times 0.738 = \text{lb ft}$
 $\text{N mm} \times 0.142 = \text{oz in}$
 $\text{mPa s} = \text{cP}$

NOTE

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **HENKEL CORPORATION SPECIFICALLY DISCLAIMS ANY AND ALL WARRANTIES EXPRESSED OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE ARISING FROM SALE OR USE OF HENKEL CORPORATION'S PRODUCTS. HENKEL CORPORATION SPECIFICALLY DISCLAIMS ANY LIABILITY FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES OF ANY KIND, INCLUDING LOST PROFITS.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Either the developmental product, nor the data or discussion except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.2



Loctite Industrial

Henkel Loctite Corporation, One Henkel Way, Rocky Hill, CT 06067, U.S.A.
 Loctite is a Trademark of Henkel Loctite Corp. U.S.A. 860.751.5100 www.loctite.com