

CoolTherm® SC-1600 Thermally Conductive Silicone Gap Filler

Technical Data Sheet

CoolTherm® SC-1600 gap filler is a two-component thermally conductive silicone system designed to provide thermal conductivity for electronic applications, while retaining desirable properties associated with silicones.

Features and Benefits:

Low Stress – exhibits low shrinkage and stress on components as it cures.

Durable – composed of an addition-curing polydimethylsiloxane polymer that will not depolymerize when heated in confined spaces.

Environmentally Resistant – provides excellent resistance to thermal shock, high temperature, and humid environments.

UL Rated – provides excellent flame retardancy; UL 94 V-0 certified.

Application:

Mixing – Mix CoolTherm SC-1600 resin with CoolTherm SC-1600 hardener at a 1:1 ratio, by weight or volume. Handheld cartridges or automatic meter/mix/dispense equipment should be used to avoid any air entrapment in the material. Manual mixing is not recommended.

Applying – Apply material using handheld cartridges or automatic meter/mix/dispense equipment.

- Handheld Cartridges
 1. Load the cartridge into the applicator gun and remove the end caps.
 2. Level the plungers by expelling a small amount of material to ensure both sides are level.
 3. Attach mixing tip and expel a mixer's length of material.
 4. Apply material to substrate and mate the parts within the working time of the gap filler. Clamp in position until material reaches handling strength.
- Meter/Mix/Dispense (MMD) Equipment
Contact your Parker LORD representative if assistance is needed using this equipment.

Avoid applying CoolTherm SC-1600 gap filler to surfaces that contain cure inhibiting ingredients, such as amines, sulfur, or tin salts. If bonding surface is in question, apply a test patch of gap filler to the surface and allow it to set for the normal cure time. A liquid layer of silicone will remain on the surface if an inhibitor is present.

Curing – Allow material to cure for 24 hours at room temperature (25°C) or for 30 minutes at 100°C. This time-at-temperature profile refers to the time the material should be allowed to cure once it reaches the target temperature. Allowance should be made for oven ramp rates, parts with large thermal mass and other circumstances that may delay material reaching the target temperature.

Typical Properties*

	SC-1600 Resin	SC-1600 Hardener	Mixed
Appearance	Pink Paste	White to Gray Paste	Light Pink Paste
Viscosity, cP @ 25°C			
1/sec Shear Rate	318,000	205,000	–
10/sec Shear Rate	114,000	75,000	–
Specific Gravity	3.3	3.3	3.3
Working Life, minutes @ 25°C	–	–	60

*Data is typical and not to be used for specification purposes.



ENGINEERING YOUR SUCCESS.

Typical Cured Properties*

Thermal Conductivity, W/m·K Hot Disc Transient Method ISO 22007-2	3.7
Hardness Shore OO, ASTM D 2240	89
Tensile Strength, MPa (psi) ASTM D 638	0.47 (68.17)
Elongation at Break, % ASTM D 638	25
Elastic Modulus, MPa ASTM D 638	3.1
Dielectric Strength @ 0.8 mm ASTM D 149	
kVDC/mm (VDC/mil)	12.1 (307)
kVAC/mm (VAC/mil)	7.6 (193)

*Data is typical and not to be used for specification purposes.

Shelf Life/Storage

Shelf life of each component is six months when stored at 15-30°C in original, unopened container.

CoolTherm SC-1600 gap filler evolves minute quantities of hydrogen gas. Do not repackage or store material in unvented containers. Adequately ventilate work area to prevent the accumulation of gas.

Cautionary Information:

Before using this or any Parker LORD product, refer to the Safety Data Sheet (SDS) and label for safe use and handling instructions.

For industrial/commercial use only. Must be applied by trained personnel only. Not to be used in household applications. Not for consumer use.

Values stated in this document represent typical values as not all tests are run on each lot of material produced. For formalized product specifications for specific product end uses, contact the Customer Support Center.

Information provided herein is based upon tests believed to be reliable. In as much as Parker LORD has no control over the manner in which others may use this information, it does not guarantee the results to be obtained. In addition, Parker LORD does not guarantee the performance of the product or the results obtained from the use of the product or this information where the product has been repackaged by any third party, including but not limited to any product end-user. Nor does the company make any express or implied warranty of merchantability or fitness for a particular purpose concerning the effects or results of such use.

WARNING — USER RESPONSIBILITY. FAILURE OR IMPROPER SELECTION OR IMPROPER USE OF THE PRODUCTS DESCRIBED HEREIN OR RELATED ITEMS CAN CAUSE DEATH, PERSONAL INJURY AND PROPERTY DAMAGE.

This document and other information from Parker-Hannifin Corporation, its subsidiaries and authorized distributors provide product or system options for further investigation by users having technical expertise.

The user, through its own analysis and testing, is solely responsible for making the final selection of the system and components and assuring that all performance, endurance, maintenance, safety and warning requirements of the application are met. The user must analyze all aspects of the application, follow applicable industry standards, and follow the information concerning the product in the current product catalog and in any other materials provided from Parker or its subsidiaries or authorized distributors.

To the extent that Parker or its subsidiaries or authorized distributors provide component or system options based upon data or specifications provided by the user, the user is responsible for determining that such data and specifications are suitable and sufficient for all applications and reasonably foreseeable uses of the components or systems.

©2021 Parker Hannifin - All Rights Reserved

Information and specifications subject to change without notice and without liability therefor. Trademarks used herein are the property of their respective owners.

OD DS4450 03/21 Rev.3



Parker LORD
Engineered Materials Group

111 LORD Drive
Cary, NC 27511-7923
USA

phone +1 877 ASK LORD (275 5673)

www.lord.com