

Technical Data Sheet



Thermal Management Adhesive Technologies

EV Therm 440 is a modified, highly engineered Structural Acrylic Adhesive designed to provide excellent thermal conductivity while maintaining superior strength and performance properties across a wide range of temperatures and substrates.

EV Therm 440 is an excellent flame retardant with a UL94 V0 rating.

EV Therm 440GB allows control of the adhesive gap to a diameter of 0.25mm (0.01").

Technology/Base:	Modified Acrylic	
Type of Product:	Structural Adhesive	
Components:	Two Component	
Curing:	Room Temperature Cure	
Appearance / Color:	Off White or Amber	
Consistency:	Viscous Liquid	

Recommended For

Metals Thermoplastics

Aluminum Acrylic
Steel ABS
Stainless Polycarbonate

E-Coated Metal

Thermosets

Fiberglass
Phenolic
Gel Coat
Epoxy
RIM Urethane
Polyurethane
Liquid Molding Resin



Features and Benefits



- Thermally Conductive
- No Surface Preparation Required
- Excellent Adhesion Properties
- Excellent Strength to Metals, E-Coat, Thermoplastics, Thermosets, and Engineering Plastics
- High Impact Resistance
- Suitable for Easy Manual and Pneumatic Dispensing

- UL94 V0 Flame Retardancy
- 100% Reactive
- Room Temperature Cure
- 10:1 meter-mix product for ease of application
- Use on aluminum, stainless and plated steels forms tough, high strength bonds without surface preparation



Technical Data

Rheology		Condition/Method
Viscosity - Resin	100,000 – 200,000 cPs @ 25°C	Brookfield RV7 20 rpm
Viscosity - Activator	40,000 - 80,000 cPs @ 25°C	Brookfield RV7 20 rpm
Density		
Mixed Density	1.67 g/cc	
Mix Ratio		
Volume Mix Ratio	10:1	
Weight Mix Ratio	14:1	
Uncured Material Characteristics		
Flash Point	>200°F	
Open Time	18 - 23 minutes	
Fixture Time	40 - 50 minutes	
Cure Temperature and Time	Room Temperature, 24 hr	
Cured Mechanical Properties		
Gap Fill Dimension		
Hardness	70 Shore D	ASTM D2240
Tensile Strength		
Over Lap Shear Strength		
Carbon Steel	15MPa (2,175 psi)	ASTM D1002, 25°C 50% RH
Aluminum	15MPa (2,175 psi)	ASTM D1002, 25°C 50% RH
Nickel Coated Low - Carbon Steel Plated	20MPa (2,900 psi)	ASTM D1002, 25°C 50% RH
Thermal Conductivity	>1.0W/(m*K)	
Flame Retardancy	UL94 V0	
Dielectric Strength	18.5 ± 0.9 kV/mm	
Elongation at Break	>4%	
Cured Thermal Properties	670F to 2420F	
Thermal Service Range	-67°F to 212°F	



General Information

The product is best used at temperatures between 65°F and 80°F. Temperatures below 65°F will slow the cure speed of the material and viscosities will be higher. Temperatures above 80°F will cause the material to cure faster and viscosities will be lower. For consistent dispensing maintain temperature in the above mentioned range.

For optimum bond strength and to insure maximum performance in the finished assembly mate parts together within the specified work time of the adhesive. Make sure the bond joint has uniform coverage and that a sufficient amount of adhesive is in the bond area. It is important to have the adhesive applied, parts aligned and positioned, within the established work times for the product. To ensure maximum performance in the finished assembly parts should remain undisturbed until the fixture time is reached.



Handling and Clean-Up

Clean up is best before the adhesive has cured. Cleaners containing NMP (N-methyl pyrolidone) or Citrus terpene provide the best results. On cured adhesive repeat use may be required.



Typical Packaging

EV Therm 440 is conveniently packaged in 50 ml, 490 ml, pail, and drum kits. Special packaging is available upon request.




Storage and Shelf Life


Product should be stored in a cool dry place out of direct sunlight. The shelf life of EV Therm 440 is 9 months from date of manufacture. Shelf life is based on the products being stored properly at temperatures between 55°F and 75°F. Exposure to temperatures above 75°F will reduce the shelf life. This product should NEVER BE FROZEN.



Safety and Disposal

Please see the Safety Data Sheet (SDS) for proper handling and disposal instructions.





www.hbfuller.com

© H.B. Fuller Company, 2021

IMPORTANT: The information, specifications, procedures and recommendations provided (information) are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is users sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. The user is advised to review the specific context of the intended use to determine whether the users intended use violates any law or infringes upon any patent(s). No employee, distributor or agent has any right to change these facts and offer a guarantee of performance

Unless otherwise noted, trademarks are property of H.B. Fuller Company or one of its affiliated entities.

NOTE TO USER: by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, (1) the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. (2) H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply. (3) Nothing in any term shall operate to exclude or limit H.B. Fullers liability for fraud, gross negligence or for death or personal injury caused by negligence, or for breach of any mandatory implied terms unless permitted by law.