



Technical Data Sheet



Thermal Management Adhesive Technologies

EV Therm 420 is a modified, highly engineered Structural Acrylic Adhesive designed to provide excellent thermal conductivity while maintaining superior strength and performance properties across a wide range of temperatures and substrates.

EV Therm 420 is low odor, has excellent flame retardant properties and meets UL 94V-0 certification.

EV Therm 420GB allows control of the adhesive gap to a diameter of 0.25mm (0.01”).

Technology/Base:	Modified Acrylic
Type of Product:	Structural Adhesive
Components:	Two Component
Curing:	Room Temperature Cure
Appearance / Color:	Off White or Amber
Consistency:	Viscous Liquid

Recommended For

Metals

Aluminum
Steel
Stainless
E-Coated Metal

Thermoplastics

Acrylic
ABS
Polycarbonate

Thermosets

Fiberglass
Phenolic
Gel Coat
Epoxy
RIM Urethane
Polyurethane
Liquid Molding Resin



Features and Benefits



- Thermally Conductive
- No Surface Preparation Required
- Excellent Adhesion Properties
- Excellent Strength to Metals, E-Coat, Thermoplastics, Thermosets, and Engineering Plastics
- High Impact Resistance
- Suitable for Easy Manual and Pneumatic Dispensing
- UL94 V0 Flame Retardancy
- 100% Reactive
- Room Temperature Cure
- 10:1 meter-mix product for ease of application
- Use on aluminum, stainless and plated steels forms tough, high strength bonds without surface preparation
- Low Odor



Plug into our EV Adhesive Technology

Download our app to learn more



EV Therm 420 & EV Therm 420GB



Technical Data

Rheology Viscosity - Resin Viscosity - Activator	100,000 - 200,000 cPs @ 25°C 40,000 - 80,000 cPs @ 25°C	Condition/Method Brookfield RV7 20 rpm Brookfield RV7 20 rpm
Density Mixed Density	1.67 g/cc	
Mix Ratio Volume Mix Ratio Weight Mix Ratio	10:1 14:1	
Uncured Material Characteristics Flash Point Open Time Fixture Time Cure Temperature and Time	>200°F 6 - 9 minutes 15 - 20 minutes Room Temperature, 24 hr	
Cured Mechanical Properties Gap Fill Dimension Hardness Tensile Strength Over Lap Shear Strength Carbon Steel Aluminum Nickel Coated Low - Carbon Steel Plated Thermal Conductivity Flame Retardancy Dielectric Strength Elongation at Break	70 Shore D >15MPa (>2,175 psi) >15MPa (>2,175 psi) >20MPa (>2,900 psi) >1.0W/(m*K) UL94 V0 23 ± 0.9 kV/mm >4%	ASTM D2240 ASTM D1002, 25°C 50% RH ASTM D1002, 25°C 50% RH ASTM D1002, 25°C 50% RH
Cured Thermal Properties Thermal Service Range	-67°F to 250°F	



General Information

The product is best used at temperatures between 65°F and 80°F. Temperatures below 65°F will slow the cure speed of the material and viscosities will be higher. Temperatures above 80°F will cause the material to cure faster and viscosities will be lower. For consistent dispensing maintain temperature in the above mentioned range.

For optimum bond strength and to insure maximum performance in the finished assembly mate parts together within the specified work time of the adhesive. Make sure the bond joint has uniform coverage and that a sufficient amount of adhesive is in the bond area. It is important to have the adhesive applied, parts aligned and positioned, within the established work times for the product. To ensure maximum performance in the finished assembly parts should remain undisturbed until the fixture time is reached.



Handling and Clean-Up

Clean up is best before the adhesive has cured. Cleaners containing NMP (N-methyl pyrrolidone) or Citrus terpene provide the best results. On cured adhesive repeat use may be required.



Typical Packaging

EV Therm 420 is conveniently packaged in 50 ml, 490 ml, pail, and drum kits. Special packaging is available upon request.



Storage and Shelf Life

Product should be stored in a cool dry place out of direct sunlight. The shelf life of EV Therm 420 is 9 months from date of manufacture. Shelf life is based on the products being stored properly at temperatures between 55°F and 75°F. Exposure to temperatures above 75°F will reduce the shelf life. This product should NEVER BE FROZEN.



Safety and Disposal

Please see the Safety Data Sheet (SDS) for proper handling and disposal instructions.

H.B. Fuller Company
9411 Corsair Road
Frankfort, IL 60423

+1-800-552-0299

www.hbfuller.com

© H.B. Fuller Company, 2021

IMPORTANT: The information, specifications, procedures and recommendations provided (information) are based on our experience and we believe this to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is users sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. The user is advised to review the specific context of the intended use to determine whether the users intended use violates any law or infringes upon any patent(s). No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

Unless otherwise noted, trademarks are property of H.B. Fuller Company or one of its affiliated entities.

NOTE TO USER: by ordering/receiving product you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, (1) the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. (2) H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply. (3) Nothing in any term shall operate to exclude or limit H.B. Fullers liability for fraud, gross negligence or for death or personal injury caused by negligence, or for breach of any mandatory implied terms unless permitted by law.