

Duroptix[™] JCR 6122 A/B KIT

Lighting

2-part, 1:1 mix ratio, clear, colorless, low modulus silicone encapsulant

Features

- 2-part
- 1:1 mix ratio
- Low Viscosity

Benefits

- Low modulus
- Clear colorless material
- Easily processed
- Excellent self-leveling
- Excellent wet-out

Composition

Polydimethylsiloxane

Applications

- LED Elastomeric Encapsulant
- ASIC, Image sensor Encapsulant

Description

DuPont silicone LED (light emitting diode) encapsulants are designed to meet the challenging needs of the LED market, including high adhesion, high purity, moisture resistance, thermal stability and optical transmittance. Silicone materials can absorb stresses caused by thermal cycling inside the package, protecting the chip and the bonding wires. With the electronics industry quickly moving toward lead-free processing, silicone encapsulants, with their demonstrated, excellent stability at reflow temperatures, are a natural fit for LED applications.

Processing/Curing

These products are also compatible with commercially available equipment and industry standard processes. These materials can be dispensed or molded depending on the product and application. OS Fluids are recommended to clean cured or uncured silicone residue from application equipment.

Typical Properties

Specification Writers: These values are not intended for use in preparing specifications. Please contact your local DuPont sales office before writing specifications on this product.

Property	Unit	Result
One or Two-Part	-	Two
Mix Ratio	-	1:1
Color	-	Colorless
Viscosity (Part A)	cP Pa-sec	350 0.4
Viscosity (Part B)	cP Pa-sec	300 0.3
Viscosity (Mixed)	cP Pa-sec	350 0.3
Heat Cure Time at 150 °C	minutes	60
Transparency at 450nm (1mm thick)	%	100
Refractive Index	-	1.41
Specific Gravity (Cured)	-	0.97
Durometer Shore A	-	34
Youngs Modulus	psi Mpa kg/cm²	160 1.1 11
Linear CTE (by TMA)	ppm/°C	320
Thermal Conductivity	btu/hr ft °F W/mK	0.294 0.17
Impurity (Na+)	ppm	0.15
Impurity (K+)	ppm	0.25
Impurity (Cl-)	ppm	0.5
Volume Resistivity	ohm*cm	9.99 E+15
Dielectric Strength	volts/mil kV/mm	536 21.1
Dielectric Constant at 1 MHz	-	2.7
Dissipation Factor at 1 MHz	-	0.0002

Adhesion

DuPont LED materials are specially designed for adhesion to commonly used LED substrates. Surface treatments such as chemical etching or plasma treatment may provide a reactive surface and improve adhesion to these types of substrates. In general, increasing the cure temperature and/or cure time will improve the ultimate adhesion

Useful Temperature Ranges

For most uses, silicone elastomers should be operational over a temperature range of -45 to 200°C (-49 to 392°F) for long periods of time. However, at both the low- and high temperature ends of the spectrum, behavior of the materials and performance in particular applications can become more complex and require additional considerations and should be adequately tested for the particular end use environment. For low-temperature performance, thermal cycling to conditions such as -55°C (-67°F) may be possible, but performance should be verified for your parts or assemblies. Factors that may influence performance are configuration and stress sensitivity of components, cooling rates and hold times, and prior temperature history. At the hightemperature end, the durability of the cured silicone elastomer is time and temperature dependent. As expected, the higher the temperature, the shorter the time the material will remain useable.

Compatibility

Certain materials, chemicals, curing agents and plasticizers can inhibit the cure of addition cure adhesives. Most notable of these include: Organotin and other organometallic compounds, Silicone rubber containing organotin catalyst, Sulfur, polysulfides, polysulfones or other sulfur containing materials, unsaturated hydrocarbon plasitcizers, and some solder flux residues. If a substrate or material is questionable with respect to potentially causing inhibition of cure, it is recommended that a small scale compatibility test be run to ascertain suitability in a given application. The presence of liquid or uncured product at the interface between the questionable substrate and the cured gel indicates incompatibility and inhibition of cure.

Usable Life And Storage

Shelf life is indicated by the "Use Before" date found on the product label. For best results, DuPont two-part products should be stored at or below 25°C (77°F). Containers should be kept tightly closed at all times to extend shelf life. Check the product label for specific storage conditions.

Packaging Information

Multiple packaging sizes are available for this product. Please contact your local distributor or DuPont representative for information on packaging size and availability.

Safe Handling Information

PRODUCT SAFETY INFORMATION REQUIRED FOR SAFE USE IS NOT INCLUDED IN THIS DOCUMENT. BEFORE HANDLING, READ PRODUCT AND MATERIAL SAFETY DATA SHEETS AND CONTAINER LABELS FOR SAFE USE, PHYSICAL AND HEALTH HAZARD INFORMATION. FOR MATERIAL SAFETY DATA SHEETS, CONTACT YOUR LOCAL DUPONT SALES OFFICE.

Health And Environmental Information

To support customers in their product safety needs, DuPont has an extensive Product Stewardship organization and a team of Product Safety and Regulatory Compliance (PS&RC) specialists available in each area. For further information, please see our website, www.dupont.com, or consult your local DuPont representative.

Limitations

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

electronics.dupont.com

For more information on Duroptix JCR 6122 A/B KIT or other DuPont products, please visit our website.

The information provided in this data sheet corresponds to our knowledge on the subject at the date of its publication. It may be subject to revision as new knowledge and experience becomes available. This information is not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for your particular purposes. Since we cannot anticipate all variations in end-use and disposal conditions. DuPont makes no warranties and assumes no liability in connection with any use of this information. It is intended for use by persons having technical skill, at their own discretion and risk. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right.

CAUTION: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see "DuPont Medical Caution Statement," H-50102-5 and "DuPont Policy Regarding Medical Applications" H-50103-5

DuPont[®], the DuPont Oval Logo, and all products, unless otherwise noted, denoted with [®], ^{ee} or [®] are trademarks, service marks or registered trademarks of affiliates of DuPont de Nemours, Inc. Copyright © 2021 DuPont de Nemours Inc. All rights reserved.

Form No. 11-3320-01 Rev 0 (05/21)