Titan Series – ANG TO

ANG T0 is a gel-state coating capable of imparting hydrophobicity to a wide variety of surfaces in a simple, one-step manufacturing process. ANG T0 is designed to protect a wide range of electronics from environmental conditions including water, salt & humidity while offering stability over a wide operating temperature range. The coating is formulated for no transfer under normal handling conditions, which makes it amenable to handling after application. The coating allows for electrical conductivity at the connection points after application. ANG T0 does not require masking or "keep out" areas in most applications, unlike standard conformal coatings. The coating is formulated with non-halogen containing materials.

Ingredients	CAS No	Concentration
C7 – C8 Isoalkanes	70024-92-9	69-71 %
Proprietary blend	Proprietary	29-31 %

Properties of Formulation	
Appearance	White/translucent
High shear viscosity (at 5000 s ⁻¹)	4-6 cP @ 25 °C
Boiling point of solvent	93-104 °C (200-220 °F)
Flash point of solvent	-11 °C (12 °F)
Environmental	Flammable, non-ozone depleting
Shalf lifa	6 months after opening
	2 years (unopened container)
Specific gravity	0.78-0.79 @ 25 °C

Properties of Applied Coating	
Typical coating thickness	5-100 µm depending on application method
Water contact angle (glass substrate)	103 °
Operating temperature	-40 to +200 °C
Dielectric strength (ASTM D149)	1.0-1.3 kV/mil

Application Techniques:

<u>Surface Preparation</u>: Typically, surfaces do not need special pre-cleaning prior to application.

<u>Application Preparation</u>: Coating needs to be agitated prior to application. Shake vessel with hand or using an overhead mixer until coating solution is re-dispersed and homogeneous.

<u>Application Options</u>: Spray/dispense by hand or with coating machine.

Curing: Air dry at room temperature until solvent has evaporated (as low as 10 seconds when sprayed).

Inspection Techniques:

- Inspect the PCB under UV light. Coated areas will fluoresce.
- Visual, the coated board will have a matte appearance.

Chemical Compatibility:

- Coating imparts hydrophobic properties to substrates.
- Coating may be susceptible to damage when exposed to certain surfactants and can be depleted by exposure to non-polar organic solvents like toluene, methylcyclohexane and MEK etc.



Safety, Handling, Storage, Shelf Life:

Coating needs to be agitated prior to application. Agitate coating by shaking vessel with hand or using an overhead mixer until coating solution is re-dispersed and homogenous. Optimal shelf life of 2 years when stored properly at 20 °C to 25 °C (68 °F to 77 °F) in a cool dry location away from heat sources or sun exposure. Humidity and high temperatures may decrease shelf life. Use an approved hazardous waste facility for disposal. Refer to the product Safety Data Sheet (SDS) for recommended work practices and other product safety information. Follow all applicable precautions and directions.

For Additional Information:

To request additional technical product data or sales assistance, contact actnano, Inc. Technical Team at (877) 655-8220. For more information on other actnano, Inc. products, please visit our website at <u>www.actnano.com</u>.

Product Use: All statements, technical information, and recommendations contained in this document are based on tests or experience that actnano, Inc. believes to be dependable. However, many factors beyond actnano, Inc. control can affect the use and effectiveness of an actnano, Inc. product in a particular use or application, including conditions under which the product is used and the time and conditions in which the product is expected to perform. Since these factors are exclusively within the user's knowledge and control, it is essential that the user evaluate the actnano, Inc. product to determine whether it is fit for a specific purpose and suitable for the user's method of application.

Warranty and Liability: actnano, Inc. makes no warranty or representation, expressed or implied, by operation of law or otherwise, as to the merchantability or fitness for a particular purpose of the goods arising out of course of dealing, custom, or usage of trade. actnano, Inc. shall not be liable for consequential, incidental, or any damages other than repair or replacement of defective goods or refund of the purchase price paid for such defective goods.

Effective 02/21 © 2022 actnano, Inc. All rights reserved. Printed in USA.



The following is a registered trademark of actnano, Inc.: Advanced nanoGUARD. The test data shown are average results of tests conducted under standard procedures and are subject to variation. Results should not be used for specification purposes. actnano, Inc. periodically updates Technical Data sheet. Before relying on any data or other information in this Technical Data Sheet, you should confirm that it is still current and has not been superseded. A Technical Data Sheet that has been superseded may contain incorrect, obsolete and/or irrelevant data and other information.

actnano, Inc. Corporate Headquarters 85 Bolton Street Cambridge, MA 02140 Telephone: 877.655.8220 Internet: www.actnano.com Email: info@actnano.com