

N109 W13300 ELLSWORTH DRIVE GERMANTOWN, WI 53022
262-253-5900 FAX 262-253-5919

DESCRIPTION:

ResinLab® UR3010 Black is a two component, room temperature curing polyurethane potting system. It is designed to cure completely at room temperature. UR3010 Black provides excellent environmental protection giving very good resistance to water, salt spray, inorganic acids and bases, and most organic solvents, while maintaining adhesion to various metals, plastics and other common assembly materials.

This product was formulated to a convenient mixing ratio of 1 to 1 by volume. It is well suited to automated meter mix operations. UR3010 Black is a DOT non-hazardous material and contains no TDI, MOCA, or other reportable substances. Part B is moisture sensitive and must be kept away from atmospheric moisture during storage. After opening a sealed container, thoroughly purge the remaining air space with dry nitrogen (or equivalent) before closing the container.

TYPICAL PROPERTIES:

All properties given are at 25 °C unless otherwise noted.

Property:	Value:	Test Method or Source:
Color	Black	Visual
Mix Ratio	Part A to Part B	Calculated
By weight	0.92 to 1	
By volume	1 to 1	
Cure Schedule	24 hours @ 25 °C 1 hour @ 85 °C	
Viscosity – Part A	1,100 cps	Rheometer parallel plate 25mm@1/s
Viscosity – Part B	250 cps	455300006291
Viscosity - Mixed	550 cps	
Specific Gravity – Part A	0.98	Calculated
Specific Gravity – Part B	1.06	
Specific Gravity - Mixed	1.02	
Pot Life, defined as the time it takes for initial mixed viscosity to double	5-10 minutes	Rheometer parallel plate 25mm@1/s 455300006291
Gel Time	70 minutes/100cc sample	455300005339/Gardco Hot Pot Gel Timer
Glass Transition Temperature/Tg	-34 °C	453560822409 by DSC
Hardness	45 Shore A	455300006287/ASTM D2240
Water Absorption	0.11% after 24 hours	457561824543/ASTM D570
Peak Exotherm	35 °C after 25 minutes for 40mL sample	455300005593 by Type K thermocouple
Elongation	50%	455300006285/ASTM D638
Coefficient of Thermal Expansion by TMA	237 ppm/ °C above Tg	455300005340/ASTM E831 TMA, 5 °C/min
Flame Resistance	Passes Resinlab testing with HB rating at 6.0 mm thickness. Not UL Certified.	UL94
Operating Temperature Range	-40 °C to 125 °C**	

** Operating Temperature Range is based on average design requirements and is not intended as a guarantee of suitability for all applications operating at that temperature.

*** This TDS contains values that have been updated. The values reported in this technical data sheet are typical values of the product, and are highly dependent on test conditions and methodology. We actively seek the most precise and accurate ways to measure and interpret performance of our products, and to update

RESINLAB L.L.C. MAKES NO EXPRESS OR IMPLIED WARRANTIES OR MERCHANTABILITY, FITNESS OR OTHERWISE with respect to its products. In addition, while the information contained herein is believed to be reliable, no warranty is expressed or implied regarding the accuracy of the data or the results to be obtained from the use thereof. All recommendations or suggestions for use are made without guarantee inasmuch as conditions of use are beyond our control. The properties given are typical values and are not intended for use in preparing specifications. Users should make their own test to determine the suitability of this product for their own purposes.

N109 W13300 ELLSWORTH DRIVE GERMANTOWN, WI 53022

262-253-5900 FAX 262-253-5919

estimated values with measured values. The formula has not been revised or changed in any way. Although the values on paper have changed, you can expect the same performance of the product.

INSTRUCTIONS:

1. Bring both components to room temperature prior to mixing.
2. Cartridge format: Mixer should be attached keeping the cartridge vertical and any air pocket purged this way. After the mixer contains material, the mixer tip can be dropped to dispense pre-bleed amount. Attach a new static mixer with each cartridge, then pre-bleed the first 3 inches of dispensed material or until a uniform color is obtained. Maintain adequate velocity during dispensing to ensure complete mixing.
3. Bulk format: weigh and mix parts A and B accurately and thoroughly, scraping sides of container often. Do not pour from mixing container, transfer to a new container as residual unmixed material may cause a tacky spot on the surface of the casting. Maintain adequate velocity during dispensing to ensure complete mixing.
4. Allow to cure undisturbed until product is fully gelled or tack-free to the touch.
5. Clean up uncured resin with suitable organic solvent such as MEK, acetone or other organic solvent.

SHELF LIFE AND STORAGE:

6 months at 25 °C Bulk. Purge Side B with inert gas after use.

12 months at 25 °C in cartridges that are foil bagged and desiccant packed.

Isocyanates are sensitive to moisture and should be kept in their original container or in a volume tank under dry nitrogen blanketing. Many isocyanates are prone to dimerization, the formation of a white precipitate. Products with minor amounts of this precipitate normally cure to full properties. Storage at 20 +/- 5 °C (60 °F to 86 °F) is recommended to ensure full shelf life.