

N109 W13300 ELLSWORTH DRIVE GERMANTOWN, WI 53022  
262-253-5900 FAX 262-253-5919

**DESCRIPTION:**

*Resinlab*<sup>®</sup> *EP1195* is a low viscosity, fast gelling, flame retardant epoxy casting resin system. It is recognized under the Component Recognition Program of Underwriters Laboratories Inc., (File # E186034, Project 96NK25676) for UL Standard 94.

*EP1195 Black* qualifies for a horizontal burn rating of 94 HB at 1/16" thickness. It also gives excellent resistance to water, salt spray, and good resistance to most inorganic acids and bases and organic solvents.

*EP1195 Black* was formulated to a 2A:1B by volume mix ratio for use in side-by-side dispensing cartridges and meter/mix and dispense equipment. Cure is normally achieved at room temperature although an elevated temperature cure schedule can be used to reach final properties quickly after product has gelled. EP1195 is a general encapsulant designed for small to medium mass potting applications.

**TYPICAL PROPERTIES:**

All properties given are at 25 °C unless otherwise noted.

<b>Property:</b>	<b>Value:</b>	<b>Test Method or Source:</b>
<b>Color</b>	Black	Visual
<b>Mix Ratio</b>	Part A to Part B	Calculated
<b>Mix Ratio by weight</b>	2.8 to 1	
<b>Mix Ratio by volume</b>	2 to 1	
<b>Cure Schedule</b>	24 hrs @ 25 °C 1 hr @ 65 °C	
<b>Viscosity - Part A</b>	5,000 cP	Rheometer parallel plate 25mm @ 1/s
<b>Viscosity - Part B</b>	1,400 cP	455300006291
<b>Viscosity - Mixed</b>	2,800 cP	
<b>Specific Gravity - Part A</b>	1.37	Calculated
<b>Specific Gravity - Part B</b>	0.97	
<b>Specific Gravity - Mixed</b>	1.24	
<b>Pot Life defined as the time it takes for initial mixed viscosity to double</b>	10 minutes	Rheometer parallel plate 25mm @1/s 455300006291
<b>Hardness</b>	85 Shore D	455300006287/ASTM D2240
<b>Glass Transition Temperature/Tg</b>	42 °C	453560822409 by DSC
<b>Water Absorption</b>	0.18 %	24 hr immersion 457561824543/ASTM D570
<b>Tensile Properties:</b>		4535601224470/ASTM D638
<b>Strength</b>	5,400 psi	
<b>Elongation</b>	1.2 %	
<b>Modulus</b>	450,000 psi	
<b>Lap Shear Strength</b>		4535601224468/ASTM D1002
<b>0.010" Bond Line, Al to Al</b>	3,000 psi	

N109 W13300 ELLSWORTH DRIVE GERMANTOWN, WI 53022  
262-253-5900 FAX 262-253-5919

<b>Property:</b>	<b>Value:</b>	<b>Test Method or Source:</b>
<b>Compressive Properties:</b>		4535601224467/ASTM D695
<b>Ultimate Strength</b>	23,500 psi	
<b>Modulus</b>	116,000 psi	
<b>Flame Resistance UL Certified, File #E186034</b>	Passes with HB Rating @ 1/16"	45376013225560/UL94HB
<b>Thermal Conductivity by LFA</b>	0.3 W/m.K	453560822409/ASTM E1461
<b>Volume Resistivity</b>	6.5 x 10 <sup>15</sup> ohm-cm	455300006612/ASTM D257 @ 18 °C @ 22 %RH
<b>Surface Resistivity</b>	5.2 x 10 <sup>16</sup> ohm/sq	455300006612/ASTM D257 @ 18 °C @ 22 %RH
<b>Dielectric Constant &amp; Dissipation Factor</b>		455300006513/ASTM D150
<b>@ 100 Hz</b>	3.4, 0.01	
<b>@ 100 kHz</b>	3.2, 0.01	
<b>AC Dielectric Strength</b>	440 V/mil *	ASTM D149 Method A, immersed in ASTM D3487 Type II Oil
<b>Coefficient of Thermal Expansion by TMA</b>		455300005340/ASTM E831 TMA, 5 °C/min
<b>below Tg</b>	55 ppm/°C	
<b>above Tg</b>	190 ppm/°C	
<b>Operating Temperature Range</b>	-40 to 150 °C**	
<b>Relative Thermal Index (RTI)</b>	90 °C	UL746B, Table 7.1 Generic Value Based on Composition

\* Asterisk denotes values considered typical to associated resin systems or extrapolated from other test results.

\*\* Operating Temperature Range is based on average design requirements and is not intended as a guarantee of suitability for all applications operating at that temperature.

\*\*\* This TDS contains values that have been updated. The values reported in this technical data sheet are typical values of the product, and are highly dependent on test conditions and methodology. We actively seek the most precise and accurate ways to measure and interpret performance of our products, and to update estimated values with measured values. The formula has not been revised or changed in any way. Although the values on paper have changed, you can expect the same performance of the product.

#### **INSTRUCTIONS:**

1. Bring to room temperature prior to use.
2. Cartridge format: Mixer should be attached keeping the cartridge vertical and any air pocket purged this way. After the mixer contains material, the mixer tip can be dropped to dispense pre-bleed amount. Attach a new static mixer with each cartridge, then pre-bleed the first 3 inches of dispensed material or until a uniform color is obtained. Maintain adequate velocity during dispensing to ensure complete mixing.

---

N109 W13300 ELLSWORTH DRIVE GERMANTOWN, WI 53022  
262-253-5900 FAX 262-253-5919

3. Bulk format: stir until homogeneous weigh and mix parts A and B accurately and thoroughly, scraping sides of container often. Do not pour from mixing container, transfer to a new container as residual unmixed material may cause a tacky spot on the surface of the casting. Maintain adequate velocity during dispensing to ensure complete mixing.
4. Clean up uncured resin with suitable organic solvent such as MEK or acetone.
5. Allow to cure undisturbed until product is fully gelled or tack-free to the touch.

**SHELF LIFE AND STORAGE:**

12 months at 25 °C.  
Specialty packaging may be less.

Many epoxy resin systems are prone to crystallization as epoxy resin is a super-cooled fluid. This condition may give the product a gritty or grainy appearance (or hazy in clear products). Products in this state will not usually cure to normal and expected properties. In extreme cases it may appear solid and cured. Fluctuating temperatures (within 5 to 50 °C) aggravate this phenomenon. Heating the individual component to 50 to 60 °C while stirring can usually restore products to original state. Storage at 25 +/- 10 °C is optimum for most products.