



STYCAST 2850FT/Catalyst 23LV

June 2010

PRODUCT DESCRIPTION

STYCAST 2850FT/Catalyst 23LV provides the following product characteristics:

Technology	Epoxy
Appearance (Resin)	Black
Components	Two component - requires mixing
Mix Ratio, by weight - Resin : Hardener	100 : 7.5
Mix Ratio, by volume - Base : Hardener	100 : 17.5
Product Benefits	<ul style="list-style-type: none"> • Thermally conductive • Low CTE • Electrically Insulating • High strength • Long pot life • Low color • Low viscosity • Excellent thermal shock resistance
Cure	Room temperature cure
Application	Encapsulant
Operating Temperature	-65 to 105 °C
Surfaces	Glass

STYCAST 2850FT/Catalyst 23LV is recommended for encapsulation of components that require heat dissipation and thermal shock properties.

STYCAST 2850FT can be used with a variety of catalysts. For more information on mixed properties when used with other available catalysts, please contact your local technical service representative for assistance and recommendations.

TYPICAL PROPERTIES OF UNCURED MATERIAL

Part A Properties 2850FT

Viscosity, Brookfield, 25 °C, mPa·s (cP):
Speed 5 rpm, # 7 200,000 to 250,000

Specific Gravity 2.35 to 2.45

Shelf Life @ 25°C, months 12

Flash Point - See MSDS

Part B Properties Catalyst 23LV

Viscosity @ 25 °C, mPa·s (cP) 20 to 30

Flash Point - See MSDS

Mixed Properties

Mixed Viscosity, mPa·s (cP) 5,600

Specific Gravity 2.19

Working Time, 100 g mass, @ 25°C, minutes 60

Flash Point - See MSDS

TYPICAL CURING PERFORMANCE

Cure Schedule

16 to 24 hours @ 25°C or

4 to 6 hours @ 45°C or

2 to 4 hours @ 65°C

Post Cure

Post Cure: 2 to 4 hours at the highest expected use temperature

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties:

Coefficient of Thermal Expansion ASTM D 3386:

Below Tg, ppm/°C	39.4
Above Tg, ppm/°C	111.5

Glass Transition Temperature, ISO 11357-2, °C 68

Thermal Conductivity, W/mk 1.1

Shore Hardness, ISO 868, Durometer D 92

Water Absorption, ISO 62 24 hours, % 0.02

Linear Shrinkage, cm/cm 0.003

Compressive Strength, psi 17,400

Flexural strength, ASTM D790 N/mm² 106
(psi) (15,300)

Electrical Properties:

Volume Resistivity, IEC 60093, Ω·cm >1×10¹⁵

Dielectric Constant / Dissipation Factor, IEC 60250:
1mHz 5.36 / 0.051

Dielectric Breakdown Strength, IEC 60243-1, kV/mm 14.8

GENERAL INFORMATION

For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).



DIRECTIONS FOR USE

1. Complete cleaning of the substrates should be performed to remove contamination such as oxide layers, dust, moisture, salt and oils which can cause poor adhesion or corrosion in a bonded part.
2. Some separation of components is common during shipping and storage. For this reason, it is recommended that the contents of the shipping container be thoroughly mixed prior to use.
3. Accurately weigh resin and hardener into a clean container in the recommended ratio.
4. Blend components by hand, using a kneading motion, for 2 to 3 minutes and scrape the bottom and sides of the mixing container frequently to produce a uniform mixture.
5. If possible, power mix for an additional 2 to 3 minutes. Avoid high mixing speeds which could entrap excessive amounts of air or cause overheating of the mixture resulting in reduced working life.
6. To ensure a void-free embedment, vacuum deairing should be used to remove any entrapped air introduced during the mixing operation.
7. Vacuum deair mixture at 1 to 5 mm mercury. The foam will rise several times the liquid height and then subside.
8. Continue vacuum deairing until most of the bubbling has ceased. This usually takes 3 to 10 minutes.
9. To facilitate deairing in difficult to deair materials, add a few drops of an air release agent, such as ANTIFOAM 88 into 100 grams of mixture.
10. Gentle warming will also help, but pot life will be shortened.
11. Pour mixture into cavity or mold.
12. Gentle warming of the mold or assembly reduces the viscosity. This improves the flow of the material into the unit having intricate shapes or tightly packed coils or components.
13. Further vacuum deairing in the mold may be required for critical applications.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage: 25 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$
 $\text{kV/mm} \times 25.4 = \text{V/mil}$
 $\text{mm} / 25.4 = \text{inches}$
 $\text{N} \times 0.225 = \text{lb}$
 $\text{N/mm} \times 5.71 = \text{lb/in}$
 $\text{N/mm}^2 \times 145 = \text{psi}$
 $\text{MPa} \times 145 = \text{psi}$
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$
 $\text{mPa}\cdot\text{s} = \text{cP}$

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all marks used above on this data sheet are trademarks and/or registered trademarks of Henkel and/or its affiliates in Germany and elsewhere.

Reference 0.5