

LOCTITE STYCAST 2762

June 2024

PRODUCT DESCRIPTION

LOCTITE STYCAST 2762 provides the following product characteristics:

Technology	Epoxy
Appearance (Resin)	Black
Product Benefits	<ul style="list-style-type: none"> High temperature resistance Low coefficient of thermal expansion Low shrinkage during cure Excellent adhesion to metals, glass or plastic materials
Cure	Heat cure
Application	Potting, Encapsulant

LOCTITE STYCAST 2762 is used to embed electronic compounds to hermetically sealed metal surfaces. It is also designed to act as a high temperature resistant protective coating.

LOCTITE STYCAST 2762FT can be used with a variety of catalysts. For more information on mixed properties when used with other available catalysts, please contact your local technical service representative for assistance and recommendations.

CATALYST DESCRIPTION

LOCTITE CAT 14 provides the following product characteristics:

Product Benefits	<ul style="list-style-type: none"> Powdered epoxy hardener Use for powdered for paste applications Chemical resistant High temperature performance Long work life
Cure	Heat cure
Mix Ratio, by weight - Material:Catalyst	100 : 8

LOCTITE CAT 17 provides the following product characteristics:

Product Benefits	<ul style="list-style-type: none"> Preferred for easy pourability High temperature resistant Long work life High temperature performance Chemical resistant
Cure	Heat cure
Mix Ratio, by weight - Material:Catalyst	100 : 10

TYPICAL UNCURED PROPERTIES

LOCTITE STYCAST 2762

Viscosity @ 25 °C,	90
Density, g/cm ³	2.3
Shelf Life @ 18 to 25°C (from date of manufacture), days	365
Flash Point - See SDS	

TYPICAL CURING PERFORMANCE

Cure Schedule

LOCTITE STYCAST 2762 with LOCTITE CAT 14

3 hours @ 120°C
For improved high temperature properties, cure for an additional 3 hours @ 150°C.

LOCTITE STYCAST 2762 with LOCTITE CAT 17

Regular Castings
3 hours @ 90°C plus 3 hours @ 150°C

For larger or extremely large castings
16 hrs @ 65°C, plus 3 hrs @ 120°C, plus 3 hrs @ 150°C

Recommended Gel Time

30 minutes @ 90°C

It is useful to gel LOCTITE STYCAST 2762 for certain applications to prevent filler setting.

Add LOCTITE CAT 17 to LOCTITE STYCAST 2762 per recommended mix ratio plus 2.5 parts LOCTITE CAT 16 as an accelerator. Pot life will be shortened. Continue to cure as indicated.

A post cure of 16 hours @ 180°C may also be used.

The above cure profiles are guideline recommendations. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

TYPICAL PROPERTIES OF CURED MATERIAL

LOCTITE STYCAST 2762 with LOCTITE CAT 17

Physical Properties

Hardness, Shore D	90
Coefficient of Linear Thermal Expansion, ppm/°C	20
Thermal Conductivity, W/(m-K)	1.4
Flexural Modulus :	
@ 20 °C	N/mm ² 8,000 (psi) (1,160,302)
@ 150 °C	N/mm ² 5,400 (psi) (783,203)
Compressive Modulus of Elasticity	N/mm ² 8,200 (psi) (1,189,309)
Moisture Absorption, 24 hrs immersion, %	0.02
Operating temperature, °C	-20 to +230
Machinability	must be ground

Electrical Properties

Volume Resistivity, ohms-cm:	
@ 20°C	1×10 ¹⁶
@ 150 °C	1×10 ¹¹
Dielectric Strength, kV/mm:	
@ 20 °C	16
@ 150°C	14.8
Dielectric Constant / Dissipation Factor:	
@ 60Hz	4.3/0.007
@ 1MHz	3.9/0.009
@ 1GHz	3.3/0.012

TYPICAL PERFORMANCE OF CURED MATERIAL**LOCTITE STYCAST 2762 with LOCTITE CAT 17****Miscellaneous**

Compressive Strength	N/mm ²	120
	(psi)	(17,404)
Flexural Strength:		
@ 20 °C	N/mm ²	70
	(psi)	(10,152)
@ 150 °C	N/mm ²	50
	(psi)	(7,251)

GENERAL INFORMATION

For safe handling information on this product, consult the Safety Data Sheet, (SDS).

DIRECTIONS FOR USE**LOCTITE STYCAST 2762 with LOCTITE CAT 14**

- Mix thoroughly in the container in which it is received. Weight out the required amount of Parts A and B. Mix the dry powdered LOCTITE CAT 14 into LOCTITE STYCAST 2762 at room temperature. Extreme care should be taken to insure thorough mixing. The resulting mixture is almost paste consistency and is stable for at least one day at room temperature. Pour into mold or cavity. Vibration will improve flowability. For sealing applications, apply to the cleaned surfaces and squeeze out the excess.
- Cure as recommended.

LOCTITE STYCAST 2762 with LOCTITE CAT 17

- Use of LOCTITE CAT 17 is preferred for easy pourability.
- Mix thoroughly in the container in which it is received. Weight out the required amount of Parts A and B.
- LOCTITE CAT 17 may be solid at room temperature. Material will become liquid when warmed to about 65°C. Warming to about 65°C will improve flowability. If desired, the catalyzed resin can be maintained at about 65°C. At this temperature, pot life is at least 8 hours. The item to be embedded and mold can also be preheated.
- Pour mixture in mold or cavity. Cure as recommended.

Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

Optimal Storage : 18 to 25 °C

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical

Service Center or Customer Service Representative.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

Conversions

(°C x 1.8) + 32 = °F
 kV/mm x 25.4 = V/mil
 mm / 25.4 = inches
 N x 0.225 = lb
 N/mm x 5.71 = lb/in
 psi x 145 = N/mm²
 MPa = N/mm²
 N·m x 8.851 = lb·in
 N·m x 0.738 = lb·ft
 N·mm x 0.142 = oz·in
 mPa·s = cP

Disclaimer**Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 2